

Compilation on Synthesis, Characterization and Properties of Silicon and Boron Carbonitride Films

P. Hoffmann¹, N. Fainer², M. Kosinova², O. Baake¹ and W. Ensinger¹

¹*Technische Universität Darmstadt, Materials Science*

²*Nikolaev Institute of Inorganic Chemistry, SB RAS*

¹*Germany*

²*Russia*

1. Introduction

During the last years the interest in silicon and boron carbonitrides developed remarkably. This interest is mainly based on the extraordinary properties, expected from theoretical considerations. In this time significant improvements were made in the synthesis of silicon carbonitride SiC_xN_y and boron carbonitride BC_xN_y films by both physical and chemical methods.

In the Si-C-N and B-C-N ternary systems a set of phases is situated, namely diamond, SiC, $\beta\text{-Si}_3\text{N}_4$, c-BN, B_4C , and $\beta\text{-C}_3\text{N}_4$, which have important practical applications. SiC_xN_y has drawn considerable interest due to its excellent new properties in comparison with the Si_3N_4 and SiC binary phases. The silicon carbonitride coatings are of importance because they can potentially be used in wear and corrosion protection, high-temperature oxidation resistance, as a good moisture barrier for high-temperature industrial as well as strategic applications. Their properties are low electrical conductivity, high hardness, a low friction coefficient, high photosensitivity in the UV region, and good field emission characteristics. All these characteristics have led to a rapid increase in research activities on the synthesis of SiC_xN_y compounds. In addition to these properties, low density and good thermal shock resistance are very important requirements for future aerospace and automobile parts applications to enhance the performance of the components. SiC_xN_y is also an important material in micro- and nano-electronics and sensor technologies due to its excellent mechanical and electrical properties. The material possesses good optical transmittance properties. This is very useful for membrane applications, where the support of such films is required (Fainer et al., 2007, 2008; Mishra, 2009; Wrobel, et al., 2007, 2010; Kroke et al., 2000).

The structural similarity between the allotropic forms of carbon and boron nitride (hexagonal BN and graphite, cubic BN and diamond), and the fact that B-N pairs are isoelectronic to C-C pairs, was the basis for predictions of the existence of ternary BC_xN_y compounds with notable properties (Samsonov et al., 1962; Liu et al., 1989; Lambrecht & Segall, 1993; Zhang et al., 2004). This prediction has stimulated intensive research in the last 40 years towards the synthesis of ternary boron carbonitride. BC_xN_y compounds are interesting in both the cubic (c-BCN) and hexagonal (h-BCN) structure. On the one hand, the

synthesis of c-BCN is aimed at the production of super-hard materials since properties between those of cubic boron nitride (c-BN) and diamond would be obtained (Kulisch, 2000; Solozhenko et al., 2001). On the other hand, h-BCN has potential applications in microelectronics (Kawaguchi, 1997), since it is expected to behave as semiconductor of varying band gap depending on the composition and atomic arrangement (Liu et al., 1989), or in the production of nanotubes (Yap, 2009).

2. Methods of synthesis

Considerable efforts in the synthesis of SiC_xN_y and BC_xN_y films have been made by a large variety of deposition methods (both physical and chemical techniques).

2.1 Physical Vapour Deposition (PVD)

2.1.1 Silicon carbonitrides

2.1.1.1 Laser based methods

CSi_xN_y thin films were grown on Si(100) substrates by pulsed laser deposition (PLD) assisted by a radio frequency (RF) nitrogen plasma source (Thäringen et al., 1999). Up to about 30 at% nitrogen and up to 20 at% silicon were found in the hard amorphous thin films (23 GPa).

SiC_xN_y films were grown on silicon substrates using the pulsed laser deposition (PLD) technique (Soto et al., 1998; Boughaba et al., 2002). A silicon carbide (SiC) target was ablated by the beam of a KrF excimer laser in a nitrogen (N_2) background gas. Smooth, amorphous films were obtained for all the processing parameters. The highest values of hardness and Young's modulus values were obtained in the low-pressure regime, in the range of 27–42 GPa and 206–305 GPa, respectively.

SiC_xN_y thin films have been deposited by ablation a sintered silicon carbide target in a controlled N_2 atmosphere (Trusso et al., 2002). The N_2 content was found to be dependent on the N_2 partial pressure and did not exceed 7.5%. A slight increase of sp^3 hybridized carbon bonds has been observed. The optical band gap E_g values were found to increase up to 2.4 eV starting from a value of 1.6 eV for a non-nitrogenated sample.

2.1.1.2 Radio frequency reactive sputtering

Nanocrystalline SiC_xN_y thin films were prepared by reactive co-sputtering of graphite and silicon on Si(111) substrates (Cao et al., 2001). The films grown with pure nitrogen gas are exclusively amorphous. Nanocrystallites of 400–490 nm in size were observed by atomic force microscopy (AFM) in films deposited with a mixture of N_2 +Ar.

Amorphous silicon carbide nitride thin films were synthesized on single crystal Si substrates by RF reactive sputtered silicon nitride target in a CH_4 and Ar atmosphere (Peng et al., 2001). The refractive index decreased with increasing target voltage.

SiCN films were deposited by RF reactive sputtering and annealed at 750°C in nitrogen atmosphere (Du et al., 2007). The as-deposited film did not show photoluminescence (PL), whereas strong PL peaks appeared at 358 nm, 451 nm, and 468 nm after annealing.

The a- SiC_xN_y thin films were deposited by reactive sputtering from SiC target and N_2 /Ar mixtures (Tomasella et al., 2008). For more than vol.30 % of nitrogen in the gas mixture, a N-saturated Si-C-N film was formed. All the structural variations led to an increase of the optical band gap from 1.75 to 2.35 eV.

SiCN films were deposited on Si(100) substrates by RF sputtering methods using SiC targets and N₂ as reactant gas (Chen et al., 2009). A high substrate temperature is not favorable for the N₂ incorporation into the SiCN films. The stoichiometry of these SiCN films was given as Si_{32.14}C_{39.10}N_{28.76}, which is close to SiCN. The film grown at room temperature showed a light structure.

2.1.1.3 Radio frequency magnetron sputtering

Amorphous SiC_xN_y films were prepared by RF magnetron reactive sputtering using sintered SiC targets and a mixture of Ar and N₂ (99.999%) (Xiao et al., 2000; Li et al., 2009). The results revealed the formation of complex networks among the three elements Si, C and N, and the existence of different chemical bonds in the SiC_xN_y films such as C-N, C=N, C≡N, Si-C and Si-N. The stoichiometry of the as-deposited films was found to be close to SiCN (Si_{36.9}C_{30.4}N_{32.7}).

Nanostructured and amorphous SiC_xN_y films have been deposited by magnetron sputtering of SiC under reactive gas environment at 700-1000°C (Lin et al., 2002). Gas mixtures containing CH₄ and N₂ with various ratios were used for deposition. As the CH₄/N₂ ratio was increased, the SiC_xN_y films changed from mirror-like smooth films to column-like and ridge-like C-rich SiC_xN_y nanostructures. The chemical composition of these films varied from Si₃₁C₃₅N₂₅O₉ up to Si₅C₈₉N₃O₃.

SiCN films have been produced by means of reactive magnetron sputtering of a Si target in an Ar/N₂/C₂H₂ atmosphere (Hoche et al, 2008). Depending on their position in the Si-C-N phase diagram, the hardness of the films varies over a broad range, with maximum values at about 30 GPa, while Young's modulus remains in a narrow range around 200 GPa.

The nano-composite SiCN thin films on silicon, glass and steel have been produced by magnetron sputtering at different substrate temperatures ranging from 100°C to 500°C at 400 W RF power from SiC targets in Ar/N₂ atmosphere (Mishra et al, 2008; Mishra, 2009). The nanocomposite SiCN films were found to have nanocrystals of 2-15 nm of the β-C₃N₄ phase distributed in an amorphous matrix. The microhardness values of the films were found to vary between 25-47 GPa and was dependent on deposition and substrate temperatures.

SiCN films were deposited on n-type Si(100) and glass substrates by RF reactive magnetron sputtering of a polycrystalline silicon target under mixed reactive gases of C₂H₂ and N₂ (Peng et al., 2010). The SiCN films deposited at room temperature are amorphous, and the C, Si and O compositions in the films are sensitive to the RF power, except N.

2.1.1.4 Reactive DC magnetron sputtering

Si-C-N films were deposited on p-type Si(100) substrates by DC magnetron co-sputtering of silicon and carbon in nitrogen-argon mixtures using a single sputter target with variable Si/C area ratios (Vlcek et al, 2002). The substrate temperature was adjusted at T_s=600°C by an ohmic heater and the RF-induced negative substrate bias voltage, U_b was 500V. With a rising Ar concentration in the gas mixture, the Si content in the films rapidly increases (from 19 to 34 at.% for a 40 at.% Si fraction in the erosion target area), while the C content decreases (from 34 to 19 at.%) at an almost constant N concentration (39-43 at.%). As a result, the N-Si and Si-N bonds dominate over the respective N-C and Si-O bonds, preferred in a pure N₂ discharge, and the film hardness increases up to 40 GPa.

2.1.1.5 Ion Beam Sputtering Assisted Deposition (IBAD)

SiCN films have been successfully synthesized at a temperature below 100°C from an adenine (C₅N₅H₅)-silicon-mixed target sputtered by an Ar ion beam (Wu et al., 1999). The chemical composition of these films varied from Si₂₄C₆₀N₁₃O₃ up to Si₃₂C₃₄N₁₉O₁₅. Only amorphous films for Si-rich SiCN were obtained, while the films with low Si incorporation and deposited at high Ar ion beam voltage contained nanocrystallites.

High-dose nitrogen ion implantation into SiC is a possible way to produce a-SiC_xN_y (Ishimaru et al., 2003; Suvorova et al., 2009). SiC crystal target was implanted by nitrogen ions at ambient temperature up to a fluence of 5×10¹⁷ N⁺/cm², followed by thermal annealing at 1500°C for 30 min. a-SiC_xN_y possesses an intermediate bond length between Si–C and Si–N.

2.1.1.6 Dual Ion Beam Sputtering (DIBS)

SiCN films were deposited by dual ion beam sputtering (DIBS) of a SiC target in mixed Ar/N₂ atmosphere at 100°C (Zhou et al., 2010). The results showed that the variations of surface roughness and hardness for the SiCN films with the assisting ion beam energy were in the range of 7–27 nm and 23–29 GPa, respectively.

2.1.1.7 Combined High Power Pulse Magnetron Sputtering (HPPMS) - DC sputtering

Amorphous SiCN coatings were synthesized by conventional DC and RF magnetron sputtering as well as with a combined sputtering process using one target in the DC mode and one target in the HPPMS mode (Hoche et al, 2010). The SiCN's Young's modulus of approximately 210 GPa makes SiCN coatings promising for the deposition onto steel. Structural differences can originate from the different carbon sources. By using acetylene a distinct amount of carbon ions can be achieved in the plasma.

2.1.1.8 An arc enhanced magnetic sputtering hybrid system


SiCN hard films have been synthesized on stainless steel substrates by an arc enhanced magnetic sputtering hybrid system using a Si target and graphite target in gases mixed of Ar and N₂ (Ma et al., 2008). The microstructure of the SiCN films with a high silicon content are nanocomposites in which nano-sized crystalline C₃N₄ hard particles are embedded in the amorphous SiCN matrix. The hardness of the SiCN films is found to increase with increasing silicon contents, and the maximum hardness is 35 GPa. The SiCN hard films show a low friction coefficient of 0.2.

2.1.1.9 Microwave Electron Cyclotron Resonance (ECR) plasma enhanced unbalance magnetron sputtering

SiCN thin films were prepared by microwave ECR plasma enhanced unbalanced magnetron sputtering (Gao et al., 2007). The Si–C–N bonds increased from 17.14% to 23.56% while the graphite target voltage changed from 450V to 650V. The optical gap value progressively decreases from 2.65 to 1.95 eV as the carbon content changes from 19.7 at.% to 26.4 at.%. The maximum hardness of the thin films reaches 25 GPa.

2.1.2 Boron carbonitrides

The goal to synthesize boron carbonitride with the participation of the gas phase and to examine its structure and properties was put forward by Kosolapova et al. (Kosolapova et al., 1971). The product corresponding to BCN composition, as indicated by chemical analysis, was obtained by nitrogenization of a mixture of amorphous boron and carbon black in nitrogen or ammonia within the temperature range 2073–2273K.



The BCN obtained according to reactions (1) and (2) was characterized by a somewhat larger unit cell parameter (0.6845 nm) than that of hexagonal boron nitride (0.6661 nm) or graphite (0.6708 nm). As the authors reported, the BCN powder was oxidized at 1073 K. This result indicates that this material did not contain carbon or boron carbide, because the interaction of these compounds with oxygen starts already at a temperature of 773 and 873 K, respectively.

2.1.2.1 Laser based methods

Using a disk combining together two semidisks, one of h-BN and one of graphite, as target, Perrone et al. deposited at room temperature polycrystalline films: a mixture of c-BCN and h-BCN by PLD in vacuum and amorphous h-BN in nitrogen gas ambient (Perrone, 1998; Dinescu, 1998). The targets used by Teodorescu et al. for film deposition were both a half C and half BN disk and a $\frac{3}{4}$ h-BN and $\frac{1}{4}$ C disk (Teodorescu et al., 1999). The influence of substrate temperature on composition and crystallinity of BCN films has been investigated. Films deposited on heated substrates are amorphous, while films produced at room temperature are polycrystalline. Wada et al. deposited BCN films from a hot-pressure BCN target consisting of graphite and h-BN powder in an 1:1 ratio (Wada et al., 2000). Later the same group (Yap et al., 2001) demonstrated that BCN films with the composition of BC_2N can be obtained by RF plasma-assisted pulsed laser deposition (PLD) at 800°C on Si substrate, but these films were carbon doped BN compounds (BN:C). Furthermore, hybridized BCN films can be deposited on Ni substrate under similar synthesis conditions. Another laser-based technique was pulsed laser ablation of a sintered B_4C target in the environment of a nitrogen plasma generated from ECR microwave discharge in nitrogen gas, with growing films being simultaneously bombarded by the low-energy nitrogen plasma stream (Ling, 2002; Pan, 2003). The prepared films are composed of boron, carbon, and nitrogen with an average atomic B/C/N ratio of 3:1:3.8. It was found that the assistance of the ECR nitrogen plasma facilitated nitrogen incorporation and film formation. Nitrogen ion beam generated by a Kaufman ion gun was applied to assist reactive PLD of BCN thin films from sintered B_4C (Ying, 2007). It is demonstrated that with nitrogen ion beam assistance, BCN films with nitrogen content of more than 30 at.% can be synthesized. The bonding characteristics and crystalline structure of the films were also found to be influenced by the substrate temperature. With increasing substrate temperature to 600°C, the BCN films exhibit nanocrystalline nature. Recently, amorphous BCN films were produced by laser ablation of B_4C target in nitrogen atmosphere (Yang, 2010).

2.1.2.2 Radio frequency reactive sputtering

Ternary boron carbonitride thin films were prepared by RF reactive sputtering method from a hexagonal h-BN target in an Ar- CH_4 atmosphere. The films with different C contents were obtained by varying the CH_4 partial pressure. The films deposited under the optimum conditions exhibit a structure of polycrystalline BC_2N (Yue et al., 2000).

2.1.2.3 Radio frequency magnetron sputtering

BCN films of diverse compositions have been deposited by magnetron sputtering, mainly from h-BN and graphite targets (Ulrich et al., 1998, 1999; Zhou et al., 2000; Lei et al., 2001; Yokomichi et al., 2002; Liu et al., 2005, 2006) or B_4C target (Louza et al., 2000; Martinez et al., 2001; Bengy et

al., 2009; Nakao et al., 2010) or B and graphite targets (Byon et al., 2004; Kim et al., 2004; Zhuang et al., 2009). In most cases the films were amorphous. It has been concluded that various intermediate compounds were obtained under different experimental conditions. Ulrich et al. (Ulrich et al., 1998, 1999) still obtained BCN films with C and BN phase separation. Liu et al. (Liu et al., 2005, 2006) also obtained the films of atomic-level BCN compounds from h-BN and graphite targets under various experimental conditions. In addition to the synthesis of microscopic ternary BCN films, the correlation between the chemical composition of films and the choice of targets has also been discussed. Lousa et al. (Lousa et al., 2000) found that the atomic ratio of B/C in the films kept almost constant as 4:1, similar to that of the target (B_4C).

2.1.2.4 Reactive DC magnetron sputtering

Reactive DC magnetron sputtering technique has been investigated to grow BC_xN_y films. Thin films were synthesized by pulsed DC magnetron sputtering from BN + C (Martinez et al., 2002) or B_4C (Johansson et al., 1996; Freire et al., 2001; Reigada et al., 2001; Chen et al., 2006) or B_4C + C (Xu et al., 2006a, 2006b) targets in Ar/ N_2 atmosphere. Effects of target power, target pulse frequency, substrate bias and pulse frequency on surface roughness were studied. Linss et al. used a set of targets with different B/C ratios (B, B_4C , BC, BC_4 , C) (Linss et al., 2004a, 2004b). Real ternary phases, presenting BCN bonds, were only found at low nitrogen contents; in boron-rich films. At higher nitrogen contents, the FTIR and XPS spectra were dominated by BN, CC/CN and $C\equiv N$ bonds, suggesting a phase separation into BN and C/ CN_x phases.

2.1.2.5 Ion Beam Assisted Deposition (IBAD)

During the last 10 years ion beam assisted deposition is used for boron carbonitride film deposition. The films were deposited by evaporating B_4C or B targets to produce BCN films. The assistance was performed with ions from the precursor gas nitrogen. IBAD has permitted to cover a wide range of compositions as a function of deposition parameters. Albella's group (Gago et al., 2000, 2001, 2002a, 2002b, 2002c) also reported that the c-BCN coatings had been synthesized successfully through evaporating B_4C target and the simultaneous bombardment of the ions from the mixture gas $Ar+N_2+CH_4$. Subsequently, they paid much attention to studying the chemical composition and bonding of the BCN coatings (Caretti et al., 2003, 2004, 2007, 2010). The structure of the BC_xN compounds grown by IBAD has shown to be quite sensitive to the C concentration (Caretti et al., 2010), as expected for compounds with supposedly different mechanical and electronic properties. The structure varies from a hexagonal laminar phase when $x < 1$ to a fully amorphous compound for $x \geq 4$. For $x = 1$, the compound consists of curved hexagonal planes in the form of a fullerene-like structure, being an intermediate structure in the process of amorphization due to C incorporation (Caretti et al., 2007, 2010).

Boron carbonitride (BCN) coatings were deposited on Si(100) wafers and Si_3N_4 disks by using IBAD from a boron carbide target. The BCN coatings were synthesized by the reaction between boron and carbon vapor as well as nitrogen ion simultaneously. The influence of deposition parameters such as ion acceleration voltage, ion acceleration current density and deposition ratio on the surface roughness and mechanical properties of the BCN coatings was investigated (Fei Zhou et al., 2006a, 2006b, 2006c).

2.1.2.6 Cathodic arc plasma deposition

Tsai et al. demonstrated that boron carbon nitride (BCN) thin films were deposited on Si (100) substrates by reactive cathodic arc evaporation from graphite and B_4C composite

targets. Ar+N₂ gases were added to the deposition atmosphere under pressure of 0.1–0.3 Pa. The deposition parameters included the substrate bias, the flow rate and ratio of the reactive gases have been varied. The analytical results (FEGSEM, HRTEM and XRD, see section 4) showed that the films revealed an amorphous cauliflower-like columnar structure (Tsai, 2007).

2.1.2.7 Ion beam implantation

BCN hybrid thin films were grown from ion beam plasma of borazine (B₃N₃H₆) on highly oriented pyrolytic graphite substrate at room temperature, 600°C, and 850°C. The substrate temperature and ion fluence were shown to have significant effects on the coordination and elemental binding states in BCN hybrid films (Uddin et al., 2005a, 2005b, 2006)

2.1.2.8 Electron-cyclotron-wave-resonance PACVD

Nanocrystalline BCN thin films were prepared on n-type Si(100) wafers using the electron-cyclotron-wave-resonance plasma-assisted chemical vapor deposition, whereby the energy for precursor ions was adjusted between 70 and 180 eV. ECR plasma of nitrogen was asymmetrically RF biased to sputter the high-purity h-BN/graphite target (Cao, 2003).

2.2 Chemical Vapor Deposition (CVD)

Chemical vapor deposition (CVD) is one of the potential growing techniques of SiC_xN_y and BC_xN_y films.

2.2.1 Silicon carbonitrides

2.2.1.1 Thermal CVD

The Si-C-N deposits were obtained by CVD using the mixture of gaseous compounds such as SiCl₄, NH₃, H₂, and C₃H₈ at very high temperatures from 1100 up to 1600°C (Hirai et al., 1981). The obtained amorphous deposits were mixtures of amorphous a-Si₃N₄, SiC and pyrolytic C (up to 10 wt. %). The deposits surface had a pebble-like structure.

The SiC_xN_y coatings were obtained by CVD at 1000–1200 °C using TMS-NH₃-H₂ (Beneddouché et al., 1997). It was found that SiC_xN_y films are not simply a mixture of the phases SiC and Si₃N₄, and have a more complex relationship between the three elements, corresponding to the existence of Si(C_{4-n}N_n) units.

Cubic crystalline Si_{1-x-y}C_xN_y films have been grown using various carbon sources by rapid-thermal CVD (Ting et al., 2002). The heat source was an ultraviolet halogen lamp with high-energy density. A mixture of carbon source, NH₃, and SiH₄ diluted in hydrogen was used as the source gas and introduced to the furnace. The different carbon sources are SiH₃CH₃, C₂H₄, and C₃H₈. The substrate's temperature was raised quickly from room temperature to 1000°C with a temperature raising rate in the range of 300–700°C/min. The Si_{1-x-y}C_xN_y films grown with C₃H₈ gas possesses the most desirable characteristics for electronic devices and other applications.

a-SiCN:H films were successfully obtained through an in-house developed vapor-transport CVD technique in a N₂ atmosphere (Awad et al, 2009). Polydimethylsilane (PDMS) was used as a precursor for both silicon and carbon, while NH₃ was mixed with argon to ensure the in-situ nitrogenation of the films. The increase of the N fraction in the a-SiCN:H films resulted in an increase of the average surface roughness from 4 to 12 nm. The a-SiCN:H films were found to be sensitive to their N content.

2.2.1.2 Hot-wire CVD method (HWCVD)

$\text{Si}_x\text{N}_y\text{C}_z\text{:H}$ films were produced by HWCVD, plasma assisted HWCVD (PA-HWCVD) and plasma enhanced (PECVD) using a gas mixture of SiH_4 , C_2H_4 and NH_3 without hydrogen dilution (Ferreira et al., 2006). For the HWCVD process the filament temperature was kept at 1900°C while for the PECVD component an RF power of 130W was applied. HWCVD films have higher carbon incorporation. PA-HWCVD films are N rich. PECVD films contain C and N bonded preferentially in the hydroxyl groups and the main achieved bonds are those related to C-H, C-N and Si- CH_x -Si.

a-SiCN:H thin films were deposited by HWCVD using SiH_4 , CH_4 , NH_3 and H_2 as precursors (Swain et al., 2008). Increasing the H_2 flow rate in the precursor gas more carbon is introduced into the a-SiCN:H network resulting in a decrease of the silicon content in the films from 41 at.% to 28.8 at.% and sp^2 carbon cluster increases when the H_2 flow rate is increased from 0 to 20 sccm.

2.2.1.3 Plasma Enhanced CVD (PECVD)

SiOCH and SiNCH films were deposited using TMS, mixed with O_2 or N_2 . (Latrasse et al, 2009). Plasmas of O_2/TMS and N_2/TMS gas mixtures can be sustained between 5 and 25 Pa.

SiCN cone arrays were synthesized on Si wafers using a microwave plasma CVD reactor with gas mixtures of CH_4 , SiH_4 , Ar, H_2 and N_2 as precursors (Cheng et al., 2006). The typical process temperature was 900°C . The SiCN cones have nanometer-sized tips and their roots vary from nanometers to micrometers. Field emission characteristic of SiCN cone arrays shows a low turn-on field with relatively high current density.

The amorphous SiCN films were grown on the Si(100) and fused silica substrates by microwave CVD using a mixture of SiH_4 , NH_3 , CH_4 and H_2 gases in various proportions (Chen et al., 2005). The stronger affinity of silicon to bond with nitrogen than to bond with carbon results in the complete absence of Si-C bonds in a-SiCN thin films.

SiCN coatings deposited on a Si substrate are produced by PECVD using methyltrichlorosilane (MTCS), N_2 , and H_2 as starting materials (Ivashchenko et al, 2007). The coatings are nanostructured and represent $\beta\text{-C}_3\text{N}_4$ crystallites embedded into the amorphous a-SiCN matrix with a hardness of 25 GPa and an Young's modulus of above 200 GPa). SiCN thin films deposited by PACVD using TMS and NH_3 have been investigated in order to determine their corrosion protective ability (Loir et al, 2007).

SiCN films were synthesized on Si wafer by microwave plasma CVD (MWCVD) with CH_4 (99.9%), high-purity N_2 (99.999%) as precursors, and additional Si column as sources (Cheng et al, 2004). When no hydrogen was introduced, the well-faceted crystals can be achieved at modest N_2 flow rate. A higher temperature results in second nucleation on previous crystals, larger crystalline size, and perfect crystalline facet.

Large and well faceted hexagonal crystallites in SiCN films can grow on Si and Ti substrates under higher nitrogen gas flow in the gaseous mixture of CH_4 and H_2 in the normal process of diamond deposition using a microwave plasma chemical vapor deposition (MP-CVD) (Fu et al., 2001).

2.2.2 Boron carbonitrides

The processes of CVD, considered in the present review, can be divided into three groups: 1) use of boron trichloride, 2) use of boron hydride, and 3) use of complex boron-nitrogen

compounds, as initial substances for obtaining boron carbonitride films. The first attempt of CVD production of boron carbonitride was reported by Badyan and co-authors (Badyan et al., 1972a) in which they used the CVD process with BCl_3 , CCl_4 , N_2 , and H_2 as starting materials:



At the synthesis temperature 2223K, they obtained solid solution with the $(\text{BN})_x\text{C}_{1-2x}$ composition, which was confirmed by X-ray diffraction (XRD) data. The authors assumed that the obtained material is a solution with substitution at the atomic level, as a result of substitution of a pair of carbon atoms in the hexagonal graphite lattice by nitrogen and boron atoms. Experimentally determined density of the material was $2.26 \pm 0.02 \text{ g/cm}^3$, which is close to the density of graphite (2.26 g/cm^3) and h-BN (2.27 g/cm^3). At a temperature above 2273 K, the obtained compound decomposed yielding boron carbide B_4C , graphite and nitrogen. Unfortunately, these works contain only a few data on the chemical and phase composition of the obtained compounds.

The BCN material was more thoroughly characterized for the first time by Kaner et al. (Kaner et al., 1987). In this paper, boron carbonitride with graphite-like structure was synthesized in the heated gas mixture:



In order to prevent the formation of h-BN, the authors recommend at first to mix BCl_3 and C_2H_2 (they do not react at low temperature), and then add ammonia into the hot region of the reactor. Chemical composition of the products obtained at 673 and 973 K was $\text{B}_{0.485}\text{C}_{0.03}\text{N}_{0.485}$ and $\text{B}_{0.35}\text{C}_{0.30}\text{N}_{0.35}$, respectively. The X-ray photoelectron analysis demonstrated that this material is not a simple mixture of boron nitride and graphite. The B1s and N1s spectra indicate that boron is bound both to carbon and to nitrogen atoms, while nitrogen atoms are bound both to carbon and to boron. These compounds exhibited semiconductor properties at room temperature. Transmission electron microscopy (TEM) showed that the film is a uniform material with grain size of about 10 nm.

Further investigations of the synthesis of boron carbonitride, involving the initial mixture of boron trichloride and methyl cyanide






at temperature above 1173 K resulted in obtaining the stoichiometric compound BC_2N with lattice parameters $a=2.5\text{\AA}$ and $c=3.4\text{\AA}$ (Kouvetakis et al., 1989).

The synthesis of boron carbonitride by CVD from the gaseous mixture of boron trichloride, ammonia and acetylene at 973-1323 K resulted in obtaining BCN solid solution (Saugnas et al., 1992). Both amorphous and polycrystalline films were obtained; their composition was $\text{C}_5\text{B}_2\text{N}$. The material was stable to heating up to 1973K.

Nevertheless, by the 90-ies the chemical and phase composition, and properties of the compounds of this ternary system remained poorly investigated.

The h-BN films containing small amount of carbon and hydrogen as impurities were synthesized by means of CVD. The formula ascribed to this compound was $\text{BN}(\text{C,H})$. The synthesis of the films was performed using different initial gas mixtures within different temperature ranges:



In all these cases, BCl_3 and hydrocarbons (C_2H_2 , C_2H_4 or CH_4) were mixed beforehand to avoid the formation of boron nitride; ammonia was admitted directly into the reaction region near the substrate. The X-ray diffraction patterns of the BN(C,H) film synthesized according to reaction (6) were recorded by means of powder diffraction (Kawaguchi et al., 1991); the patterns contain a very broad (001) reflex and several reflexes the positions of which are close to the positions of peaks in t-BN. Additionally, the films synthesized according to reactions (7) and (8) exhibited diffraction patterns with only one diffraction reflex (001), the position of which is close to the positions of reflexes in h-BN, t-BN or graphite. The (100) and (101) reflexes are very weak and broadened. This result indicates that the BN(C,H) films obtained by means of CVD at high temperature possess the structure similar to that of t-BN. A similar ternary compound $\text{BC}_{0.43}\text{N}_{0.29}$ with turbostratic structure was synthesized on graphite at $T=1650\text{K}$ from a mixture of boron trichloride, methane, ammonia, and hydrogen at reduced pressure (Bessmann et al., 1990).

Amorphous boron-carbon-nitrogen (a-BCN) films have been fabricated by hot-wire CVD using BCl_3 , C_2H_2 and N_2 or NH_3 (Yokomichi et al., 2004).

The N concentration of the films synthesized by using a N_2 was below several at.%, and Cl atoms were incorporated to 3-5 at.%. The N concentration increased and the Cl concentration decreased by using NH_3 gas. In the case of NH_3 gas, the N concentration was nearly equal to the B concentration in most cases. The nearly identical concentrations in N and B resulted from high chemical reactivity between the BCl_3 and NH_3 gases, and the decrease in Cl concentration resulted from the removal as HCl due to NH_3 gas. These results indicate that the combination of BCl_3 and NH_3 is suitable for fabrication of a-BCN films by the CVD method.

BCN films were deposited by PECVD from a mixture of $\text{BCl}_3+\text{C}_2\text{H}_4+\text{N}_2+\text{H}_2+\text{Ar}$ in an industrial-scale DC plasma CVD plant (Kurapov et al., 2003, 2005). It was shown that the power density at the substrate has a large effect on the structure evolution of the BCN thin films. The authors suggest that with increasing power density the structure of the deposited films changed from an orientation where the c-axis is parallel to the substrate surface to a more randomly oriented structure.

During the last 10 years a group from Osaka University, Japan, studies intensively the PECVD synthesis from $\text{BCl}_3+\text{CH}_4+\text{N}_2+\text{H}_2$ mixtures and the properties of BC_xN_y films. The BC_xN_y films produced at 650°C were polycrystalline (Aoki et al., 2007, 2008a, 2008b, 2009a, 2009b, 2009c, 2009d; Etou, et al., 2002; Kimura, et al., 2005, 2009; Mazumder et al., 2009; Nesládek et al., 2001; Okada et al., 2006; Shimada et al., 2006; Sugino & Hieda, 2000; Sugino et al., 2000, 2001, 2002, 2008, 2010; Sugiyama et al., 2003, 2002; Tai et al., 2003; Umeda et al., 2004; Watanabe et al., 2008; Yuki et al., 2004; Zhang et al., 2005).

Amorphous BCN:H films were first prepared by Montasser et al. in 1984 by means of RF and microwave plasma-stimulated CVD using the initial gas mixture composed of diborane, ethane (or methane) and nitrogen (or argon) (Montasser et al., 1984, 1985, 1990). The synthesis of transparent stable films of hydrogenated boron carbonitride $B_xC_yN_z:H$ is described on substrates made of NaCl, Si and glass (at room temperature). Film deposition rate was 2-12 nm/min, refractive index 1.3-1.6. Correlation between micro-hardness and chemical composition of the film was established; in turn, it depends on synthesis conditions: total pressure in the reactor, concentration ratio of the initial compounds $B_2H_6:CH_4$ (or C_2H_6), and plasma discharge power. The $B_xC_yN_z:H$ films exhibited very complicated IR spectra; the authors have specially stressed that it is impossible to make conclusions concerning types of chemical bonds in the material basing only on the IR spectroscopic data.

Amorphous $BC_xN_y:H$ films were prepared in a capacitively coupled RF-PECVD reactor at deposition temperatures $<200^\circ\text{C}$ starting from $B_2H_6+CH_4+N_2+H_2$ gas mixture (Dekempeneer et al., 1996, 1997). Films were deposited on Si, steel and glass substrates. By varying the partial pressure of the gases, the composition was varied in a wide area of the B-N-C triangle. The same initial gas mixture was used by Polo et al. (Polo et al., 1998, 1999). It was found that the films had a less ordered structure.

Both amorphous and polycrystalline coatings were deposited by microwave low pressure CVD (LPCVD) using a mixture of $B_2H_6+CH_4+NH_3+H_2$ at substrate temperature in the range $800-1350^\circ\text{C}$. (Stanishevsky, 2010). Amorphous coatings were usually formed at lower substrate temperatures and were non-homogeneous across the coating thickness. Polycrystalline coatings were generally represented by both diamond and boron nitride phases. In one case, a polycrystalline coating with the composition of B_2CN_4 was fabricated. The turbostratic structure of BC_xN_y with various compositions was synthesized by bias-assisted hot-filament CVD (HFCVD) (Yu et al., 1999a, 1999b; Wang, 1999) within the temperature range 873-1273 K from $B_2H_6+CH_4+N_2+H_2$ mixture. Investigation of the films by means of XPS demonstrated that the three atoms B, C, N are chemically bound. Boron carbonitride is the main phase in all the deposited samples, though in some cases (at high temperature) this phase was co-deposited with boron carbide. The growth rate of BCN films decreased substantially with increased temperature. Chemical composition and morphology of the layers were also dependent on deposition temperature. The turbostratic BC_xN_y films were also grown by HFCVD from mixture of $B_2H_6+CH_4+NH_3+H_2$ (Xie et al., 1998).

Laser-assisted CVD was used for preparation of single-phase BC_xN_y layers at low temperature in a gas atmosphere containing $B_2H_6+CH_4+NH_3$, where the starting composition ratio could be varied in a large range. Layers exhibited turbostratic structure. Some planar structure, containing especially CB_2N groups, were suggested for the "unit cell" of CBN solid solutions (Morjan et al., 1999).

BCN films were deposited from mixture $B_2H_6+CH_4+N_2+H_2$ with electron beam excited plasma-chemical vapor deposition (EBEP-CVD) (Hasegawa et al., 2002, 2003). By controlling the flow rate ratios of the process gases, films with composition expressed as B_xC_yN , where $x=0.9-4.7$ and $y=0.5-6.0$ were obtained.

3. Syntheses of layers by single-source precursors

3.1 Silicon carbonitrides

The review highlights of the synthesis, processing and properties of non-oxide silicon-based bulk ceramics materials derived from silazanes and polysilazanes (Kroke et al., 2000).

At the present time, the alternative way of synthesis of silicon carbonitride films is through the use of low-toxicity siliconorganic compounds of various compositions and structures used as single source-precursors containing all the necessary elements Si, C, and N in one molecule. These compounds are of special interest because the molecular structure of the initial organosilicon compound affects the chemical and phase compositions plus the microstructure of deposited silicon carbonitride films.

3.1.1 Hexamethyldisilazane (HMDSN)

SiCN films were deposited by HWCVD method using HMDSN which is an organic liquid material (Izumi et al, 2006; Limmanee et al, 2008). It is found that the composition ratio of SiCN can be controlled by changing the flow rate of NH_3 . SiCN films can be deposited at the substrate temperature of 100°C . The dielectric constant can be controlled from 2.9 to 7 by changing the flow rate of NH_3 . The best efficiency of 13.75% for polycrystalline silicon solar cells using a-SiCN:H films was achieved at the temperature of 750°C .

SiCN films were obtained at a substrate temperature of 250°C by HWCVD using HMDSN (Nakayamada et.al, 2008). No SiCN film thickness was changed at all for 1 week in 10wt.% H_2SO_4 . A high corrosion resistance was confirmed.

SiCN nanopowders with different chemical compositions and characteristics can be prepared by CO_2 laser pyrolysis of organosilicon precursors (HMDSN or TMDSN, see section 3.1.9) or their mixture with silane (Dez et.al, 2002). A correlation is established between the synthesis conditions of powders and their chemical composition, morphology, structure and thermal stability.

a-SiCN thin films were deposited at $250\text{-}500^\circ\text{C}$ using a microwave plasma assisted CVD process fed with a mixture of CH_4 , N_2 , Ar and hexamethyldisilazane (Bulou et al., 2010). The increase of the CH_4 rate results in less organic, films of higher density and in an increase of the refractive index. The CH_4 addition to the gaseous mixture leads to a value of the Si/N ratio of films very close to stoichiometric Si_3N_4 .

Si:C:N:H thin films were deposited by PECVD using HMDSN as monomer and Ar as carrier gas (Vassallo et al., 2006). The films become more amorphous and inorganic at increasing RF plasma power. The wettability of the film has been studied and related to the chemical composition and to the morphology of the deposited layers.

SiC_xN_y films were synthesized with the composition varying in a wide range from those similar to silicon carbide to those similar to silicon nitride. HMDS was used by PECVD as single-source precursor in the mixtures with helium, nitrogen or ammonia in the wide range of temperatures from 100 up to 800°C and RF plasma powers from 15 up to 70 W (Fainer et.al., 1999, 2000, 2001a, 2001b, 2003, 2004, 2008).

3.1.2 Ethylsilazane

Thin films of amorphous Si-C-N were grown on Si(100) substrates by the pyrolysis of ethylsilazane in mixtures with H_2 in the temperature range of 873-1073K. (Bae et al., 1992). It was shown that the refraction index of these films varied from 1.81 to 2.09, elastic recoil detection decreased from 21 to 8% in the range of temperatures from 873K to 1073K. The chemical composition of the films was determined to be $\text{Si}_{43}\text{C}_7\text{N}_{48}\text{O}_2$.

3.1.3 Polysilazane

Non-stoichiometric X-ray-amorphous $\text{Si}_{3+x}\text{N}_4\text{C}_{x+y}$ was deposited during pyrolysis of polysilazane at 1440°C . (Schonfelder, 1993). The heating up to 1650°C results in formation of a mixture of the nanocomposites $\text{Si}_3\text{N}_4/\text{SiC}$ or $\text{Si}_3\text{N}_4/\text{SiC}/\text{C}$.

3.1.4 Bis(dimethylamino)dimethylsilane (BDMADMS)

SiCN thin films for membrane application were deposited by PECVD from bis(dimethylamino)dimethylsilane (BDMADMS) (Kafrouni et al., 2010). Single gas permeation tests have been carried out and a helium permeability of about 10^{-7} mol m⁻² s⁻¹ Pa⁻¹ was obtained with an ideal selectivity of helium/nitrogen of about 20. Moreover these PECVD membranes also seem to be stable at higher temperature in air (up to 500°C).

a-Si:C:N:H films were produced by RPCVD from dimethylaminodimethylsilane (Blaszczyk-Lezak et al., 2005, 2006). The films deposited at different substrate temperatures (30–400°C). Strong adhesion to a substrate, high hardness (H=28–35GPa), low friction coefficient ($\mu=0.04$, against stainless steel), and strong resistance to wear (predicted from high “plasticity index” values $H/E^{\circ}=0.10-0.12$) were found for these films suggest that these materials are promising coatings for improving tribological properties of engineering materials for advanced technology.

Siliconnitride-like films were deposited at low temperatures using RF inductively coupled plasma fed with bis(dimethylamino)-dimethylsilane (BDMADMS) and argon (Ar) (Mundo et al., 2005). The results indicate that at high power input and low monomer-to-Ar ratio, low carbon and high nitrogen content films can be obtained, stable and with a refractive index of 1.87.

3.1.5 Bis(dimethylamino)methylsilane (BDMAMS)

The RPCVD with bis(dimethylamino)methylsilane precursor was used for the synthesis of Si:C:N films (Blaszczyk-Lezak et al., 2007). The increase of T_S enhances crosslinking in the film via the formation of nitridic Si-N and carbidic Si-C bonds. On the basis of the structural data a hypothetical crosslinking reaction has been proposed, contributing to silicon carbonitride network formation.

3.1.6 Tris(dimethylamino)silane (TrDMAS)

Amorphous SiCN films were fabricated by RPCVD using H₂ and TrDMAS, (Me₂N)₃SiH, as a novel single-source precursor, being a carrier of Si-N and C-N units (Wrobel et al., 2010). The Arrhenius plot of the temperature dependence of the film density implies that for $T_S > 200^{\circ}\text{C}$ a thermally enhanced crosslinking process predominates, and the density reaches a high value of $\rho \approx 3.0$ g cm⁻³ at $T_S = 350^{\circ}\text{C}$. SiCN films are morphologically homogeneous materials exhibiting very low surface roughness $R_{rms} = 0.3$ nm. The photoluminescence of SiCN films is sensitive to the contribution of the Si-CH₂-N links.

3.1.7 Bis(trimethylsilyl)carbodiimide (BTSC)

Amorphous SiCN coatings were prepared on steel substrates by RF-PECVD from BTSC (Zhou et al., 2006; Probst et al., 2005; Stelzner et al., 2005). The results of the studies show that the coatings obtained on the RF-powered electrode (cathode) were black, thick (>20 μm) and hard (21–29GPa), while those grown on the grounded electrode (anode) were yellow, thin (<4 μm) and soft (~5GPa). The surfaces of all coatings were very smooth with a maximum rms roughness between 2 nm and 5 nm for an area of $5\mu\text{m} \times 5\mu\text{m}$. Wear tests at 600°C showed that the coatings possess an excellent high-temperature stability.

3.1.8 Dimethyl(2,2-dimethylhydrazino)silane (DMDMHS) and dimethyl-bis-dimethylhydrazino silane (DM-bis-DMHSN)

SiCN films were synthesised by RPECVD using a novel single-source precursors dimethyl(2,2-dimethylhydrazino) silane $(\text{CH}_3)_2\text{HSiNH}(\text{CH}_3)_2$, (DMDMHS) and dimethyl-bis-dimethylhydrazino silane $(\text{CH}_3)_2\text{Si}[\text{NHN}(\text{CH}_3)_2]_2$ (DM-bis-DMHSN), which are silyl derivatives of 1,1-dimethylhydrazine (Smirnova et al., 2003). The films were found to be predominantly amorphous with a number of crystallites embedded in an unstructured matrix. The crystalline phase can be indexed as a tetragonal cell with lattice parameters $a=9.6 \text{ \AA}$ and $c=6.4 \text{ \AA}$. This novel material has an optical band gap varying within the energy range from 2.0 to 4.7 eV.

3.1.9 Tetramethyldisilazane (TMDSN)

Si:C:N films were produced by RPCVD from mixture of a 1,1,3,3-tetramethyldisilazane precursor with H_2 (Blaszczyk-Lezak et al., 2006a, 2006b; Wrobel et al., 2007). An increase in T_S leads to the elimination of the organic groups and subsequent crosslinking via the formation of Si-C and Si-N networks. In view of the relatively high hardness (16 GPa) and a low friction coefficient μ value (0.02-0.05 against stainless steel) found for the a-Si:C:N film deposited at $T_S=400^\circ\text{C}$, this material may be useful as a tribological coating for metals.

3.1.10 Hexamethylcyclotrisilazane (HMCTS)

Silicon nitride films were obtained in glow-discharge plasma from HMCTS in a mixture with nitrogen gas or ammonia at low temperatures (below 150°C) (Voronkov et al., 1981). Chemical composition was analyzed with IR-spectroscopy and demonstrated that in the films obtained at such conditions are present Si-N, C-C, Si-H (or Si-C \equiv N) and N-H bonds.

The silicon nitride films synthesized from HMCTS with a set of additional gases such as NH_3 , H_2 , and N_2 by PECVD at temperatures ($150\text{--}400^\circ\text{C}$) and plasma power of 5-50 W (Brooks & Hess, 1987, 1988). The films obtained from a gas mixture (HMCTS + NH_3) and characterized by lesser than 4 at.% carbon and hydrogen content of about 25 at.% are close to the chemical composition of silicon nitride films. The Si-N bonds are dominant. The films obtained from the mixture (HMCTS + H_2), contain significant amount of carbon (30-40 at.%) and 21 at.% of hydrogen. These films contain both Si-N and Si-C bonds.

SiCN films were obtained by RPECVD using HMCTS in a mixture with helium or nitrogen in the range of temperatures of $100\text{--}750^\circ\text{C}$ and plasma powers of 15-50W (Fainer et al, 2009a, 2009b). The low temperature $\text{Si}_x\text{N}_y\text{O}_z\text{:H}$ films are compounds with chemical bonds among the main elements Si, N, and C together with impurity elements such as hydrogen and oxygen. The empirical formula of the high-temperature films is represented by Si_xN_y . The absence of hydrogen in these films leads to good thermal stability and microhardness. These films exhibit an excellent transparency with a transmittance of $\sim 92\text{--}95\%$ in the spectral range $\lambda=380\text{--}2500 \text{ nm}$.

3.1.11 N-bromhexamethyldisilazane

SiCN films were produced from the new volatile organosilicon compound N-bromhexamethyldisilazane (Smirnova et al, 2008). An increase in the refractive index from 1.5 to 2.2 and a decrease in the optical band gap width from 4.5 to 2.1 eV is observed as the chemical composition of the films changes in the temperature interval of $470\text{--}870\text{K}$.

3.2 Boron carbonitrides

During the recent years, special attention was paid to the introduction of volatile compounds – single-source precursors - containing all the necessary atoms (boron, carbon, and nitrogen) for the synthesis of boron carbonitrides. The use of complex organoelemental volatile compounds should be considered as an essential step forward. Since these compounds are incombustible and rather stable toward reactions in the natural atmosphere, their application in technology is preferable over chemically active boron trichloride and diborane. These substances have a well-defined ratio of B:C:N due to their stoichiometry, and they can be evaporated and easily handled due to their chemical and physical properties. With these compounds, one can obtain layers of different composition using different gaseous additives (ammonia, nitrogen, hydrogen).

In CVD processes, molecular precursors such as dimethylamine borane $(\text{CH}_3)_2\text{HN}\cdot\text{BH}_3$ (DMAB), trimethylamine borane $(\text{CH}_3)_3\text{N}\cdot\text{BH}_3$ (TMAB), triethylamine borane $(\text{C}_2\text{H}_5)_3\text{N}\cdot\text{BH}_3$ (TEAB), N,N',N'' -trimethylborazine $(\text{CH}_3)_3\text{N}_3\text{B}_3\text{H}_3$, N,N',N'' -triethylborazine $(\text{C}_2\text{H}_5)_3\text{N}_3\text{B}_3\text{H}_3$, tris-(dimethylamino)borane $\text{B}(\text{N}(\text{CH}_3)_2)_3$, (N-pyrrolidino)diethylborane $\text{C}_8\text{H}_{18}\text{BN}$, pyridine borane $\text{C}_5\text{H}_5\text{NBH}_3$, and triazaborabicyclohexane $\text{BN}_3\text{H}_2(\text{CH}_2)_6$ have been used as boron, carbon, and nitrogen sources.

3.2.1 Trimethylamine borane (TMAB)

Kosinova et al. pioneered the use of trimethylamine borane complex $(\text{CH}_3)_3\text{N}\cdot\text{BH}_3$ in both RF PECVD (40.68 MHz) and LPCVD processes for BCN film deposition (Kosinova et al., 2001, 2003a, 2003b; Fainer et al., 2001). Boron carbonitride films were grown by PECVD using TMAB and its mixtures with ammonia, hydrogen, or helium. The effects of the starting-mixture composition and substrate temperature on the chemical composition of the deposits were studied. The results indicate that the initial composition of the gas mixture, the nature of the activation gas, and substrate temperature play a key role in determining the deposition kinetics and the physicochemical properties of the deposits. Depending on these process parameters, one can obtain h-BN, h-BN + B_4C , or h- BC_xN_y films.

h-BCN films with a thickness of $\approx 4 \mu\text{m}$ were synthesized on Si(100) substrate by RF (13.56 MHz, 1kW) and microwave (2.45 GHz) PECVD using mixture of TMAB and H_2 as precursors (Mannan et al., 2007). The temperature of deposition was 300 and 600°C for RF PECVD, and 840-850°C for MF PECVD processes. The films were amorphous with an inhomogeneous microstructure confirmed by XRD and FEG-SEM. XPS and FTIR suggested that the films were consisted of a variety of bonds between B, C and N atoms such as B-N, B-C and C-N. Oxygen was inevitably incorporated as a contaminant (13-15 at.%). The effects of the deposition conditions, including microwave power and carrier gas, on the film properties was studied by Kida (Kida, 2009). The deposition time varied between 0.5 h and 2 h with microwave powers of 200, 300, and 400W (2.45 GHz). Substrate temperatures depended on the microwave power applied and ranged between 700 and 900°C. N_2 and a gas mixture of CH_4 (10vol.%) and H_2 (90vol.%) were used as carrier gases. The films deposited were found to have fibrous nanostructures consisting of nanosized fibers. For the films deposited under N_2 flow, boron and nitrogen contents of the films increased as the microwave power increased, leading to the formation of B-N and C-N bonds, as confirmed by FTIR. Moreover, deposition at higher microwave power reduced the oxygen content in the films. However, for films deposited under CH_4+H_2 flow, B-O bond formation dominated ($\text{B}_{30}\text{C}_{15}\text{N}_4\text{O}_{51}$), owing to the high reactivity of boron with oxygen in the absence of N_2 .

3.2.2 Dimethylamine borane (DMAB)

Boron nitride films were obtained by means of PECVD of DMAB+(CH₃)₂NH·BH₃ - in mixture with ammonia (Schmolla et al., 1983; Bath et al., 1989, 1991, 1994) or nitrogen (Baehr et al., 1997; Boudiombou et al., 1997; Abdellaoui et al., 1997).

Amorphous and poor crystalline phases in the B-C-N system were obtained by plasma chemical decomposition of DMAB in mixture with hydrogen and argon (Loeffler et al., 1997).

3.2.3 Triethylamine-borane (TEAB)

In the study of Levy et al., films consisting of B-N-C-H have been synthesized by LPCVD using the liquid precursor TEAB = (C₂H₅)₃N·BH₃ complex both with and without ammonia (Levy et al., 1995). In the absence of NH₃, the growth rate dependency on temperature follows an Arrhenius behaviour with an apparent activation energy of 11 kcal/mole. The addition of NH₃ has the effect of lowering the deposition temperature to 300°C and doubling the apparent activation energy. The deposits were found to be in all cases amorphous. A significant increase in carbon concentration was observed above 650°C due to the break up of the amine molecule. The addition of NH₃ was used to reduce the carbon content in the films. The same result of the ammonia effect was also obtained by Kosinova et al. (Kosinova et al., 1999, 2001). The BCN films were deposited on Si(100), GaAs(100) and fused silica substrates using TEAB with and without ammonia by both LPCVD and RF-PECVD (40.68 MHz) methods.

With TEAB in the direct current glow discharge plasma process (GD-PECVD) the highest carbon concentrations (48–73 at.%) in BCN films are obtained without using an additional carbon source (Thamm et al., 2005). Elastic recoil detection analysis (ERDA) measurements yield information on the layer composition regarding the concentrations of the elements boron, carbon, nitrogen, and hydrogen. The hydrogen content in the produced BCN layers strongly depends on the substrate temperature and increases up to 35 at.%. Depth profiles show a homogeneous distribution of the elements B, C, N, and H over the entire layer thickness.

The paper of Mannan et al. presents the chemical bonding states and the local structures of oriented hexagonal BCN films with the grain size of around 100 nm synthesized by microwave PECVD (MW-PECVD) using mixture TEAB and CH₄+H₂ as the carrier gas (Mannan et al., 2008). The deposition was performed at different microwave power settings of 200–500W at working pressure of 5.0 Torr. The substrate temperature was measured to be 750 and 850°C, respectively. It was estimated a particle size of around 100-150 nm. The crystallinity was not good as the hexagonal structures appeared in a short-range order which could not be detected by XRD.

3.2.4 Tris-(dimethylamino)borane (TDMAB)

Homogeneous carbon boronitride coatings were produced with cold-wall CVD varying the temperature of the deposition substrate from 800°C up to 1400°C using tris-(dimethylamino) borane B[N(CH₃)₂]₃ as a single-source molecular precursor. The deposition temperature has an influence on the growth rate as well as on the coating composition (C: 35–75at%; B: 12–40at%; N: 7–24at%). Below 700°C substrate temperature no deposition can be observed. At temperatures between 700°C and 800°C the layers grow very slowly and they are oriented parallel to the substrate's surface. If temperatures are raised to 900°C the layer already seems to be under stress as it cracks into small pieces during cooling to room temperature. Higher

substrate temperatures lead to the formation of hemispheres (approximately 10 μm in diameter) on the surface, thus increasing the roughness of the BCN layers (Gammer et al., 2002).

BCN-layers were deposited in a hot-filament supported reactor using TDMAB (Weissenbacher et al., 2002, 2006). These experiments were strongly influenced by the stability of the Ta-filament. At filament temperatures of 1500°C layer deposition on the surface of the filament takes place, at temperatures higher than 2000°C liquid phase formation led to filament breakdown in many cases. The morphology of the deposited BCN layers on hard metal substrates (WC-Co) depends on the deposition conditions and films contain high amounts of tantalum (BCN-Ta layers).

Methyl-BCN films were deposited by plasma-assisted CVD (PACVD) using mixture of TDMAB and N_2 at 350°C (Aoki et al., 2010a, 2010b).

Hexagonal boron carbonitride hybrid films - sp^2 -BCN phase with h-BN-like configuration - have been synthesized on Si(100) and on highly oriented pyrolytic graphite, respectively, by RF-PACVD using TDMAB (Mannan et al., 2009a, 2009b, 2010). The deposition was performed at different RF powers of 400–800W, at the working pressure of 2×10^{-1} Torr and temperature 650–750°C.

The influence of the B/C/N containing single-source precursors pyridine-borane (PB) and triazaborabicyclodecane (TBBD) on the chemical composition of boron carbonitride thin films was investigated in (Hegemann et al., 1997, 1999). The films are deposited via a PACVD process, activated by 13.56 MHz radio frequency (RF). N_2 , Ar and He serve as carrier gases. It becomes evident, that from a certain bias voltage, the self-bias in capacitively RF electrical discharges mainly influences the chemical composition of the BCN films independent of the kind of the used precursor. Films that were either deposited in He using a low power density or in N_2 using a high power density showed comparable properties. Analysis of these films showed their chemical composition to be BC_4N .

3.2.5 (N-pyrrolidino)-diethylborate (PEB)

BCN films were deposited on polycarbonate and silicon wafer by means of different RF PACVD (inductively coupled and capacitively coupled RF PACVD), by use of liquid organic compound (N-pyrrolidino)diethylborane ($\text{C}_8\text{H}_{18}\text{BN}$) as precursors. Deposition was carried out on at 95–120°C. A mixture of argon, hydrogen, and nitrogen was used as process gas. The layer shows a columnar structure. The composition of BCN films deposited ranged between $\text{BC}_{7.3}\text{N}_{0.8}$ and $\text{BC}_{0.9}\text{N}_{0.6}$ (Wöhle et al., 1999; Ahn et al., 2003).

3.2.6 Borazine derivatives

Amorphous semiconductor BCN films were produced by means of pyrolysis of borazine derivatives (tris(1,3,2-benzodiazaborolo)borazine) at 1073 K (Maya, 1988a, 1988b; Maya, & Harris, 1990). Quartz, titanium and silicon were used as substrates. Chemical analysis showed that the synthesized material had the composition $\text{BC}_{5.2}\text{N}_{1.8}\text{H}_{1.9}\text{O}_{0.45}$. The density of the coating was 2.05 – 2.09 g/cm^3 .

3.2.6.1 Trimethylborazine

Mixtures of N,N',N'' -trimethylborazine = $(\text{CH}_3)_3\text{N}_3\text{B}_3\text{H}_3$ (TMB) (the B:C:N ratio 1:1:1) and argon have been used to deposit BCN:H films by means of ECR PECVD processes at 100–150°C (Weber et al., 1992, 1993). Amorphous BCN layers were deposited on a polycarbonate substrate by RF PACVD at low temperature (95–120°C) using a mixture of TMB and H_2 , N_2 , or Ar (Wöhle et al., 1999). The composition of the layers varied in a wide range. The boron

content of the films ranged from 3at% to 42at%, the carbon content from 16at.% to 80at.%, and oxygen content from 2at.% to 10 at.%. BCN films with hexagonal turbostratic graphite like structure were deposited by both isothermal chemical vapour deposition (ITCVD) under atmospheric pressure and PECVD from gaseous mixtures of trimethylborazine, toluene and ammonia at 950°C (Stockel, 2002, 2003). Parallels between ITCVD and PECVD films emerged in the case of chemical composition and the correlation between carbon content and hardness values. Considerable differences exist with regard to the microstructure, especially the texture of the films. Moreover in ITCVD films the carbon is preferentially incorporated between the BN basal planes, whereas in PECVD films it is incorporated preferentially in between the BN basal planes as well. BCN coatings were deposited on polycarbonate by means of a capacitively or inductively coupled RF-PACVD (capacitive coupled plasma (CCP) vs. inductively coupled plasma (ICP)) using the elemental-organic compound trimethylborazine as precursor. The influence of the plasma parameters on the properties of films has been discussed (Ahn et al., 2003).

BCN:H films on silicon substrates were deposited with two different PECVD techniques (Thamm et al., 2005, 2007). A microwave plasma with RF-bias enhancement (MW-PECVD) and a direct current glow discharge plasma system (GD-PECVD) was used with TMB and benzene as an additional carbon source. Argon and nitrogen were used as plasma gases. Substrate temperature, substrate bias and gas composition were varied. The hydrogen content in the produced BCN layers strongly depends on the substrate temperature and increases up to 35at.%. Depth profiles show a homogeneous distribution of the elements B, C, N, and H over the entire layer thickness. Impurities such as oxygen or argon are detected in only small quantities (below 0.5at.%) and the concentration does not increase towards the surface. The hydrogen content mostly depends on the substrate temperature during the coating process. If the layers are deposited on 50°C substrate temperature (MW-PECVD) the hydrogen content increases up to 35at.%. If the temperature is increased up to 800°C, only 8at.% hydrogen are detected, independently of the plasma gas. The variation of the MW plasma power and RF-bias have no significant effects on the layer composition. Multicomponent films were grown by PECVD from N-trimethylborazine–nitrogen mixtures at temperatures from 373 to 973 K and varied RF power. According to XPS and IR spectroscopy results, the major component of the films is boron nitride. The films grown at temperatures below 673 K contain hydrogen. The higher temperature films contain carbon (Sulyaeva et al., 2007, 2009, 2010).

3.2.6.2 Triethylborazine (TEB) and Tripropylborazine (TPB)

Thermolysis of N-triethylborazine = $(C_2H_5)_3N_3B_3H_3$ (TEB) and N-triethylborazine = $(C_3H_7)_3N_3B_3H_3$ (TPB) at 500°C produces homogeneous, amorphous boron carbonitride phases, whose compositions are dependent upon the borazine substituent, and whose structures are similar to that of icosahedral boron carbide B_4C (Brydson et al., 2002). The deposition of BCN-layers by decomposing TEB was performed in a hot-filament CVD apparatus and for the gas activation a carburized Ta wire was used. Untreated, etched and diamond coated WC-Co hardmetal inserts were used as substrates. Substrate temperature was 890°C. The deposition parameters filament temperature (1800–2200°C), precursor flow rate and gas atmosphere were varied. The layer growth rates increased with the precursor flow rate and showed less influence of the substrate material. Layer morphology was of the pyrolytic type. When the layers became thick they tended to eliminate from the substrate. Due to the atomic hydrogen produced at the filament the deposition rate decreased in case

of hydrogen atmosphere compared to the experiments in argon atmosphere. This can be explained by etching reactions of the atomic hydrogen. Due to the etching reactions of the atomic hydrogen the IR-spectra also look different. Nevertheless, it was not possible to identify a cubic phase from the IR or XRD measurements (Weissenbacher et al., 2003).

4. Physical and chemical characterization

Mainly for judging the synthesis success, the products have to be characterized for physical and chemical properties. The analytical procedures are quite different, belonging to the interest of the scientists. One part is interested in the physical parameters, e.g., as mechanical (e.g., dimension, hardness, roughness), optical (e.g., reflectivity, absorption coefficient), thermal (e.g., conductivity), and electrical and electronic (e.g., resistivity, conductivity, band gap) properties. An other part examines the chemical properties, e.g., the elemental composition, the phase state (e.g., crystallinity, amorphous state), the character of chemical bonds (e.g., participation of the elements, single/double/triple, energy, distances, ionic/covalent/metal/van der Waals), and the chemical reactivity (e.g., inertness). Obviously, there is a relation between the physical and the chemical parameters.

The first citation of a carbonitride, to our knowledge, was given by a Soviet group (Dubovik & Struk, 1965). They referred to papers, published earlier (Samsonov et al., 1962; Chelepenkov et al., 1964). These scientists synthesized the product by nitriding of boron carbide and were interested in an excellent thermal resistance. The test of the material as crucibles at 1600-2000°C was successful, but a fundamental characterization was not performed. This situation changed a little later, when the elemental composition and structure of carbonitrides of different productions were determined (Kosolapova et al., 1971). Such information was derived from X-ray and electron diffraction measurements. Later on, nearly all papers dealing with the synthesis of silicon or boron carbonitrides contain a voluminous chapter with physical and/or chemical characterization of the products.

The description of the methods is partly taken from text books, lecture notes, application notes of manufacturers of analytical instruments, from the internet encyclopaedia Wikipedia, and from other not-authorized sources in the internet.

4.1 Ellipsometry

Ellipsometry is an optical method in material science and surface physics (Fujiwara, 2007; Tompkins, 2006). It permits to determine the real and the imaginary part of the complex dielectrical refractory index and of the thickness of thin layers, as well. It can be used for various materials, as organic and inorganic substances (metals, semiconductors, insulators). Ellipsometry is working in a wide range: UV, visible part, and far in the IR (THz range) light. By means of this method the change of the polarization state at reflection or transmission is determined. This change is given by the relation of the reflection coefficients vertical r_s and parallel r_p to the incidence plane of the polarized light. In nearly all cases a model analysis is carried out, in which the optical constants are described by a model dielectric function. In all former papers of the authors the absorption coefficient, refractory index, and the thickness of the silicon and boron carbonitride layers are determined by ellipsometry (Fainer et al., 1997; Kosinova et al., 1999; Hoffmann et al., 2007; Baake et al., 2010).

4.2 Indentation

The hardness of the synthesized products is determined by usual methods, described in text books. The so called Mohs` hardness (mainly for minerals) is divided in a graduation

scale of 10 parts. These parts are defined by the materials which scratch the surface of a sample. The indentation, and mainly the nano-indentation is a local (positional) high-resolution method for the characterization of thin solid samples. The method is based on the measurement of force and path during an elastic/plastic contact of a hard tester (indenter) with the sample. The advantages of this procedure are: Extremely high-resolution lateral and in the depth, no optical measurement at indentation is necessary, simultaneous determination of the hardness and of the Young's modulus, generation and measurement of defined scratches. In most cases, a diamond tip is pressed into the sample with increasing force. Then the force is decreased to zero. First, an elastic deformation is observed, followed by a plastic deformation at higher force. Only the elastic deformation is traced back during the unloading. Several methods are given to evaluate the data. In most cases, the contact stiffness is determined at the beginning of the unloading (Bauer-Marschallinger et al., 2007).

4.3 Scanning electron microscopy (SEM)

In this type of an electron microscope the sample is scanned by a high-energy beam of electrons. Utilizable information are mainly derived from signals of secondary electrons (SE), of back-scattered electrons (BSE), and of characteristic X-rays. The secondary electrons can produce very high-resolved images of the sample surface, showing details less than 5 nm in size. Because the intensity of the BSE signal is strongly related to the atomic number (Z) of the specimen, BSE images provide information about the lateral distribution of different elements. In case of relaxation of the excited atoms in the sample, characteristic X-rays are emitted. These are used to determine the elemental composition and to measure the abundance of the elements in the sample. The information depth is related to the primary electron energy (0.5 keV – 40 keV), to the mean atomic number and the density of the sample, and to the energy of the emitted X-rays (Moseley's law gives the relation between energy and atomic number). The electrons typically are thermoionically emitted from a tungsten (W) or a lanthanum hexaboride (LaB_6) cathode. For conventional imaging in SEM, the specimen must be electrically conductive. Nonconductive specimens, e.g. ceramics, tend to charge and, therefore, have to be coated by an ultrathin conducting layer (e.g., gold, carbon). Back scattered electron imaging, quantitative X-ray analysis, and X-ray mapping of materials (e.g., metals, ceramics, geological) require that the surfaces have to be ground and polished to an ultra smooth surface. Special high resolution coating techniques are used for high magnification imaging of inorganic thin films. As an example, SEM images of carbonitride layers are given in Fig. 1.

The most common imaging mode collects the low-energy (< 50 eV) secondary electrons (SE), which originate from a thin (few nanometers) surface layer of the sample. These electrons are biased to about + 2 kV and detected by scintillator-photomultiplier systems. The high-energetic back-scattered or reflected electrons are usually measured by detectors of the scintillation or semiconductor types. The X-rays are detected by wavelength-(WDXRS) or energy-dispersive (EDXRS) systems. Expanded systems contain several WDXRS detectors (arranged vertically and horizontally) and one EDXRS detector – so called electron micro probe analyzer (EMPA). More detailed information is given in the text books and in special papers. As introduction the monography of Goldstein et al. is suggested (Goldstein et al., 1981).




Fig. 1. Typical SEM images of surfaces of PECVD SiC_xN_y film (left) and BC_xN_y (right).

4.4 Atomic Force Microscopy (AFM)

The atomic force microscopy (AFM) or scanning force microscopy (SFM) provides a three-dimensional profile of the sample surface (in comparison to SEM, which works two-dimensional). It is of very high-resolution on the order of fractions of a nanometer. The AFM consists of a cantilever with a sharp tip (silicon or silicon nitride) to scan the sample surface. When the probe is brought to the proximity of the specimen mechanical contact force, van der Waals forces, capillary forces, chemical bonding, electrostatic and magnetic forces, Casimir forces, and/or solvation forces influence the deflection of the cantilever. The deflection is, typically, measured by a laser spot reflected from the top of the cantilever. In best cases, individual surface atoms can be identified. The advantages of AFM are in comparison to SEM: The receiving of a three-dimensional image, the sample viewing without any treatments (coatings), working perfectly in ambient air, giving true atomic resolution in ultra-high vacuum (and in liquid environment). The disadvantages are: Single scan image size in the micrometer range (height: 10-20 μm, scanning area: 150×150 μm²), and a limitation in the scanning speed (Giessibl, 2003; Sugimoto et al., 2007).

4.5 X-ray (XRD), electron, and neutron diffraction

The diffraction methods are used to determine the arrangement of atoms within a crystal. That directly means that the method is not suitable for amorphous materials. Beneath the structure and phases, a quantitative determination of the elemental composition can be derived. Therefore, X-ray diffraction was first used for the characterization of carbonitrides (Kosolapova et al., 1971). X-ray crystallography is called the chief method for characterizing the atomic structure of new materials.

A regular array of scatterers (crystal) produces a regular array of spherical waves. In most directions these waves cancel one another out through destructive interference, they add constructively in a few specific directions, determined by Bragg's law (8)

$$2d \cdot \sin \Theta = n \cdot \lambda, \quad (8)$$

where d = spacing between diffraction planes, Θ =incident angle, n =any integer, and λ =wavelength of the beam. That is successful because the wavelength λ is typically of the

same order of magnitude as the spacing d between planes of the crystal (1-100 Å). The initial studies revealed the typical radii of atoms, and confirmed many theoretical models of chemical bonding, such as the tetrahedral bonding of carbon in the diamond structure (Bragg & Bragg, 1913). In material sciences, many complicated systems (e.g., fullerenes) were analyzed using single-crystal methods. The Cambridge Structural Database contains over 500,000 structures; over 99 % of them were determined by X-ray diffraction. In laboratories X-ray diffraction devices contain X-ray tubes (X-ray generators) as sources. Electrons are thermally emitted from a metal and extracted through a strong electric potential (e.g., 50 kV) and directed to a metal plate (mostly Cu). Thereby, bremsstrahlung and some characteristic lines are emitted. Usually, the X-ray tube has a stationary anode (2 kW). For application of an intensive beam a rotating anode (14 kW) is used. The brightest and most useful X-ray source is a synchrotron. These systems allow a better resolution, and they make it convenient to tune the wavelength (energy) of the radiation. An XRD diffraction diagram recorded at a synchrotron beam is given in Fig. 2.




Fig. 2. The typical XRD-SR pattern of nanocomposite SiC_xN_y film shows that the peaks' position is close to standard $\alpha\text{-Si}_3\text{N}_4$ phase. There are some unknown peaks at small diffraction angles indicated by "?", which do not correspond to peaks positions of other known phases of the Si-C-N system.

The intensities of the reflections are recorded by photographic film, area detector or by a charge-coupled device (CCD) image sensor. To collect the total information, the crystal must be rotated step-by-step through 180° ($\Theta/2\Theta$ -geometry). As an additional method grazing incidence XRD is used.

Electrons interact with positively charged atomic nuclei and with the surrounding electrons, whereas X-rays interact with valence electrons only, and neutrons scatter by atomic nuclei. Whereas X-rays interact relatively weakly with the electrons, for some applications electron beams are used to examine relatively thin crystals (> 100 nm). The strong interaction of charged electrons with matter by Coulomb forces (about 1000 times stronger than for X-rays) allows determination of the atomic structure of extremely small volumes. The field of application of electron diffraction ranges from bio molecules over organic thin films to the

complex structures of (nanocrystalline) intermetallic compounds and zeolites. Electron diffraction is used in solid state physics and chemistry in devices as transmission electron microscopy (TEM, see 4.13) or scanning electron microscopy (SEM, see 4.3).

For structural determination of light elements neutron diffraction is the favoured method (Ibberson & David, 2002). For application of monochromatic, intense beams nuclear reactors and spallation neutron sources are used. Neutrons being uncharged scatter much more readily from the atomic nuclei than from the electrons. As mentioned, neutron scattering is very useful for observing the positions of light elements, especially hydrogen, which is essentially invisible in the X-ray diffraction. The samples are mostly exposed as powders and their sizes are relatively large.

4.6 X-ray Reflectometry (XRR)

X-ray reflectometry is a highly accurate method for the determination of layer thickness (Als-Nielsen, 2001). The reflectance of the sample is measured as a function of the grazing incidence angle of X-rays. Due to interference effects of the radiation from each layer, oscillations are observed in the reflectance curve. The oscillation period is mainly determined by the layer thickness, the oscillation amplitude depends on the densities and on the surface roughness. The reflectance curve can be fitted according to the Fresnel equations. XRR can provide information on the thickness, roughness and density of thin films on a substrate. Using synchrotron radiation layers can be distinguished with similar optical constants.

4.7 Nuclear Magnetic Resonance spectroscopy (NMR)

Nuclear magnetic resonance is one of the most important methods for the determination of the molecular structure of mostly organic and organometallic, rarely of inorganic compounds (Keeler 2005). All stable isotopes that contain an odd number of protons and/or neutrons have an intrinsic magnetic moment. The most commonly studied nuclei are ^1H , ^{13}C , ^{19}F , and ^{31}P . The liquid or solid sample is placed between very narrow positioned poles of a huge magnet. The magnet produces a field of extremely high stability and homogeneity. This field is varied by a so called sweep coil. In the measurements the applied magnetic field is reduced (absorbed) by induction effects, yielding an "effective field strength". This effect is also called "shielding" and varies with the electron distribution of atoms. The change of a resonance line due to binding effects is called the chemical shift. The spectra are recorded in relation to the proton signal of tetramethylsilane = $\text{Si}(\text{CH}_3)_4$ (TMS). An example of NMR being used in the determination of a structure is that of buckminsterfullerene (C_{60}). As this structure contains no hydrogen, ^{13}C NMR has to be used (longer acquisition time since ^{13}C is not the common isotope of carbon). However, the spectrum was obtained and was found to exhibit a single peak, confirming the unusual structure of C_{60} (Taylor et al., 1990).

4.8 Infrared Spectroscopy (IR)

The infrared spectroscopy deals with the electromagnetic spectrum of the near- (14000-4000 cm^{-1} ; 0.8-2.5 μm ; to excite overtone or harmonic vibrations), mid- (4000-400 cm^{-1} ; 2.5-25 μm ; to study fundamental vibrations and associated rotational-vibrational structures) and far-infrared (400-10 cm^{-1} ; 25-1000 μm ; used for rotational spectroscopy) regions; this light has a longer wavelength (lower frequency) than visible light. IR spectroscopy has been applied successfully for characterization in organic and inorganic compounds. Also it was successfully utilized in the field of semiconductor microelectronics (Lau 1999). Molecules absorb specific frequencies

that are characteristic of their structures; these absorptions are at resonant frequencies. A molecule to be "IR active" must be associated with changes in the permanent dipole. Molecules with the number N atoms have many vibrational modes: linear have $3N-5$ and nonlinear molecules have $3N-6$ vibrational degrees of freedom (e.g., H_2O has 3 degrees or modes). Stretching, bending, rocking, wagging and twisting vibrations were distinguished. Gaseous samples are measured in cells with a long path length of 5-10 cm. Liquid samples are placed between two plates of salt (e.g., NaCl, KBr, CaF). Solid samples are crushed with e.g. Nujol (oily agent) and smeared as a thin film onto salt plates. Sometimes microtomy cuts can be used. The techniques' arrangement consists of a light source (e.g., Nernst glower, Globar = SiC rod, mercury vapour lamp), a monochromator (former: Prisms, today: Gratings) or interferometer (mainly for FTIR technique), the sample position, and the detection arrangement (thermocouple, Golay detector, PbS cell, PbSe cell, or other semiconductors). Thus absorption spectra will be recorded as function of the frequency. Today the Fourier-transform-technique is used mostly. It permits to analyze a large amount of data when the total spectrum is recorded simultaneously (Fellgett's advantage or multiplex advantage). By this way both speed and signal-to-noise ratio are improved (White 1990). Fig. 3 exhibits the FTIR spectrum of a carbonitride sample.




Fig. 3. FTIR spectra of PECVD SiC_xN_y film grown at 973 K: total view and deconvolution of the main adsorption band into components.

4.9 Raman spectroscopy

Raman spectroscopy permits like IR spectroscopy to study vibrational and rotational modes of molecules (Gardiner, 1989). Whereas IR spectroscopy is mostly working in the absorption mode, the Raman scatter spectra are recorded in 90° geometry. Therefore both methods are complementary. Raman spectroscopy relies on inelastic (Raman) scattering of monochromatic (laser) light in the visible, near IR and near UV range, resulting in the energy of the laser photons being shifted down (Stokes lines) and up (Anti-Stokes lines). The light from the sample is collected with a lens, sent through a monochromator (holographic gratings, multiple dispersion stages, Czerny-Turner arrangements), and directed to a detector (photomultiplier, CCD camera).




Fig. 4. Typical Raman spectra of PECVD SiC_xN_y film grown at 373-673 K (left) and 873-973 K (right).

The Raman spectra provide a fingerprint by which the molecule can be identified. In solid state physics Raman spectroscopy characterizes materials and finds the crystallographic orientation of a sample. Raman spectra of carbonitride samples are shown in Fig. 4. In nanotechnology, a Raman microscope can be used to analyze nanowires to better understand the composition of the structures. Variations of Raman spectroscopy have been developed. The usual purpose is to enhance the sensitivity (e.g., surface-enhanced Raman), to improve the spatial resolution (Raman microscopy), or to acquire very specific information (resonance Raman) (Lombardi & Birke, 2008).

4.10 Wavelength and/or energy dispersive X-ray spectroscopy (WDX/EDX)

For excitation of atoms to emit X-rays, radiation of higher energy is required. For X-ray fluorescence (XRF) the emission of X-ray tubes, of radionuclides, or of synchrotron radiation is applied (Beckhoff et al. (Eds.), 2006; Van Grieken & Markowicz (Eds.), 2002). For the excitation of X-rays in SEM (see 4.3) electrons are used. The principle structure of a XRF device to determine the elemental composition is quite simple: source - sample - detector. The main properties of XRF systems are: simple element identification by Moseley's law; to be applied for non-destructive analysis of solid samples (compact or powders); simple conditions for the elemental region $20 < Z > 92$; for light elements vacuum conditions, windowless detectors and special sources are needed; the detection limit is in the range 10^{-4} - 10^{-7} g/g is related to the device, the source, the detector, the element, and the composition of the sample. The information depth depends on the incident energy, the composition of the sample, and the energy of the excited X-radiation - it varies from the μm -range to some cm-range. For a quantitative determination, calibration procedures using standard materials of a composition similar to the unknown sample or an evaluation using fundamental parameters are used. The principle of XRF is the excitation of electrons to a higher energy level (their relaxation leads to the emission of X-rays). These X-rays are divided into K-, L-, and M series, depending on the ground level of the electrons. Various cathodes (e.g., Cr, Pd, W) of the tubes or various radionuclides (^{55}Fe , ^{109}Cd , ^{241}Am) are used for a high efficient excitation. The incident X-ray beam usually is directed in an angle of 45° on the sample. The very intensive synchrotron radiation has various advantages: Continuous spectrum from about 1 eV up to many 10 keV, and tunable for optimal excitation (resonance), highly collimated beam. Semiconductor diodes are applied for energy-dispersive detection (EDX). An EDX spectrum of the light elements in a

silicon carbonitride sample is given in Fig. 5. In that case the spectra are recorded simultaneously. For wavelength-dispersive (WDX) detection a system with a diffraction monocrystal (or monolayer), collimators, and a combined proportional/scintillation counter are used. In that case the spectra are recorded sequentially. This system exhibits a better energetic resolution. For a quantitative analysis, calibration measurements are inserted in the procedure using reference materials with a composition similar to the sample to be analyzed. In all cases a validation is necessary: Either by measurement of well-known standard reference materials (SRM) or by comparison with the result of an independent analytical method.




Fig. 5. EDS spectrum of PECVD SiC_xN_y grown at 973 K using a (HMDS+He+ NH_3) mixture.

A special arrangement is used in the so called “total-reflection XRF (TXRF)”. The incident beam is directed onto a flat (polished) sample at an angle of $1\text{--}2^\circ$. In case of total reflection the penetration depth is in the nm-range. Therefore, this method can be used for surface analysis. As sample carrier quartz, plexiglass, glassy carbon, or boron nitride are applied. The absolute lower limit of detection (LLD) varies between 5 and 100 pg, that corresponds to a relative LLD of about 0.1–2 ng/g. The field of application is very broad: microsamples (droplets, particles), surface analysis, thin films from high vacuum techniques, semiconductor handling, evaporation and sputter procedures, and laser mirror production (Hein et al., 1992). A powerful technique can be build up by arranging a TXRF unit at a synchrotron beam line (Beckhoff et al., 2007).

4.11 Near-edge X-ray Absorption Fine Structure spectroscopy (NEXAFS)

NEXAFS, also known as “X-ray Absorption Near Edge Structure” (XANES), is an absorption spectroscopy method. Electrons from the core level are excited by photons to partially filled and empty states and the consequent emission of photoelectrons is measured (Hemraj-Benny et al., 2006). The resulting core hole is filled either via an Auger process or by capture of an electron from another shell followed by emission of a fluorescent photon. The absorption intensity is detected as a function of the exciting photons’ energy. NEXAFS measurements can detect specific bonds in molecules as well as the angular dependence of the specific orbitals involved (Stöhr 1992). The fluorescent photons originate from the the top 200 nm of the film, whereas the Auger electrons arise from the top 10 nm.




Fig. 6a. NEXAFS spectra of Si_3N_4 , SiC , and SiC_xN_y .

In a total-reflection geometry (see Figs. 6a,b) at the sample, the information depth using photon detection decreases to about 5 nm (Baake et al., 2010). As an example, detailed spectral resonances at the carbon K-edge yield information about the bonding environment of this atom, such as functionalized species and chemisorbed impurities. The lower π^* resonance can provide insights into bond hybridization, while the σ^* resonance is a measure of the intramolecular bond length. Since the light from the synchrotron source used is linearly polarized, the intensity of the π^* and σ^* transitions will be sensitive to the orientation of these orbitals (Hemraj-Benny et al., 2006).




Fig. 6b. NEXAFS spectra of BN , B_4C , and BC_xN_y .

The great power of NEXAFS derives from its elemental specificity. Additionally, NEXAFS can be used to determine: presence of defects and amorphous content in carbon nanotubes, varying degrees of bond hybridization in mixed sp^2/sp^3 -bonded carbon materials, degree of vertical alignment in nanotube samples, nature of oxygen-containing functional groups on nanotube surfaces (Hemraj-Benny et al., 2006). Applying grazing-incidence XRF-NEXAFS it will be possible to build up a profile of chemical bonding in multilayered samples (Pagels et al., 2010).

4.12 X-ray Photoelectron Spectroscopy (XPS)

X-ray photoelectron spectroscopy (XPS) is a technique that measures the elemental composition, empirical formula, chemical state and the electronic state of the elements in the

sample (Briggs & Seah 1990). The spectra are obtained by irradiation of a sample with a monochromatic X-ray beam while simultaneously measuring the kinetic energy and number of electrons that escape from a surface layer of 1 to 10 nm. XPS is a surface analysis technique. It is also known as “Electron Spectroscopy for Chemical Analysis (ESCA)”. XPS detects all elements except hydrogen and helium.




Fig. 7a. XPS spectra of Si_3N_4 , SiC , and SiC_xN_y .




Fig. 7b. XPS spectra of BN , B_4C , and BC_xN_y .

A typical spectrum is a plot of the intensity of the electrons detected versus their binding energy of (see Fig.7a,b for several silicon and boron compounds). The peaks in such a spectrum correspond to the electron configuration of the compounds in the sample. The number of detected electrons in a characteristic peak is directly related to the amount of the element in the area irradiated. To generate atomic percentage values the signal intensity must be corrected by the “relative sensitivity factor (RSF)”.

Monochromatic Al K_α X-rays with an energy of 1486.7 eV are used for excitation. As electron analyzer a “Concentric Hemispherical Analyzer (CHA)” is applied with a channeltron.

Under optimum conditions, the quantitative accuracy of the atomic percent values is 90-95% for major peaks and 60-80% of the true value for weaker signals (10-20% of the strongest signal). The binding energy will be determined via the equation (9)

$$h \cdot \nu = E_{\text{kin}} + E_{\text{B}}^{\text{V}}(\mathbf{k}), \quad (9)$$

where $h \cdot \nu$ = irradiation energy, E_{kin} =energy of the emitting electron, and $E_{\text{B}}^{\text{V}}(\mathbf{k})$ =binding energy. The determination of the different binding energies of an element in a sample is the most important power of XPS. It is stated by the “chemical shift” in comparison to a pure substance. For fixing the energy resolution over the total measuring region the electrons are limited to a constant velocity before their entrance into the analyzer (“pass energy”).

4.13 Transmission Electron Microscopy (TEM)

In transmission electron microscopy (TEM) an electron beam is transmitted through an ultra thin sample. An image is formed from the interaction (e.g., absorption, diffraction) of the electrons with the specimen. The electrons are guided through an expanded electron optical column. The imaging device is a fluorescent screen, a photographic film, or a CCD camera (Fultz & Howe, 2007; Rose, 2008). The analytical power of a TEM is described by the resolution properties: By reduction of spherical aberrations a magnification of 50 million times (resolution: $0.5 \text{ \AA} = 50 \text{ pm}$) is reached. The ability to determine the position of atoms has made the high-resolution TEM (HRTEM) an indispensable tool for nanotechnology research, including heterogeneous catalysis and the development of semiconductor devices for electronics and photonics (O’Keefe & Allard, 2004). High quality samples will have a thickness of only a few tens of nanometers. Preparation of TEM specimen is specific to the material under analysis. Some of the methods for preparing such samples are: Tissue sectioning by a microtome, sample staining, mechanical milling, chemical etching, and ion etching (sputtering). Recently, focussed ion beams (FIB) have been used for sample preparation (Baram & Kaplan, 2008).

For measurement of the fine structure of absorption edges to determine chemical differences in nano structures, electron energy loss spectroscopy (EELS) can be used. This method is a supplement to NEXAFS and XPS (mainly for nano sized samples).

4.14 Secondary Ion Mass Spectrometry (SIMS)

The advantages of secondary ion mass spectrometry (SIMS) can shortly be described as: Detection limit in the range of parts per million (ppm) or below, all elements can be measured (H-U), full isotopic analysis, atomic and molecular detection, rapid data acquisition, and three dimensional imaging capability (depth profiling) (Goldsmith et al., 1999). SIMS is based on the impact of primary ions (0.5-20 keV) on the sample surface, resulting in the sputtering of positive and negative secondary ions (atomic and molecular), electrons, and neutral species. SIMS instruments are build up by a primary ion source (e.g., O^- , O_2^+ , Cs^+), a sample manipulation system, a secondary ion extraction system, magnetic and electric fields mass spectrometer (double focussing) (also quadrupole and time of flight devices are applied), and several kinds of detectors (Faraday cup, electron multiplier, microchannel plate). As an example, a SIMS profile is given in Fig. 8 of a layered sample with the substrate Si(100) and a BCN layer on a Cu layer.

As positive ions are only a small fraction of the total sputtered material, a method called “secondary neutrals mass spectrometry (SNMS)” is in use. The transformation of raw spectral or image intensities into meaningful concentrations is still challenging.




Fig. 8. SIMS profile of a layered system BCN/Cu/Si.

4.15 Rutherford back scattering (RBS)

Rutherford back scattering (RBS) is a method applied in material science for the determination of the composition, the structure and of the depth profile in a sample (Oura et al., 2003). A beam of high energy (1-3 MeV) ions is directed on a sample. The ions partly backscattered at nuclei (the scattering at electrons leads to some extent to a decrease of the resolution) are detected. The energy of these backscattered ions is a function of the mass of the atoms (and of the scatter angle), at which the collision take place. An RBS instrument consists of an ion source (linear particle accelerator or an alpha particle source) and an energy sensitive detector (silicon surface barrier detector). In practice, the compositional depth profile can be determined from an intensity-energy measurement. The elements are characterized by the peak position in the spectrum and the depth can be derived from the width and shifted position of these peaks. Crystal structures (channeling) and surface information can also be evaluated from the spectra.

4.16 Elastic Recoil Detection Analysis (ERDA)

Elastic recoil detection analysis is a nuclear technique in materials science to obtain elemental concentration depth profiles in thin films. An energetic ion beam is directed at the sample to be depth profiled. As in RBS an elastic nuclear interaction with the atoms of the sample is observed. The energy of the incident ions (some MeV) is enough to recoil the atoms which are detected with a suitable detector. The advantage in ERDA is that all atoms of the sample can be recoiled if a heavy incident beam is used. For example, a 200 MeV Au beam is used with an ionization detector. In the right recoil angle the scattered incident beam ions do not reach the detector. ERDA is often used with a relatively low energy ^4He beam (2 MeV) for depth profiling of hydrogen.

5. Properties of carbonitride compounds

5.1 Silicon carbonitride compounds

Currently, strict conditions of modern technologies and aggressive working environment dictate higher requirements for construction materials quality. Two approaches are implemented to create new advanced materials: Synthesize radically new materials, or improve existing ones.

In the last twenty years, researchers from different countries are studying the possibility to synthesize a new class of multifunctional materials based on the ternary compound silicon carbonitride SiCN. Varying the elemental composition of silicon carbonitrides, that is, synthesis of any set of compounds, corresponding to the ternary phase diagram of Si-C-N from silicon and carbon nitrides to silicon carbide, diamond, and their mixtures, can obtain new materials with desired physical and chemical properties in a wide range.

It is assumed that these materials may possess the unique properties combining the best ones of the compounds mentioned, such as high mechanical strength and hardness, high thermal resistance, and chemical inertness. Silicon carbide SiC is studied as a promising high-temperature semiconductor material. It is known that silicon nitride Si₃N₄ is one of the key materials of modern electronics and a basic component of the ceramic composites. In recent years, there have been active attempts to synthesize carbon nitride C₃N₄ as a material having higher hardness than the one of diamond.

According to the literature, in those years several researchers have attempted to obtain silicon nitride films, not only with the use of ammonolysis of monosilane widely applied at that time, but also to develop many alternative ways of synthesis, in particular, with the use of organosilicon compounds. In the beginning of the 80-ies of the last century scientists from the Irkutsk Institute of Chemistry, specialized in synthesis of organosilicon compounds, used them as single-source precursors to obtain silicon nitride films. Hence, silicon nitride films were obtained in glow-discharge plasma from HMCTS in mixtures with N₂ or NH₃ at low temperatures (below 150°C) (Voronkov et al., 1981). There Si-N, C-C, Si-H (or Si-C≡N) and N-H chemical bonds were determined in the films obtained at such conditions. Later silicon nitride films were deposited by PECVD using a mixture of HMCTS and a wider set of additional gases such as NH₃, H₂, and N₂, and higher temperatures up to 400°C and plasma power (5-50 W) (Brooks & Hess, 1987, 1988). The set of characterization methods has been expanded. We can assume that so called silicon nitride films in reality consist of silicon carbonitride, whereas the films obtained from the mixture HMCTS+H₂ have significant amounts of carbon (30-40at.%) and 21at.% of hydrogen and contain both Si-N and Si-C bonds.

Lateron, the films were obtained by plasma enhanced chemical decomposition using HMCTS in the mixture with helium or nitrogen in the temperature range of 100-750°C and plasma powers of 15-50 W (Fainer et al., 2009a, 2009b). Physical and chemical as well as functional properties of these films were studied by FTIR, Raman spectroscopy, XPS, EDXRS, XRD using synchrotron radiation, SEM, AFM, nanoindentation, ellipsometry, spectrophotometry, and electrophysical methods. The evaluation of the results obtained by spectroscopic methods showed that the low temperature Si_xN_y films are compounds in which chemical bonding are present among Si, N, and C and with impurity elements, such as hydrogen and oxygen. Thus, a formula Si_xN_yO_z:H is more correct. Electrophysical and mechanical characteristics, and other physicochemical properties have allowed new consideration of these Si_xN_yO_z:H films as perspective interlayer dielectric films in

microelectronics devices of novel generation. The empirical formula of the high-temperature films is represented as SiC_xN_y . It was established that the films are nanocomposite materials consisting of an amorphous part and nanocrystals with a size of 1-60 nm having lattice parameters close to those of the standard phase $\alpha\text{-Si}_3\text{N}_4$. According to the Raman spectroscopic data, the films synthesized at a high temperature (up to 1023K) contain an insignificant number of graphite nanocrystals. The films synthesized from the mixture of HMCTS and helium or nitrogen exhibit an excellent transparency with a transmittance of 92-95% in the spectral range $\lambda=380\text{-}2500\text{ nm}$.

Thus, the increase number of research techniques and improving their accuracy revealed that the films obtained from one and the same single-source precursor HMCTS are silicon carbonitrides. SiC_xN_y films are nanocomposite materials consisted of an amorphous part and distributed nanocrystals having lattice parameters close to those of the standard phase $\alpha\text{-Si}_3\text{N}_4$. The films grown at above 973K contain inclusions of free graphite nanocrystals with a size of about 1 nm.

The compilation of publications, especially the earlier ones shows that among the authors involved in the synthesis of silicon carbonitride, no assumptions exist about what is meant by the term "carbonitride". Typically, the researchers saw it as a material having in its structure the elements of Si, C, and N. In this case, it may be a mixture of individual compounds as Si_3N_4 , C, and SiC, and/or ternary SiC_xN_y compounds of variable composition.

What is silicon carbonitride, what its possible structure, let us consider some examples. In one of the first publications Si-C-N deposits were obtained by CVD using mixtures of gaseous compounds such as SiCl_4 , NH_3 , H_2 , and C_3H_8 and very high temperatures from 1100 up to 1600°C (Hirai & Goto, 1981). The obtained amorphous deposits were mixtures of amorphous $\alpha\text{-Si}_3\text{N}_4$, SiC, and pyrolytic C (up to 10 weight %). The deposits surface had a pebble-like structure.

Thin films of amorphous silicon nitride and silicon carbonitride were grown on Si(100) substrates by pyrolysis of ethylsilazane [$\text{CH}_2\text{CH}_3\text{SiHNH}$] in mixtures with ammonia or hydrogen in the temperature range of 873-1073K (Bae et al., 1992). The films were studied by AES, RBS, and nuclear reaction analysis. It was shown, that the refraction index varied from 1.81 to 2.09. The hydrogen content was determined by ERDA to decrease from 21 to $8\pm 1\%$ in silicon carbonitride with increasing deposition temperature (873-1073K). According to AES the chemical composition of the films was determined as $\text{Si}_{43}\text{C}_7\text{N}_{48}\text{O}_2$. The silicon carbonitride films contained the bonds Si-C-N and Si-H.

Non-stoichiometric X-ray-amorphous $\text{Si}_{3+x}\text{N}_4\text{C}_{x+y}$ was deposited during pyrolysis of polysilazane at 1440°C (Schonfelder et al., 1993). The heating up to 1650°C results in formation of a mixture of nanocomposites $\text{Si}_3\text{N}_4/\text{SiC}$ or $\text{Si}_3\text{N}_4/\text{SiC}/\text{C}$.

SiC_xN_y coatings were obtained by CVD at 1000-1200°C using $\text{TMS-NH}_3\text{-H}_2$ (Beneddouché et al., 1997). These coatings were analyzed by XPS, Raman spectrometry, FTIR, TEM/EELS and ^{29}Si magic-angle spinning NMR (^{29}Si MAS-NMR). The main bonds are Si-C, Si-N, and C-C in these films. It was demonstrated that silicon carbonitride coatings obtained at high temperatures are nonhydrogenated. To clarify the chemical environment of silicon atoms by carbon and nitrogen atoms the $\text{SiKL}_{2,3}\text{L}_{2,3}$ line shapes were analyzed. It was shown that these peaks are decomposed into components corresponding to an intermediate position between the tetrahedra $\text{Si}(\text{C})_4$ and $\text{Si}(\text{N})_4$, i.e., silicon carbonitride films are not simply a mixture of phases of SiC and Si_3N_4 , and have a more complex relationship between the three elements, corresponding to the existence of $\text{Si}(\text{C}_{4-n}\text{N}_n)$ units. Mixed coordination shells

around silicon have been confirmed by TEM/EELS analyses. Also links were observed between the three elements: Silicon, nitrogen and carbon, which was confirmed by FTIR, and NMR.

Remote microwave hydrogen plasma CVD (RP-CVD) was used with BDMAADMS as precursor for the synthesis of silicon carbonitride (Si:C:N) films (Blaszczyk-Lezak et al., 2007). The Si:C:N films were characterized by XPS and FTIR, as well as by AFM. The increase of T_5 enhances crosslinking in the film via the formation of nitridic Si-N and carbidic Si-C bonds. On the basis of the structural data a hypothetical crosslinking reaction contributing to silicon carbonitride network formation have been proposed.

Si:C:N films were produced by RPCVD from a 1,1,3,3-TMDSN precursor and at a substrate temperature in the range of 30–400°C (Wrobel et al., 2007). The effects of the substrate temperature on the rate and yield of the RP-CVD process and chemical structure (examined by FTIR) of the resulting films were investigated. The Si:C:N film properties were characterized in terms of density, hardness (2.5–16 GPa), Young's modulus (43–187 GPa), and friction coefficient (0.02–0.05). With the IR structural data, reasonable structure–property relationships were determined.

Physical, optical, and mechanical properties were investigated of amorphous hydrogenated silicon carbonitride (a-Si:C:N:H) films produced by the remote PECVD from (dimethylamino)dimethylsilane in relation to their chemical composition and structure (Blaszczyk-Lezak et al., 2006). The films deposited at different substrate temperatures (30–400°C) were characterized in terms of their density (1.95–2.27 g/cm³), refractive index (1.8–2.07), adhesion to a substrate, hardness (24–35 GPa), Young's modulus (150–198 GPa), friction coefficient (0.036–0.084), and resistance to wear predicted from the "plasticity index" values $H/E^0=0.10-0.12$. The correlations between the film compositional parameters, expressed by the atomic concentration ratios N/Si and C/Si, as well as structural parameters described by the relative integrated intensities of the absorption IR bands from the Si-N, Si-C, and C-N bonds, and the XPS Si2p band from the Si-C bonds (controlled by substrate temperature) were investigated. On the basis of the results of these studies, reasonable compositional and structural dependencies of film properties were determined.

In his review Badzian proposed stable and solid phases in the ternary system Si-N-C as silicon carbonitride (Badzian, 2002). Silicon carbonitride films obtained at 1000–1200°C from mixture of tetramethylsilane, ammonia and hydrogen are characterized by a hardness of 38 GPa, that exceeds hardness of both Si₃N₄ and SiC.

Crystalline films of silicon carbonitride were obtained by MW-PECVD using H₂, CH₄, N₂, and SiH₄ mixture (Chen et al., 1998). The ternary compound (CSi)_xN_y exhibits a hexagonal structure and consists of a network wherein Si and C are substitutional elements. While the N content of the compound is in the range 35–40 at.%, the fraction of Si varies and can be as low as 10 at.%. The preliminary lattice parameters *a* and *c* are 5.4 and 6.7 Å, respectively. Photoluminescence of silicon carbonitride films has been studied as well. The direct band gap of crystalline (CSi)_xN_y is 3.8 eV at room temperature. The measurements of optical properties have shown that SiCN is a perspective wide-band material with energies suitable for light emitting diodes (LED) in blue and UV spectrum areas.

Si-C-N films were deposited on p-type Si(100) substrates by DC magnetron co-sputtering of silicon and carbon using a single sputter target with variable Si/C area ratios in nitrogen-argon mixtures (Vlcek et al., 2002). As a result, the N-Si and Si-N bonds dominate over the

N–C and Si–O bonds (XPS), preferred in a pure nitrogen discharge, and the film hardness increases up to 40 GPa.

SiCN coatings were deposited on silicon substrates (350°C) by PECVD using mixtures of methyltrichlorosilane (MTCs), nitrogen, and hydrogen (Ivashchenko et al., 2007). The coatings were characterized by AFM, XRD, and FTIR. Their mechanical properties are determined with nanoindentation. The abrasion wear resistance is examined using a ball-on-plane (calowear) test and adhesion to the base was tested using a scratch test. The XRD measurement indicates that the coatings are nanostructured and represent β -C₃N₄ crystallites embedded into an amorphous a-SiCN matrix. The coatings deposited at a higher nitrogen flow rate are amorphous. β -C₃N₄ crystallites embedded into the amorphous a-SiCN matrix promote an increase in hardness (25 GPa) and Young's modulus (above 200 GPa) of SiCN coatings.

Tribological tests have revealed that the friction coefficients of the coatings containing nitrogen are two to three times smaller than those based on SiC and deposited on a silicon substrate. The ball-on-plane tests show that the nanostructured coatings also exhibit the highest abrasive wear resistance. These findings demonstrate that the SiCN films deposited using MTCs show good mechanical and tribological properties and can be used as wear-resistant coatings.

SiCN hard films have been synthesized on stainless steel substrates by an arc enhanced magnetic sputtering hybrid system using a silicon target and graphite target in mixed gases of Ar and N₂ (Ma et al., 2008). The XRD results indicate that basically the SiCN films are amorphous. However, the HRTEM results confirm that the microstructure of the SiCN films with a high silicon content are nanocomposites in which nano-sized crystalline C₃N₄ hard particles are embedded in the amorphous SiCN matrix. The hardness of the SiCN films is found to increase with increasing silicon content, and the maximum hardness is 35 GPa. The SiCN hard films show a surprising low friction coefficient of 0.2 when the silicon content is relatively low.

SiCN films have been produced by means of reactive magnetron sputtering of a silicon target in an argon/nitrogen/acetylene atmosphere (Hoche et al., 2008). The mechanical, chemical, and structural properties have been thoroughly investigated by means of indentation hardness testing, pin on disk wear testing in reciprocating sliding motion, glow discharge optical emission spectroscopy (GDOES), FTIR, Raman spectroscopy, XPS. The main aim of this investigation was to establish the relationship between deposition conditions, resulting mechanical, chemical, structural, and the respective wear properties. Analogous to their position in the Si–C–N phase diagram, the hardness of the films varies over a broad range, with maximum values of around 30 GPa, while Young's modulus remains in a narrow range around 200 GPa. XPS spectra showed the main component to be Si–C, but Si–N and to a minor extent C–C bonds were also detected. Further, IR spectra suggested the presence of the carbodiimide group. Raman spectra show a varying ratio of sp³ to sp² carbon, depending on deposition condition. The hardest films were found along the SiC–Si₃N₄ tie line. In dry sliding their brittleness coupled with a high friction coefficient led to premature coating failure. Carbon rich films have a very low friction coefficient leading to good wear behaviour in dry conditions, but their ability to withstand high Hertzian pressures is reduced. The low friction coefficient of is attributed to more graphitic structures of the free carbon in the films.

To decrease the level of contamination of silicon melts during the Czochralski process the novel protective layer of silicon carbonitride was proposed for the inner surface of quartz

crucibles (Fainer et al., 2008). SiC_xN_y coatings were grown on fused silica substrates from hexamethyldisilazane with helium or ammonia in the temperature interval of 873–1073 K. Change of surface morphology, elemental composition and wetting angles were studied after the interaction of the surface of SiC_xN_y layers with the silicon melt at 1423 K by SEM, EDX and sessile drop measurements. The drop measurements after interaction of liquid Si ($\approx 1450^\circ\text{C}$) with the surface of SiC_4N sample determined a wetting angle of $\approx 90^\circ$ that implying a poor wetting. The lack of etching figures on the SiC_xN_y surface proved, that no chemical reaction starts of Si melt with the SiC_xN_y coating. In case of silicon carbonitride with larger concentration of nitrogen ($\text{Si}_2\text{C}_3\text{N}_2$) wetting angle was obtained as $\approx 60^\circ$ close to that one of Si melt on Si_3N_4 of $\approx 55^\circ$.

Silicon carbonitride (SiC_xN_y) films were grown on silicon substrates using the PLD technique (Boughaba et al., 2002). A SiC target was ablated by the beam of a KrF excimer laser in a N_2 background gas. The morphology, structure, composition, as well as the optical and mechanical properties of the coatings were investigated as functions of the N_2 pressure (1–30 mTorr) and substrate temperature (250 – 650°C). Smooth, amorphous films were obtained for all the processing parameters. The hardness, Young's modulus of the films were found to be a function of the growth regime; the highest values of the hardness and Young's modulus values were obtained in the low-pressure regime, in the range of 27–42 GPa and 206–305 GPa, respectively.

A visible-blind ultraviolet (UV) photodetector (PD) with metal-semiconductor-metal (MSM) structure has been developed on a cubic-crystalline SiCN film (Chang et al., 2003). The cubic-crystalline SiCN film was deposited on Si substrate with rapid thermal CVD (at 1150°C) using SiH_4 , C_3H_8 , NH_3 , and H_2 mixture. The optoelectronic performances of the SiCN-MSMPD have been examined by the measurement of photo and dark currents and the current ratio under various operating temperatures. The current ratio for 254 nm UV light of the detector is about 6.5 at room temperature and 2.3 at 200°C , respectively. The results are better than for the counterpart SiC of 5.4 at room temperature, and less than 2 for above 100°C , thus offering potential applications for low-cost and high-temperature UV detection.

The internal stress, optical gap, and chemical inertness were examined of amorphous silicon-nitride films incorporating carbon prepared by RF magnetron sputtering (Yasui et al., 1989). The carbon composition of the films was less than 15 at.%. The optical band gap was barely affected by the carbon addition. The internal stress was compressive in all films and increased up to 7.3×10^8 N/cm² in a-SiN:H films proportional to the nitrogen content, and decreased to less than half in carbon-free films. The buffered HF etch rate increased to greater than 1 $\mu\text{m}/\text{min}$ in proportion to the nitrogen content in SiN:H films. The etch rate decreased by about one order of magnitude with the addition of carbon.

In several papers thin films of silicon carbonitride are described with compositions varying in the wide range from similar to silicon carbide to similar to silicon nitride. These were synthesized by PECVD using HMDS as single-source precursor in the mixtures with helium, nitrogen or ammonia in the wide range of temperatures from 100 up to 800°C and RF plasma powers from 15 up to 70 W (Fainer et al., 1999, 2000, 2001a, 2001b, 2003, 2004, 2008). The nondestructive method XRD-SR was developed to determine phase composition and crystallinity of the obtained films composed of lightweight elements (Si, N, C) using the facilities of the station "Anomalous Scattering" (International Siberian Center for Synchrotron and Terahertz Radiation, Budker Institute of Nuclear Physics, SB RAS, Novosibirsk, Russia). The application of SR-XRD and high-resolution electron microscopy

with selective area electron diffraction (HRTEM-SAED) yielded to the result that silicon carbonitride films contain nanocrystals close to α -Si₃N₄, distributed in amorphous matrix of the film, i.e. the films are nanocomposite. The spectroscopic results (FTIR, XPS, EDX, AES, Raman) clarified that silicon carbonitride is a ternary compound, in which complex chemical bonds between all three elements – silicon, carbon and nitrogen with impurity of oxygen and inclusion of nanocrystalline graphite - are formed. The formation of mixed Si(C_{4-n}N_n) units could be proposed in the films. Apparently, the formation of nanocrystals With a phase composition close to the standard α -Si₃N₄ and the presence of silicon atoms surrounded by nitrogen and carbon atoms, suggests that some places in the crystal lattice occupied by silicon atoms may be substituted by isovalent carbon atoms. The formation of a substitutional solid solution is in fact possible. The films possess high transparency in the spectral region of 270–3500 nm and a large variation of band gap from 2.0 to 5.3 eV. Hydrogenated silicon oxycarbonitrides are perspective low-k dielectrics in the silicon technology of new generation. Presence of complex chemical bonds between three elements and nanocrystals in the films allowed obtaining films with higher hardness of above 30 GPa as compared with mixture phases such as α -Si₃N₄, SiC or C.

5.2 Boron carbonitride compounds

In the last 20 years the publications dealing with BCN are countless. They are dealing with the production, as described in the paragraphs 2 and 3. Additionally, the methods of characterization of BCN compounds to determine the elemental composition, the crystal structure, the chemical bonding, and several physical properties are abundant. All over the world (e.g., China, France, Germany, Japan, Korea, Spain, Russia, United States, and others) research and commercial materials science institutes were and are engaged in this field. The importance of BCN compounds is shown by the recent edition of a monography (Yap, 2009). Obviously, it is not possible to touch all the activities and to comment them. The selection we have made is therefore somewhat subjective and somewhat accidental.

The first activities on boron carbonitride dealt with high-melting substances, mainly to be applied in space technique. For these specimen neither physical nor chemical characterization is described in the relevant papers (Samsonov et al., 1962; Chepelenkou et al., 1964). Nearly 10 years later, another group (Kosolapova et al., 1971) using XRD measurements characterized the products from elemental composition data as BCN. The structure of this boron carbonitride is based on BN with a somewhat increased period *c* of the crystal lattice. The black powder with a particle (branched) size of the order of 1 μ m showed a density of 2.13 g/cm³ (determined by pycnometry). As secondary constituents or as impurities boron carbide B₄C and graphite C were identified.

In the first (to our knowledge) experimental paper on BCN from the United States (Kaner et al., 1987) another group dealing with BCN is cited (Badzian, 1972). In the paper of Kaner et al. outstanding analytical methods as XRD and XPS were applied for the characterization of the product, not being a mixture of BN+C but a specific new chemical compound B_xC_yN_z with a ratio of boron and nitrogen approximately 1:1 and an increasing fraction of C with increasing temperature at synthesis. This new compound shows a room temperature conductivity $\sigma = 6 \times 10^{-4}$ S/cm (whereas BN is an insulator), a thermal band gap of 0.2 eV, and is intercalated by strong reducing and oxidizing agents.

Referring to the papers of Badyan et al. and Kaner et al. a calculation examination of the BCN compounds was performed by Liu et al. (Liu et al., 1989). The possible atomic

arrangements and the electronic structures of three models of BC_2N were studied. A correlation was found between the structural symmetries and the conducting properties. Two structures were found to have semiconducting gaps and one to be metallic. This behaviour is similar to the relation of graphite to BN. This paper initiated a world wide activity in synthesizing of BC_xN_y by various methods and characterizing the products by an increasing number of analytical methods. Beneath the interest for the chemical structure, the elemental composition, the speciation (chemical bonding), and the relation between chemical situation and physical properties were investigated, up to now.

About 10 years later a review on BCN materials was published (Kawaguchi 1997). The chemical bond energies are given as B-N: 4.00 eV, C-C: 3.71 eV, N-C: 2.83 eV, and N-N: 2.11 eV. Furthermore, the product is described by a possible replacement of nitrogen by carbon in h-BN. The conductivity of BC_2N was found to be variable over several orders of magnitude at room temperature related to the synthesis conditions. The conductivity of BC_3N was 10 times lower than that of carbon plates, and slightly larger than that of BC_2N - the increase at temperatures between 25 and 700°C shows, that BC_3N is stated to be a semiconductor. Additionally, photoluminescence and cathodoluminescence were observed for BN(C,H) films, intercalation chemistry is discussed, and an application of intercalated Li into B/C/N is proposed for Li battery systems. Mainly, for the future it is desirable to receive large-crystalline B/C/N materials, e.g., by a selection of appropriate starting materials for CVD.

In the same year BCN samples were prepared by nitridation of B_4C (Kurmaev et al. 1997). For characterization X-ray emission, XRD, Raman, and TEM-EELS were used. New signals were found (no B_4C , no graphite, no h-BN), which confirmed the structural model in which boron nitride monolayers are in random intercalation with the graphite ones.

BCN films were deposited by RF magnetron sputtering from h-BN and graphite targets in an Ar- N_2 gas mixture (Zhou et al. 2000). A large variety of analytical methods was used: XPS, Auger, FTIR, Raman, XRD, and nanoindentation. B-N, B-C, and C-N bonds were identified. No phase separation between h-BN and graphite was observed. Amorphous BC_2N films with an atomically smooth surface were obtained. As mechanical and tribological parameters were measured: Hardness in the range 10-30 GPa, microfriction coefficient was 0.11 under a load of 1000 μ N, and the Young's modulus was within 100-200 GPa.

In the following years a number of papers was published by a Spanish group. Their method of production was the IBAD technique. Therein B_4C was evaporated with concurrent N_2^+ bombardment (Gago et al., 2001a, 2001b, 2002a, 2002b). Various methods were used to identify the character of the products: NEXAFS, FTIR, Raman, HRTEM, and time-of-flight-ERDA. The results can be summarized as follows: c-BCN and h-BCN ($B_{50}C_{10}N_{40}$, solubility of C in h-BN about 15%) were identified, and the transition from amorphous B_xC to h-BN-like structures was observed. As physical parameters a hardness of 35 GPa, a Young's modulus, a friction coefficient of 0.05, and thermal stability were measured.

Fullerene-like B-C-N products were synthesized by dual cathode sputtering (Hellgren et al., 2004). By means of RBS, SEM, HRTEM, and nanoindentation a fullerene-like microstructure was determined and an elastic response was observed.

The incorporation of carbon into the crystal structure of h-BN was stated first by S.C. Ray (Ray et al., 2004) using XRD and NEXAFS examinations.

In these years, a systematic examination of BCN products can be observed from the literature. For chemical bonding determination mainly XPS and NEXAFS (also FTIR) are

used, and the hardness is measured by nanoindentation. Caretti et al. described an experimental reliable change of carbon in BC_xN yielding hexagonal structure (Caretti et al., 2004). They describe a hardness of 17 GPa, a Young's modulus of 170 GPa, and friction and wear experiments. An increase of the carbon flux is followed by an increase of carbon in the product (increase of the sp^3 fraction) that improves the mechanical properties. Morant et al. and Zhou et al. produced samples with a hardness of 33 GPa, determined the roughness, and established excellent friction properties (Morant et al., 2005; Zhou et al., 2006). The chemical properties were determined by XPS with an identification of B-N, B-C, and C-N bonds. The highest value for the hardness of 40 GPa were published in 2005 (Kosinova et al., 2005).

One of first papers dealing with the production of BCN compounds by using a large molecule as precursor is authored by Uddin et al. (Uddin et al., 2005). The product was identified as graphite-like BCN with B-C, B-N, and B-C-N hybrids.

Beneath the usual characterisation of BCN compounds by XPS and FTIR, the chemical behaviour (solubility) in acidic, neutral, and alkaline solutions was examined (Byon et al., 2006). In HCl no anodic dissolution was observed, in NaOH the dissolution depends on the potential and is increasing with increasing pH.

The group from Osaka, Japan, synthesized polycrystalline BCN by PECVD (Tai et al., 2003). Various properties of the films were investigated in the last years: e.g., electrical and optical characteristics (Yuki et al., 2004), influence of UV radiation on dielectric constant (Zhang et al., 2005), adaptation as humidity sensor (Aoki et al., 2007), acid and alkaline wet influence on quality of LSI devices (Watanabe et al., 2008), modification of the tunneling controlled field emission (Sugino et al., 2010).

BCN compounds were synthesized by DC reactive sputtering of B_4C target in a gas mixture of N_2 and Ar (Xu et al., 2006). The composition of the product depends on the N_2/Ar ratio. By nanoindentation the surface morphology and roughness were examined.

A method of BCN production by PECVD with TMB (+benzene) is described by Thamm et al. (Thamm et al., 2007). The main result is: The structure and the mechanical properties are in strong dependence on the substrate temperature.

An amorphous product was synthesized with corrosion protection properties better than B_4C and CN_x (Chen et al. 2006) for commercial application. This is attributed to the smoother morphology of $B_xC_yN_z$ films. The hardness was determined to be 20 ± 3 GPa, and the Young's modulus to 210 ± 30 GPa.

BCN compounds were produced by ball milling of h-BN, graphite and polypropylene (Torres et al., 2007). SEM, XRD, FTIR, and NEXAFS examinations yielded compositions as BCN, BC_2N , BC_4N , $BCNH_2$, a-BCN, and a- BC_4N . The particles are nearly spherical in shape (60 nm), whereas the crystallites have a size of about 1 nm. Tribological studies were performed on a- BC_4N films with a thickness of 2 μm (Caretti et al., 2007). Nanoindentation shows a hardness of 18 GPa and a Young's modulus of 170 GPa, whereas the wear examinations yielded in a constant rate of 2×10^{-7} mm^3/Nm and a coefficient of friction of 0.2.

h-BCN was synthesized in a PECVD with triethylamine borane (TEAB) or with tris-(dimethylamine) borane (TDEAB) as single source precursors (Mannan et al., 2008, 2009). The chemical characterization by FTIR, XPS and NEXAFS showed B-N, B-C, C-N, and B-C-N bonds. A h-BCN (or sp^2 -BCN) was produced with a microhardness of 4 GPa (nanoindentation).

Various single source precursors (TMAB, TEAB, TMB) were introduced in a PECVD system. XPS, NEXAFS, and SEM/EDX were used for chemical identification. As results are determined h-BCN with stoichiometric formulas B_2C_3N (produced without NH_3) or B_2CN_3 (produced with NH_3).

Thick (20-70 nm) amorphous $B_xC_yN_z$ films were produced by DMAB ($(CH_3)_2HN: BH_3$) in a CVD procedure (Wu et al., 2010). XPS and SIMS were used for the determination of the elemental composition. The stoichiometry factors varied drastically: $0.46 \leq x \leq 0.68$; $0.07 \leq y \leq 0.43$; $0.01 \leq z \leq 0.26$. The results on thick BCN films are encouraging.

As can be derived from a large number of papers, the synthesized compounds are h-BCN in which carbon is replacing to some extent nitrogen in the hexagonal boron nitride structure. An extended TEM examination enlarge the knowledge in this field (Caretti et al., 2010). For low carbon content the h-BN is preserved in boron carbonitride compounds. By increasing the carbon content towards BCN stoichiometry ($1 < x > 2$) the hexagonal stacking sequence tends into a fullerene-like structure. Increasing the carbon content to the composition BC_4N , the sample exhibit an amorphous structure. Surprisingly, the authors call their compounds "solid solutions", although in various papers the chemical bonds B-C, B-N, and C-N were determined, yielding a defined chemical, completely hybridized compound and not a solution (Caretti et al., 2010).

Only a few papers announced the production of c-BCN (e.g., Gago et al., 2001a). The yield of this material (in IBAD), proposed to be as hard as diamond, was related to the optimization of the deposition temperature, the Ar content in the gas mixture, to the assisting current density, and to the ion energy. Although, the identification of c-BCN is still not proved (Mannan et al., 2011).

6. Acknowledgements

The authors acknowledge the financial support granted by the Deutsche Forschungsgemeinschaft (DFG) for the research projects "nanolayer speciation" (EN 207/22-1) and "chemical and physical characterization of nanolayers" (EN 207/22-2). The authors of the Russian Federation thank RFBR for the grant 07-03-91555-NNIOa and 10-03-91332-NNIOa.

7. References

- Als-Nielsen, J. (2001). *Elements of Modern X-Ray Physics*. Wiley, New York
- Abdellaoui, A., Bath, A., Bouchikhi, B., & Baehr, O. (1997). Structure and optical properties of boron nitride thin films prepared by PECVD. *Mater. Sci. Engin. B*, Vol. B47, No. 3, pp.257-262, ISSN 0921-5107
- Ahn, H., Alberts, L., Kim, Y.-M., Yu J., & Rie, K.T. (2003). BCN coatings at low temperature using PACVD: capacitive vs. inductive plasma coupling. *Surf. Coat. Technol.*, Vol. 169 -170, (June 2003), pp. 251-253, ISSN 0257-8972
- Ahn, H., Klimek, K.S., & Rie K.-T. (2003). BCN coatings by RF PACVD at low temperature. *Surf. Coat. Technol.*, Vol. 174 -175, pp. 1225-1228, ISSN 0257-8972
- Aoki, H., Shima, H., Kimura, C., & Sugino, T. (2007). Characterization of boron carbon nitride film for humidity sensor. *Diamond Related Materials* *Diamond Relat. Mater.*, Vol. 16, No. 4-7, pp. 1300-1303, ISSN 0925-9635

- Aoki, H., Tokuyama, S., Sasada, T., Watanabe, D., Mazumder, M. K., Kimura, C., & Sugino, T. (2008). Dry etching properties of boron carbon nitride (BCN) films using carbon fluoride gas. *Diamond Relat. Mater.*, Vol. 17, No. 7-10, pp.1800-1804, ISSN 0925-9635
- Aoki, H., Watanabe, D., Moriyama, R., Mazumder, M. K., Komatsu, N., Kimura, C., & Sugino, T. (2008). Influence of moisture on BCN (low-K) film for interconnection reliability. *Diamond Relat. Mater.*, Vol. 17, No. 4-5, pp. 628-632, ISSN 0925-9635
- Aoki, H., Hara, M., Masuzumi, T., Mazumder, M. K., Ooi, N., Watanabe, D., Kimura, C., & Sugino, T. (2009). Influence of Cu electroplating solutions on boron carbon nitride (BCN) film. *Appl. Surf. Sci.*, Vol. 255, No. 6, (October 2008), pp. 3719-3722, ISSN 0169-4332
- Aoki, H., Masuzumi, T., Hara, M., Watanabe, D., Kimura, C., & Sugino, T. (2009). Boron carbon nitride film containing hydrogen for 2nm node low-k interconnection, *VLSI Technology, Systems, and Applications (VLSI-TSA) 2009 International Symposium*, Hsinchu, April 2009
- Aoki, H., Masuzumi, T., Watanabe, D., Mazumder, M.K., Sota, H., Kimura, C., & Sugino, T. (2009). Influence of oxygen plasma treatment on boron carbon nitride film composition. *Appl. Surf. Sci.*, Vol. 255, No. 6, October 2008, pp. 3635-3638, ISSN 0169-4332
- Aoki, H., Tokuyama, S., Masuzumi, T., Hara, M., Mazumder, M. K., Watanabe, D., Kimura, C., & Sugino, T. (2009). Synthesis of methyl boron nitride film as low-k insulating film for LSI interconnection. *Diamond Relat. Mater.*, Vol. 18, No. 5-8, pp. 1048-1051, ISSN 0925-9635
- Aoki, H., Hara, M., Masuzumi, T., Ahmed, F., Kimura, C., & Sugino, T. (2010). Dry etching properties of methyl-BCN film with C4F8 gas for Cu/low-k interconnection. *Diamond Relat. Mater.*, Vol. 19, No.5-6, (January 2010), pp. 507-509, ISSN 0925-9635
- Aoki, H., Masuzumi, T., Hara, M., Lu, Z., Watanabe, D., Kimura, C., & Sugino, T. (2010). Influence of the methyl group on the dielectric constant of boron carbon nitride films containing it. *Diamond Relat. Mater.*, Vol. 19, No.12, (June 2010), pp. 1437-1440, ISSN 0925-9635
- Awad, Y., El Khakani, M.A., Aktik, C., Mouine, J., Camiré, N., Lessard, M., Scarlete, M., Al-Abadleh, H.A., & Smirani, R. (2009). Structural and mechanical properties of amorphous silicon carbonitride films prepared by vapor-transport chemical vapor deposition. *Surf. Coat. Technol.*, Vol. 204, No.4, (August 2009), pp.539-545, ISSN 0257-8972
- Baake, O., Hoffmann, P.S., Kosinova, M.L., Klein, A., Pollakowski, B., Beckhoff, B., Fainer, N.I., Trunova, V.A., & Ensinger, W. (2010). Analytical characterization of BC_xN_y films generated by LPCVD with triethylamine borane. *Analytical & Bioanalytical Chemistry*, Vol.398, No.2, (June 2010), pp.1077-1084, ISSN 1618-2642
- Badyan, A., Nemiski, T., Appenheimer, S., & Olkusnik, E. (1972). Crystal structure in the system boron - carbon - nitrogen - In: *Himicheskaya soyaz v poluprovodnikah i polumetallah*, pp. 362-366, "Nauka I tehnika", Minsk (in Russian)
- Badzian, A. (2002). Stability of Silicon Carbonitride Phases. *J. Am. Ceram. Soc.*, Vol.85, pp.16-20
- Badzian, A.R., Niemyski, T., Appenheimer, S., & Olkusnik, E. (1972). Graphite-Boron Nitride solid solution by chemical vapor deposition. *Proc. Third Inter.Conf.CVD*. Vol.3, pp.747-753, Salt Lake City, UT, 1972
- Bae, Y. W., Du, H., Gallois, B., Gonsalvest, K. E., & Wilkens, B. J. (1992). Structure and Chemistry of Silicon Nitride and Silicon Carbonitride Thin Films Deposited from

- Ethylsilazane in Ammonia or Hydrogen. *Chem. Mater.*, Vol.4, No.2, pp.478-483, ISSN 0897-4756
- Baehr, O., Theverin, P., Bath, A., Koukab, A., Losson, E., & Lepley, B. (1997). Preparation of boron nitride thin films by microwave plasma enhanced CVD, for semiconductor applications. *Mater. Sci. Engin. B*, Vol.B46, pp.101-104, ISSN 0921-5107
- Baram, M., Kaplan, W.D., (2008). Quantitative HRTEM analysis of FIB prepared specimens. *J. Microscopy*, Vol.232, No.3, pp. 395-405, ISSN 0022-2720
- Bath A., van der Put P.J., Lepley B. (1989). Study of boron nitride gate insulators grown by low temperature plasma enhanced chemical vapor deposition on InP. *Appl. Surf. Sci.*, V.39, pp.135-140, ISSN 0169-4332
- Bath, A., van der Put, P.J., Becht, J.G.M., Schooman, J., & Lepley, B. (1991). Plasma enhanced chemical vapor deposition and characterization of boron nitride gate insulators on InP. *J. Appl. Phys.*, Vol.70, No.8, pp.4366-4370, ISSN 0021-8979
- Bath, A., Baehr, O., Barrada, M., Lepley, B., van der Put, P.J., & Schoonman, J. (1994). Plasma enhanced chemical vapour deposition of boron nitride onto InP. *Thin Solid Films*, Vol.241, pp.278-281, ISSN 0040-6090
- Bauer-Marschallinger, J., Reitinger, B., Pfaff, H. (2007). Nanoindentation und Oberflächenwellen (Laser-ultraschall) zur Charakterisierung dünner Schichten. *Industrielles Symposium Mechatronik*. Linz, Austria
- Beckhoff, B., Kanngieser, B., Langhoff, N., Wedell, R., & Wolff, H. (Eds.), (2006). *Practical X-Ray Fluorescence Analysis*. Springer Verlag, ISBN-10 3-540-28503-9
- Beckhoff, B., Fliegau, R., Kolbe, M., Müller, M., Weser, J., & Ulm, G., (2007). Reference-Free Total Reflection X-ray Fluorescence Analysis of Semiconductor Surfaces with Synchrotron Radiation. *Analytical Chemistry*, Vol.79, No.20, pp.7873-7382, ISSN 0003-2700
- Beneddouch, A., Berjoan, R., Beche, E., Merle-Mejean, T., Schamm, S., Serin, V., Taillades, G., Pradel, A., & Hillel, R. (1997). Structural characterization of amorphous SiC_xN_y chemical vapor deposited coatings. *J.Appl.Phys.*, Vol.81, No.9, pp.6147-6154, ISSN 0021-8979
- Bengu, E., Genisel, M. F., Gulseren, O. & Ovali, R. (2009). Theoretical and spectroscopic investigations on the structure and bonding in B-C-N thin films. *Thin Solid Films*, Vol. 518, No. 5, pp. 1459-1464, ISSN 0040-6090
- Besmann, T. M. (1990). Chemical Vapor Deposition in the Boron-Carbon-Nitrogen System. *J.Amer. Ceram. Soc.*, Vol.73, Is. 8, April 1990, pp.2498-2501, ISSN 0002-7820
- Blaszczak-Lezak, I., Wrobel, A. M., Kivitorma, M. P. M., & Vayrynen, I. J. (2005). Silicon Carbonitride Films Produced by Remote Hydrogen Microwave Plasma CVD Using a (Dimethylamino)dimethylsilane Precursor. *Chem. Vap. Deposition*, Vol. 11, No. 1, (January 2005), pp. 44-52, ISSN 0948-1907
- Blaszczak-Lezak, I., Wrobel, A.M., Aoki, T., Nakanishi, Y., Kucinska, I., & Tracz. A. (2006). Remote nitrogen microwave plasma chemical vapor deposition from a tetramethyldisilazane precursor. 1. Growth mechanism, structure, and surface morphology of silicon carbonitride films. *Thin Solid Films*, Vol. 497, No.1-2, (February 2006), pp. 24-34, ISSN 0040-6090
- Blaszczak-Lezak, I., Wrobel, A.M., & Bielinski, D.M. (2006). Remote nitrogen microwave plasma chemical vapor deposition from a tetramethyldisilazane precursor. 2. Properties of deposited silicon carbonitride films. *Thin Solid Films*, Vol. 497, No. 1-2, (February 2006), pp. 35-41, ISSN 0040-6090

- Blaszczuk-Lezak, I., Wrobel, A.M., & Bielinski, D.M. (2006). Remote hydrogen microwave plasma chemical vapor deposition of silicon carbonitride films from a (dimethylamino)dimethylsilane precursor: Compositional and structural dependencies of film properties. *Diamond Relat. Mater.*, Vol. 15, No. 10, (October 2006), pp. 1650–1658, ISSN 0925-9635
- Blaszczuk-Lezak, I., Wrobel, A.M., Kivitoroma, M.P.M, Vayrynen, I.J., & Tracz, A. (2007). Silicon carbonitride by remote microwave plasma CVD from organosilicon precursor: Growth mechanism and structure of resulting Si:C:N films. *Appl. Surf. Sci.*, Vol. 253, No. 17, (June 2007), pp. 7211-7218, ISSN 0169-4332
- Boudiombo, J., Baehr, O., Boudrioua, A., Thevenin, P., Loulergue, J.C., & Bath, A. (1997). Modes of propagating light waves in thin films of boron nitride deposited by plasma enhanced chemical vapor deposition. *Mater. Sci. Engin. B*, Vol.B46, pp.96-98, ISSN 0921-5107
- Boughaba, S., Sproule, G.I., McCaffrey, J.P., Islam, M., & Graham, M.J. (2002). Synthesis of amorphous silicon carbonitride films by pulsed laser deposition. *Thin Solid Films*, Vol. 402, pp.99-110, ISSN 0040-6090
- Bragg, W.H., Bragg, W.L., (1913). The structure of the diamond. *Nature*, Vol.91, No.2283, p.557, ISSN 0028-0836.
- Briggs, D.,; Seah, M.P., (1990). *Practical Surface Analysis*. Vol.1, Wiley
- Brooks, T.A., Hess, D.W. (1987). Plasma-enhanced chemical vapor deposition of silicon nitride from 1,1,3,3,5,5 - hexamethylcyclotrisilazane and ammonia. *Thin Solid Films.*, Vol.153, No. 1-3, (March 1987), pp.521-529, ISSN 0040-6090
- Brooks, T.A., Hess, D.W. (1988). Deposition chemistry and structure of plasma-deposited silicon nitride films from 1,1,3,3,5,5 - hexamethylcyclotrisilazane. *J. Appl. Phys.*, Vol.64, No. 2, (January 1988), pp. 841–849, ISSN 0021-8979
- Brydson, R., Daniels, H., Fox, M.A., Greatrex R., & Workman, C. (2002). Synthesis of a new boron carbonitride with a B₄C-like structure from the thermolysis of N-alkylated borazines. *Chem. Commun.*, No.7, (February 2002), pp. 718–719
- Bulou, S., Le Brizoual, L., Miska, P., de Poucques, L., Hugon, R., & Belmahi, M. (2010). a-Si_xN_y thin films deposited by a microwave plasma assisted CVD process using a CH₄/N₂/Ar/HMDSN mixture: methane rate effect. *IOP Conf. Series: Materials Science and Engineering.*, Vol. 12, pp.012002-012005
- Byon, E., Son, M., Hara, N. & Sugimoto, K. (2004). Corrosion behavior of boron-carbon-nitride films grown by magnetron sputtering. *Thin Solid Films*, Vol. 447-448, pp. 197-200, ISSN 0040-6090
- Byon, E.; , Son, M.; , Lee, K.-H.; , Nam, K.-S.; , Hara, N.; , Sugimoto, K., (2006). Electrochemical properties of boron-carbon-nitride films formed by magnetron sputtering. *Electrochim.Acta*, Vol.51, No.13 (August 2005), pp.2662-2668, ISSN: 0013-4686
- Cao, Z. X. (2001). Nanocrystalline silicon carbonitride thin films prepared by plasma beam-assisted deposition. *Thin Solid Films*, Vol. 401, pp.94-101, ISSN 0040-6090
- Cao, Z. X., Oechsner, H. (2003). Optical and mechanical characteristics of nanocrystalline boron carbonitride films synthesized by plasma-assisted physical vapor deposition. *J. Appl. Phys.* Vol. 93, No. 2, (October 2002), pp. 1186-1189
- Caretti, I., Jimenez, I., & Albella J.M. (2003). BCN films with controlled composition obtained by the interaction between molecular beams of B and C with nitrogen ion beams. *Diamond Relat. Mater.*, Vol. 12, pp. 1079–1083, ISSN 0925-9635

- Caretti, I.; Jimenéz, I.; Gago, R.; Cáceres, D.; Abendroth, B.; & Albella, J.M., (2004). Tribological properties of ternary BCN films with controlled composition of bonding structure. *Diamond Relat. Mater.*, Vol.13, No.4-8, pp.1532-1537, ISSN 0925-9635
- Caretti I., Albella J.M., Jimémez I. (2007). Tribological study of amorphous BC₄N coatings. *Diamond Relat. Mater.*, Vol. 16, No.1, (March 2001), pp. 63–73, ISSN 0925-9635
- Caretti, I., Torres, R., Gago, R., Landa-Cánovas, A.R., & Jiménez, I. (2010). Effect of Carbon Incorporation on the Microstructure of BC_xN (x=0.25, 1, and 4) Ternary Solid Solutions Studied by Transmission Electron Microscopy. *Chem. Mater.*, Vol. 22, No.6, (February 2010), pp. 1949–1951, ISSN 0897-4756
- Chang, W.-R., Fang, Y.-K., Ting, Sh.-F., Tsair, Y.-Sh., Chang, Ch.-N., Lin, Ch.-Yu, & Chen, Sh.-F. (2003). The Hetero-Epitaxial SiCN/Si MSM Photodetector for High-Temperature Deep-UV Detecting Applications. *IEEE Electron Device Letters*, Vol. 24, No.9, pp.565-567, ISSN 0741-3106
- Charitidis, C., Panayiotatos, Y., & Logothetidis, S. (2003). A quantitative study of the nano-scratch behavior of boron and carbon nitride films. *Diamond Relat. Mater.*, Vol. 12, No. 3-7, pp. 1088-1092, ISSN 0925-9635
- Chen, C.W., Huang, C.C., Lin, Y.Y., Chen, L.C. & Chen, K.H. (2005). The affinity of Si-N and Si-C bonding in amorphous silicon carbon nitride (a-SiCN) thin film. *Diamond Relat. Mater.*, Vol.14, No.3-7, pp.1126– 1130, ISSN 0925-9635
- Chen, L. C., Chen, C. K., Wei, S. L., Bhusari, D. M., Chen, K. H. & Huang, Y. S. (1998). Crystalline silicon carbon nitride: A wide band gap semiconductor. *Appl. Phys. Lett.*, Vol. 72, No.19, (March 1998), pp.2463-2465, ISSN 0003-6951
- Chen, Y.; Chung, Y.-W.; & Li, S.-Y., (2006). Boron carbide and boron carbonitride thin films as protective coatings in ultra-high density hard disc drives. *Surf. Coat. Technol.*, Vol.200, No.12-13 (February 2005), pp.4072-4077, ISSN 0257-8972
- Chen, Z., Lin, H., Zhou, J., Ma, Z., & Xie, E. (2009). IR studies of SiCN films deposited by RF sputtering method. *J. Alloys and Compounds*, Vol.487, pp. 531–536, ISSN 0925-8388
- Cheng, W., Jiang, J., Zhang, Y., Zhu, H., & Shen, D. (2004). Effect of the deposition conditions on the morphology and bonding structure of SiCN films. *Materials Chemistry and Physics*, Vol. 85, No.2-3, (January 2004), pp.370–376, ISSN 0254-0584
- Cheng, W., Lin F., Shi W., Ma X., Shen D., & Zhang, Y. (2006). Synthesis and field emission property of SiCN cone arrays. *Materials Chemistry and Physics*, Vol.98, (September 2005), pp.500-503, ISSN 0254-0584
- Chepelenkou, Y.V., Em, A.P., Borodulin, P.Y., & Momot, L.B. (1964). Thermal stability of refractory crucibles based on boron nitride. No.6, p.253.
- Dekempeneer, E.H.A., Meneve, J., Kuypers, S., & Smeets, J. (1996). Tribological properties of r.f. PACVD amorphous B-N-C coatings. *Thin Solid Films*, Vol. 281-282, pp. 331-333, ISSN 0040-6090
- Dekempeneer, E., Wagner, V., Gibson, P., Meneve, J., Kuypers, S., van Izendoorn, L., Smeets, J., Geurts, J., & Caudano, R. (1997) Tribology and microstructure of PACVD B-N-C coatings. *Diamond Film & Technol.* Vol.7, No.3, pp. 181-193., ISSN 0917-4540
- Derre, A., Filipozzi, L., Bouyer, F. & Marchand, A. (1994) Parametric study of the chemical vapour deposition of carbon-boron-nitrogen compounds. *J. Mater. Sci.*, Vol. 29, No. 6, pp.1589-1594, ISSN 0022-2461
- Dez, R., Ternergal, F., Reynaud, C., Mayne, M., Armand, X. & Herlin-Boime, N. (2002). Laser synthesis of silicon carbonitride nanopowders; structure and thermal

- stability. *J. European Ceramic Society*, Vol. 22, No.16, (February 2002), pp.2969–2979, ISSN 0955-2219
- Di Mundo, R., d'Agostino, R., Fracassi, F., & Palumbo, F. (2005). A Novel Organosilicon Source for Low Temperature Plasma Deposition of Silicon Nitride-like Thin Films. *Plasma Process. Polym.*, Vol. 2, No. 8 (June, 2005), pp. 612–617, ISSN 1612-8850
- Dinescu, M., Perrone, A., Caricato, A.P., Mirengi, L., Gerardi, C., Ghica, C., & Frunza, L. (1998). Boron carbon nitride films deposited by sequential pulses laser deposition. *Appl. Surf. Sci., Appl. Surf. Sci.*, Vol. 127-129, pp. 692-696, ISSN 0169-4332
- Du, X.-W., Fu, Y., Sun, J., Yao, P., & Cui, L. (2007). Intensive light emission from SiCN films by reactive RF magnetron sputtering. *Materials Chemistry and Physics*. Vol.103, pp.456–460, ISSN 0254-0584
- Dubovik, T.V. & Struk, L.I. (1965). Electric insulation tube of boron carbonitride for protection of metal thermocouples. *Translated from Poroshkovaya Metallurgia*, No.5, pp.107-110
- Etou, Y., Tai, T., Sugiyama, T., & Sugino, T. (2002). Characterization of boron carbon nitride films with a low dielectric constant. *Diamond Relat. Mater*, Vol. 11, No. 3-6, pp. 985-988, ISSN 0925-9635
- Fainer, N.I., Rumyantsev, Yu.M., Kosinova, M.L., Yurjev, G.S., Maximovskii, E.A., & Kuznetsov F.A. (1997). The investigation of properties of silicon nitride films obtained by RPECVD from hexamethyldisilazane. *Appl. Surf. Sci.*, Vol. 113-114, pp. 614-617, ISSN 0169-4332
- Fainer, N.I., Kosinova, M.L., Rumyantsev, Yu.M. & Kuznetsov, F.A. (1999). RPECVD thin silicon carbonitride films using hexamethyldisilazane. *J. Phys. IV*, V. 9, pp.Pr8-769 - Pr8-775, ISSN 1155-4339
- Fainer, N.I., Kosinova, M.L., Yurjev, G.S., Rumyantsev, Yu.M. & Asanov, I.P. (2000). The structure study of thin boron and silicon carbonitride films by diffraction of synchrotron radiation. *NIMA.*, Vol. 448, No. 1-2, (June 2000), pp.294-298, ISSN 0168-9002
- Fainer, N.I., Kosinova, M.L., & Rumyantsev, Y.M. (2001). Thin films of silicon and boron carbonitrides: synthesis, composition and structure research. *Russ. Chem. J.*, Vol. XLV, No. 3., pp. 101-108, ISSN ISSN 0373-0247
- Fainer, N.I., Maximovskii, E.A., Kosinova, M.L., & Rumyantsev, Yu.M. (2001). The study of thermal annealing influence on structure and phase composition of silicon carbonitride by diffraction of synchrotron radiation. *Materials Science Forum*, Vol. 378-381, pp.493-498, ISSN 0255-5476
- Fainer, N.I., Maximovskii, E.A., Rumyantsev, Yu.M., Kosinova, M.L. & Kuznetsov, F.A. (2001). Study of structure and phase composition of nanocrystal silicon carbonitride films. *NIMA*. Vol. 470, No. 1, (September 2001), pp.193-197, ISSN 0168-9002
- Fainer, N.I., Rumyantsev, Yu.M., Golubenko, A.N., Kosinova, M.L., & Kuznetsov, F.A. (2003). Synthesis of nanocrystalline silicon carbonitride films by remote plasma enhanced chemical vapor deposition using the mixture of hexamethyldisilazane with helium and ammonia. *J. Cryst. Growth.*, Vol. 248, pp.175-179, ISSN 0022-0248
- Fainer, N.I., Kosinova, M.L., Rumyantsev, Yu.M., & Kuznetsov, F.A. (2004). Physical and chemical properties of silicon carbonitride nanocrystalline films. *J. Struct. Chem.*, Vol. 45, Supplement 1, (January 2004), pp. S65-S70, ISSN 0022-4766
- Fainer, N., Rumyantsev, Y., Kosinova, M., Maximovski, E., Kesler, V. (2007). Low-k dielectrics on base of silicon carbon nitride films. *Surf. Coat. Technol.*, Vol. 201, (April 2007), pp. 9269-9274, ISSN 0257-8972

- Fainer, N.I., Kosinova, M.L., Rumyantsev, Yu.M., Maximovskii, E.A., & Kuznetsov, F.A. (2008). Thin silicon carbonitride films are perspective low-k materials. *Journal of Physics and Chemistry of Solids*, Vol. 69, No. 2-3, (February-March 2008), pp. 661-668, ISSN 0022-3697
- Fainer, N.I., Bakovets, V.V., Kosinova, M.L., Rumayntsev, Yu.M., Maximovski, E.A., & Kuznetsov, F.A. (2008). SiCN coating as the protecting layer of quartz crucibles used for silicon crystallization. *Abstracts of 14-th APAM General Assembly and conference "State of materials research and new trends in material science"*, pp. 84-85, New Delhi, India, November, 2008
- Fainer, N.I., Golubenko, A.N., Rumyantsev, Yu.M., & Maximovskii, E.A. (2009). Use of Hexamethylcyclotrisilazane for Preparation of Transparent Films of Complex Compositions. *Glass Physics and Chemistry*, Vol.35, No.3, (August 2008), pp. 274-283, ISSN 1087-6596
- Fainer, N.I., Rumyantsev, Yu.M., Kesler, V.G., Maximovski, E.A. & Kuznetsov, F.A. (2009). Synthesis and thermal stability of nanocomposite $\text{Si}_x\text{N}_y\text{:H}$ films from cycle siliconorganic precursor. *ECS Trans.*, Vol. 25, No. 8, pp.921-926, ISSN 1938-5862
- Ferreira, E., Fortunato, I., Vilarinho, P., Viana, A.S., Ramos, A.R., Alves, E., & Martins, R., (2006). Hydrogenated silicon carbon nitride films obtained by HWCVD, PA-HWCVD and PECVD techniques. *Journal of Non-Crystalline Solids*, Vol.352, No.9-20, pp.1361-1366, ISSN 0022-3093
- Filipozzi, L., Derré, A., Conard, J., Piraux, L., & Marchand, A. (1995). Local order and electrical properties of boron carbonitride films. *Carbon*, Vol. 33, IsNo. 12, (August 1995), pp. 1747-1757; ISSN 0008-6223
- Filipozzi, L., Piraux, L., Marchand, A., Derré, A., Adouard, A., & Kinany-Alaoui, M. (1997). Unusual behavior of the magnetoresistance of boron carbonitride films at low temperature. *Journal of Materials Research*, Vol. 12 , IsNo. 07, (December 1996), pp.1711-1721
- Fitzpatrick, P.R., & Ekerdt, J.G., (2008). Film continuity and interface bonding of thin boron carbonitride films on Ge(100) and Si(100). *J. Vac. Sci. Technol.A*, Vol.26, No.6, pp.1397-1401, ISSN 0734-2101
- Freire Jr., F.L., Reigada, D.C., & Prioli, R. (2001). Boron Carbide and Boron-Carbon Nitride Films Deposited by DC-Magnetron Sputtering: Structural Characterization and Nanotribological Properties. *Physica status solidi (a)*, Vol. 187, No. 1, (July 2001), pp 1-12, ISSN 1862-6300
- Fu, Yo., Sun, C. Q, Du, H., & Yan, B. (2001). Crystalline carbonitride forms harder than the hexagonal Si-carbonitride crystallite. *J. Phys. D: Appl. Phys.*, Vol.34, No.9, pp.1430-1435, ISSN 0022-3727
- Fujiwara, H. (2007). *Spectroscopic Ellipsometry: Principles and Applications*. John Wiley & Sons Inc., ISBN 0-470-01608-6
- Fultz, B. & Howe, J. (2007). *Transmission Electron Microscopy and Diffractometry of Materials*. Springer, ISBN 3540738851
- Gago, R., Jimenez, I., & Albella J.M. (2000). Boron[carbon]nitrogen compounds grown by ion beam assisted evaporation. *Thin Solid Films* , Vol. 373, pp. 277-281, ISSN 0040-6090
- Gago, R., Jimenez, I., Sajavaara, T., Rauhala, E., & Albella, J.M., (2001). X-Ray absorption studies of cubic boron-carbon-nitrogen films grown by ion beam assisted evaporation. *Diamond and Related. Materials*, Vol.10, No.3-7, pp.1165-1169, ISSN 0925-9635

- Gago, R., Jimenez, I., Albella, J.M., & Terminello, L.J., (2001). Identification of ternary boron-carbon-nitrogen hexagonal phases by x-ray absorption spectroscopy. *Appl. Phys. Lett.*, Vol.78, (April 2001), pp.3430-3432, ISSN 0003-6951
- Gago, R., Jimenez, I., Agulló-Rueda, F., Albella, J.M., Czigány, Zs., & Hultman, L. (2002). Transition from amorphous boron carbide to hexagonal boron carbon nitride thin films induced by nitrogen ion assistance. *J. Appl. Phys.*, Vol. 92, No. 9, (August 2002), pp. 5177-5182, ISSN 0021-8979
- Gago, R.; Jimenez, I.; Garcia, I.; Albella, J.M., (2002). Growth and characterisation of boron-carbon-nitrogen coatings obtained by ion beam assisted evaporation. *Vacuum*, Vol.64, No.3-4, pp.199-204, ISSN 0042-207X
- Gago, R., Jimenez, I., Kreissig, U., & Albella, J.M. (2002). X-Ray absorption study of the bonding structure of BCN compounds enriched in carbon by CH₄ ion assistance. *Diamond and Relat.ed Mater.ials*, Vol. 11, pp. 1295-1299, ISSN 0925-9635
- Gammer, K., Kolber, T., Piplits, K., Nowikow, K., Tang, X., Haubner, R., & Hutter, H. (2002). Characterization of carbon-boron nitride-coatings prepared with chemical vapor deposition by auger electron spectroscopy, electron probe microanalysis and secondary ion mass spectrometry. *Thin Solid Films*, Vol. 406, (December 2001), pp. 98-102, ISSN 0040-6090
- Gao, P., Xu, J., Piao, Y., Ding, W., Wang, D., Deng, X., & Dong, C. (2007). Deposition of silicon carbon nitride thin films by microwave ECR plasma enhanced unbalance magnetron sputtering. *Surf. Coat. Technol.*, Vol. 201, No.9-11, pp.5298-5301, ISSN 0257-8972
- Gardiner, D.J. (1989). *Practical Raman spectroscopy*. Springer-Verlag, ISBN 978-0387502540
- Giessibl, F.J. (2003). Advances in atomic force microscopy. *Reviews of Modern Physics.* , Vol.75, No.3, pp.949-983, ISSN: 0034-6861
- Goldsmith, J.G.; , Lazof, D.B.; , & Linton, R.W. (1999). *Secondary ion mass spectrometry. Biomedical Applications of Microprobe Analyses*. Academic Press
- Goldstein, G.I.; Newbury, D.E.; Echlin, P.; Joy, D.C.; Fiori, C.; & Lifshin, E. (1981). *Scanning electron microscopy and x-ray microanalysis*. Plenum Press, New York, ISBN 030640768X
- Hasegawa, T., Yamamoto, K. & Kakudate, Y. (2002). Synthesis of B-C-N thin films by electron beam excited plasma CVD. *Diamond and Relat.ed Mater.ials*, Vol. 11, No.3-6, pp. 1290-1294, ISSN 0925-9635
- Hasegawa, T., Yamamoto, K. & Kakudate, Y. (2003). Influence of raw gases on B-C-N films prepared by electron beam excited plasma CVD. *Diamond Relat.ed Mater.ials*, Vol. 12, No.10-11, pp. 1945-1048, ISSN 0925-9635
- Hegemann, D., Riedel, R., Dreblner, W., Oehr, C., Schindler, B., & Brunner H. (1997). Boron Carbonitride Thin Films by PACVD of Single-Source Precursors. *Chem. Vap. Deposition*, Vol. 3, No. 5, pp.257-262, ISSN 1521-3862
- Hegemanna, D., Riedel, R., & Oehr C. (1999). Influence of single-source precursors on PACVD-derived boron carbonitride thin films. *Thin Solid Films*, Vol. 339, (August 1999), pp. 154-159, ISSN 0040-6090
- Hein, M., Hoffmann, P., Lieser, K.H., & Ortner, H., (1992). Application of X-ray fluorescence analysis with total-reflection (TXRF) in material science. *Fresenius J.Anal.Chem.*, Vol.343, No.9-10, pp.760-764, ISSN 0937-0633
- Hellgren, N., Berlind, T., Gueorguiev, G.K., Johansson, M.P., Stafström, S., & Hultman, L. (2004). Fullerene-like B-C-N thin films: a computational and experimental study. *Mater. Sci. Engin. B.*, Vol.113, No.3, (August 2004), pp.242-247, ISSN: 0921-5107

- Hemraj-Benny, T., Banerjee, S., Sambasivan, S., Balasubramanian, M., Fischer, D.A., Eres, G., Puretzky, A.A., Geohegan, D.B., Lowndes, D.H., Han, W., Misevich, J.A., & Wong, S.S. (2006). Near-Edge X-ray Absorption Fine Structure Spectroscopy as a Tool for Investigating Nanomaterials. *Small*, Vol.2, No.1, pp.26-35, online ISSN: 1613-6829
- Hirai, T., & Goto, T. (1981). Preparation of amorphous Si₃N₄-C plate by chemical vapour deposition. *Journal of Materials Science*, Vol. 16, No.1, pp.17-23, ISSN: 0022-2461
- Hoche, H., Allebrandt, D., Bruns, M., Riedel, R. & Fasel, C. (2008). Relationship of chemical and structural properties with the tribological behavior of sputtered SiCN films. *Surf. Coat. Technol.*, Vol.202, No.22-23, pp.5567-5571, ISSN 0257-8972
- Hoche H., Pusch C., Riedel R., Claudia F. & Klein A. (2010). Properties of SiCN coatings for high temperature applications – Comparison of RF-, DC- and HPPMS-sputtering. *Surf. Coat. Technol.*, Vol.205, Suppl.1, pp.S21-S27, ISSN 0257-8972
- Hoffmann, P.; Baake, O.; Beckhoff, B.; Ensinger, W.; Fainer, N.; Klein, A.; Kosinova, M.; Pollakowski, B.; Trunova, V.; Ulm, G.; Weser, J., (2007). Chemical bonding in carbonitride nanolayers. *Nuclear Instruments and Methods A*, Vol.575, No.1-2, pp.78-84, ISSN: 0168-9002
- Houška, J.; Vlček, J.; Potocký, Š.; Peřina, V., (2007). Influence of substrate bias voltage on structure and properties of hard Si-B-C-N films prepared by reactive magnetron sputtering. *Diamond and Related Materials*, Vol.16, No.1 (March 2006), pp.29-36, ISSN: 0925-9635.
- Ibberson, R.M.; David, W.I.F., (2002). Neutron powder diffraction. In: *Structure determination from powder diffraction data. IUCr monographs on crystallography*, Oxford scientific publications, ISBN 0-19-850091-2
- Ishimaru, M., Naito, M., Hirotsu, Y., & Sickafus, K. E. (2003). Amorphous structures of silicon carbonitride formed by high-dose nitrogen ion implantation into silicon carbide. *Nuclear Instruments and Methods in Physics Research B*, Vol.206, pp.994-998, ISSN 0168-583X
- Ivashchenko, L. A., Ivashchenko, V. I., Porada, O. K., Dub, S. M., Skrinkskii, P. L., Ushakov, M. V., Karpets, M. V., Stegnii, A. I., & Grishnova L. A. (2007). Hard plasma chemical coatings based on silicon carbon nitride. *Powder Metallurgy and Metal Ceramics*, Vol. 46, No.11-12, pp.543-549, ISSN 1068-1302
- Izumi, A., Oda, K. (2006). Deposition of SiCN films using organic liquid materials by HWCVD method. *Thin Solid Films*, Vol.501, No.1-2, pp.195-197, ISSN 0040-6090
- Jäschke, T.; Jansen, M., (2006). A new borazine-type single source precursor for Si/B/C/N ceramics. *J.Mater.Chem.*, Vol.16, No.27, pp.2792-2799, ISSN 0959-9428 DOI: 10.1039/B601939K
- Johansson, M. P., Ivanov, I., Hultman, L., Münger, E. P., & Schütze, A. (1996). Low-temperature deposition of cubic BN:C films by unbalanced direct current magnetron sputtering of a B4C target. *J. Vac. Sci. Technol. A*, Vol.14, No.6, (August 1996), p.3100-3108, ISSN 0734-2101
- Kafrouni, W., Rouessac, V., Julbe, A., & Durand, J. (2010). Synthesis and characterization of silicon carbonitride films by plasma enhanced chemical vapor deposition (PECVD) using bis(dimethylamino)dimethylsilane (BDMADMS), as membrane for a small molecule gas separation. *Appl. Surf. Sci.*, Vol. 257, No. 4, (December 2010), pp. 1196-1203, ISSN 0169-4332
- Kaner, R. B., Kouvetakis, J., Warble, C. E., Sattler, M. L., and Bartlett, N. (1987). Boron-carbon-nitrogen materials of graphite-like structure. *Materials Research Bulletin*, Vol. 22, IsNo. 3, (March 1987), pp. 399-404, ISSN: 0025-5408

- Kawaguchi, M., Nozaki, K., Kita, Y., & Doi, M. (1991). Photoluminescence characteristics of BN(C,H) prepared by chemical vapour deposition. *J. Mater. Sci.*, Vol.26, No.14, pp.3926-3930, ISSN 0022-2461
- Kawaguchi, M., & Bartlett, N. (1995). Syntheses, Structure, and Intercalation Chemistry of B/C/N Materials Based on the Graphite Network, In: *Fluorine-Carbon and Fluoride-Carbon Materials. Chemistry, Physics, and Applications*, Nakajima, T., pp.187-238, Marcel Dekker, Inc., New York-Basel-Hong Kong.
- Kawaguchi, M., Kawashima, T., Nakajima, T. (1996). Syntheses and Structures of New Graphite-like Materials of Composition BCN(H) and BC₃N(H). *Chem. Mater.*, Vol. 8, No. 6, pp.1197-1201, ISSN 0897-4756
- Kawaguchi, M. (1997). B/C/N Materials Based on the Graphite Network. *Adv.Mater.*, Vol.9, No. 8, pp.615-625, ISSN 1521-4095
- Kawaguchi, M., Sugiyama, A. (1997). Syntheses and characterization of graphite-like material of composition BC₆N₂(H). *Materials Science Research International*, Vol. 3, No.2, (1997) pp. 88-93, ISSN: 1341-1683
- Kawaguchi, M., & Wakukawa, Y. (1999). Synthesis of Graphite-like Material of Composition BC₆N by CVD method at high temperature. *Carbon*, Vol. 37, No. 1, pp.147-163, ISSN: 0008-6223
- Kawaguchi, M., Wakukawa, Y., & Kawano, T. (2001). Preparation and electronic state of graphite-like layered material BC₆N. *Synthetic Metals*, Vol. 125, IsNo. 2, July 2001, pp. 259-263, ISSN: 0379-6779
- Keeler, J.; (2005). *Understanding NMR Spectroscopy*. John Wiley & Sons. ISBN 0470017864
- Kida, T., Shigezumi, K., Mannan, Md. A., Akiyama, M., Baba, Y., & Nagano, M. (2009). Synthesis of boron carbonitride (BCN) films by plasma-enhanced chemical vapor deposition using trimethylamine borane as a molecular precursor. *Vacuum*, Vol. 83, pp. 1143-1146, ISSN 0042-207X
- Kim, D. H., Byon, E., Lee, S., Kim, J.-K. & Ruh, H. (2004). Characterization of ternary boron carbon nitride films synthesized by RF magnetron sputtering. *Thin Solid Films*, Vol. 447-448, pp. 192-196, ISSN 0040-6090
- Kimura, C., Okada, K., Funakawa, Sh., Sakata, Sh., & Sugino, T. (2005). Electron affinity and field emission characteristics of boron carbon nitride film. *Diamond Relat. Mater*, Vol. 14, No. 3-7, pp. 719-723, ISSN: 0925-9635
- Kimura, C., Sota, H., Aoki, H., & Sugino, T. (2009). Atomic bonds in boron carbon nitride films synthesized by remote plasma-assisted chemical vapor deposition. *Diamond Relat. Mater*, Vol. 18, No. 2-3, pp. 478-481, ISSN: 0925-9635
- Kosinova, M.L., Fainer, N.I., Rumyantsev, Yu.M., Golubenko, A.N., & Kuznetsov, F.A. (1999). LPCVD boron carbonitride films from triethylamine borane. *J. Phys. IV France*, Vol. 9, pp. Pr8-915- Pr8-921, ISSN 1155-4339
- Kosinova, M.L., Rumyantsev, Yu.M., Fainer, N.I., Maximovski, E.A., & Kuznetsov, F.A. (2001). The structure study of boron carbonitride films obtained by use of trimethylamine borane complex. *NIMA*, Vol. 470, pp. 253-257, ISSN 0168-9002
- Kosinova, M.L., Fainer, N.I., Sulayeva, V.S., Rumyantsev, Yu.M., Terauchi, M., Shibata, K., Satoh, F., Tanaka, M., & Kuznetsov, F.A. (2001). Structure and composition investigation of RPECVD SiCN and LPCVD BCN films. *J. Phys. IV France*, Vol. 11, pp. Pr3-987- Pr3-994, ISSN 1155-4339
- Kosinova, M. L., Rumyantsev, Yu. M., Golubenko, A. N., Fainer, N.I., Ayupov, B.M., Dolgovosova, I.P., Kolesov, B.A., Kaichev, V. V., & Kuznetsov, F.A. (2003). Chemical Composition of Boron Carbonitride Films Grown by Plasma-Enhanced

- Chemical Vapor Deposition from Trimethylamineborane. *Inorganic Mater.*, Vol. 39, No. 4, (May 2002), pp. 366-373, ISSN 0020-1685
- Kosinova, M.L., Fainer, N.I., Rumyantsev, Yu.M., Maximovski, E.A., Kuznetsov, F.A., Terauchi, M., Shibata, K., & Satoh, F. (2003). Growth of homogeneous and gradient BC_xN_y films by PECVD using trimethylamino borane complex. *ECS Proc.*, Vol. 2003-08, pp. 708-715, ISSN 1938-5862
- Kosinova, M.L., Fainer, N.I., Sulayeva, V.S., Rumyantsev, Yu.M., Kuznetsov, F.A., Maximovski, E.A., Cao, Z.X., Terauchi, M., Shibata, K., & Satoh, F. (2005). Synthesis, nanoindentation and AFM studies of CVD boron nitride films». *ECS Proc.*, Vol. 2005-09, pp.1082-1087, ISSN 1938-5862
- Kosolapova, T.Ya., Makarenko, G.N., Serebryakova, T.I., Prilutskii, E.V., Khorpyakov, O.T., & Chernysheva, O.I. (1971). Nature of boron carbonitride I. Conditions of preparation of boron carbonitride. *Powder Metallurgy and Metal Ceramics*, Vol. 10, No 1, pp. 22-26, ISSN 1068-1302
- Kouvetakis, J., Sasaki, T., Shen, C., Hagiwara, R., Lerner, M., Krishnan, K. M. & Bartlett, N. (1989). Novel aspects of graphite intercalation by fluorine and fluorides and new B/C, C/N and B/C/N materials based on the graphite network. *Synthetic Metals*, Vol. 34, IsNo. 1-3, pp. 1-7, ISSN: 0379-6779
- Kroke, E., Li, Y.-L., Konetschny, C., Lecomte, E., Fasel, C. , & Riedel, R. (2000). Silazane derived ceramics and related materials. *Mater. Sci. Eng.*, Vol. R26, No.4-6, (January 2000), pp.97-199, ISSN 0927-796X
- Kulisch, W. (2000). Deposition of Diamond-Like Superhard Materials in the B/C/N System. *Phys. stat. sol. (a)*, Vol. 177, No.1, (December 1999), pp. 63-79, ISSN 1862-6300
- Kurapov, D., Neuschütz, D., Cremer, R., Pedersen, T., Wuttig, M., Dietrich, D., Marx, G., & Schneider, J. M. (2002). Synthesis and mechanical properties of BCN coatings deposited by PECVD. *Vacuum*, Vol. 68, IsNo. 4, July 2002, pp.335-339, ISSN: 0042-207X.
- Kurapov, D. and Schneider, J. M. (2005). Structure, Composition, Mechanical, and Tribological Properties of BCN Films Deposited by Plasma Enhanced Chemical Vapor Deposition. *Plasma Chemistry and Plasma Processing*, Vol. 25, No. 6, (April 2005), pp.613-623, ISSN: 0272-4324.
- Kurmaev, E.Z.; ., Ezhov, A.V.; ., Shamin, S.N.; ., Cherkashenko, V.M.; ., Andreev, Y.G.; ., & Lundström, T., (1997). X-ray Emission Spectra and Structural Models of BCN Materials. *J.Alloys and Compounds*, Vol.248, No.1-2, pp.86-89, ISSN: 0925-8388
- Lambrecht, W.L., & Segall, B. (1993). Anomalous band-gap behavior and phase stability of c-BN-diamond alloys. *Phys. Rev. B*, Vol. B 47, No. 15, pp. 9289, ISSN 1098-0121
- Latrasse, L., Lacoste, A., Sánchez-López, J.C., Bès, A., Rayar, M. & Pelletier, J. (2009). High deposition rates of uniform films in tetramethylsilane-based plasmas generated by elementary microwave sources in matrix configuration. *Surf. Coat. Technol.*, Vol.203, No.16, (February 2009), pp.2343-2349, ISSN 0257-8972
- Lau, W.S., (1999). *Infrared characterization for microelectronics*. World Scientific. ISBN 9810223528
- Lei, M. K., Li, Q., Zhou, Z. F., Bello, I., Lee, C. S.& Lee, S. T. (2001). Characterization and optical investigation of BCN film deposited by RF magnetron sputtering. *Thin Solid Films*, Vol. 389, No. 1-2, (march March 2001), pp. 194-199, ISSN 0040-6090
- Levy, R.A., Mastromatteo, E., Grow, J.M., Paturi, V., & Kuo, W.P. (1995). Low pressure chemical vapor deposition of B-C-N-H films from triethylamine borane complex. *J. Mater. Res.* Vol. 10, No. 2, (October 1994), pp. 320-327, ISSN 0884-2914

- Li, W.L., Yang, J.L., Zhao, Y. & Fei, W.D. (2009). Effect of assistant RF plasma on structure and properties of SiCN thin films prepared by RF magnetron sputtering of SiC target. *J. Alloys Comp.*, Vol.482, pp.317-319, ISSN 0925-8388
- Limmanee, A., Otsubo, M., Sugiura, T., Sato, T., Miyajima, Sh., Yamada, A., & Konagai, M. (2008). Effect of thermal annealing on the properties of a-SiCN:H films by hot wire chemical vapor deposition using hexamethyldisilazane. *Thin Solid Films*, Vol. 516, No.5, pp.652-655, ISSN 0040-6090
- Lin, H.Y., Chen, Y.C., Lin, C.Y., Tong, Y.P., Hwa, L.G., Chen, K.H., & Chen, L.C. (2002). Field emission of nanostructured amorphous SiCN films deposited by reactive magnetron sputtering of SiC in CH₄/N₂ atmosphere. *Thin Solid Films*, Vol. 416, pp.85-91, ISSN 0040-6090
- Ling, H.,; Wu, J. D.,; Sun, J.,; Shi, W.,; Ying Z. F. & Li, F. M. (2002). Electron cyclotron resonance plasma-assisted pulsed laser deposition of boron carbon nitride films. *Diamond and Related Materials*, Vol. 11, No. 9 (February 2002), pp. 1623-1628. , ISSN 0925-9635.
- Linss, V., Rodil, S. E., Reinke, P., Garnier, M. G., Oelhafen, P., Kreissig, U. & Richter, F. (2004). Bonding characteristics of DC magnetron sputtered B-C-N thin films investigated by Fourier-transformed infrared spectroscopy and X-ray photoelectron spectroscopy. *Thin Solid Films*, Vol. 467, No. 1-2, (March 2004), pp. 76-87, ISSN 0040-6090
- Linss, V., Barzola-Quiquia, J., Häussler, P. & Richter, F. (2004). Structural properties of d.c. magnetron sputtered B-C-N thin films and correlation to their mechanical properties: a new empirical formula. *Thin Solid Films*, Vol. 467, No. 1-2, (March 2004), pp.66-75, ISSN 0040-6090
- Lippmann, G., (Coord.), (2006-2010). *Progress Summary 2009*. <http://www.google.de/search?client=firefox-a&rls=org.mozilla%3Ad>
- Liu A.Y., Wentzovitch R.A., & Cohen M.L. (1989). Atomic arrangement and electronic structure of BC₂N. *Phys. Rev. B*, Vol. B 39, No. 3, pp. 1760-1765, ISSN 1098-0121
- Liu, L., Wang, Y., Feng, K., Li, Y., Li, W., Zhao, Ch. & Zhao, Yo. (2006). Preparation of boron carbon nitride thin films by radio frequency magnetron sputtering. *Appl. Surf. Sci.*, Vol. 252, No. 12, (June 2005), pp. 4185-4189, ISSN 0169-4332
- Loeffler, J., Konyashin, I., Bill, J., Uhlig, H., & Aldinger, F. (1997). PACVD nano-crystalline B-C-N thin films obtained by use of an organoboron precursor. *Diamond and Related Materials*, Vol.6, No.5-7, pp.608-611, ISSN 0925-9635
- Loir, A.-S., Pech, D., Steyer, P., Gachon, Y., Herau, C., & Sanchez-Lopez, J. C., (2007). Study of the Si Chemical Bonding and the Semiconductive Behavior of the SiCN Coatings and their Correlation with Anti-Corrosion Properties. *Plasma Process. Polym.*, Vol. 4, pp.173-179, ISSN 1612-8850
- Lombardi, J.R. & Birke, R.L., (2008). An Unified Approach to Surface-Enhanced Raman Spectroscopy. *Journal of Physical Chemistry C*, Vol.112, No.14, pp.5605-5617, ISSN 1932-7447
- Lousa, A., Esteve, J., Muhl, S. & Martínez, E. (2000). BCN thin films near the B₄C composition deposited by radio frequency magnetron sputtering. *Diamond Relat. Mater.*, Vol. 9, No. 3-6, pp. 502-505, ISSN: 0925-9635
- Ma, R., & Bando, Y., (2003). Pyrolytic grown B-C-N and BN nanotubes. *Science & Technology of Advanced Materials*, Vol.4, No.5, pp.403-407, ISSN: 1468-6996
- Ma, S., Xu, B., Wu, G., Wang, Y., Ma, F., Ma, D., Xu, K. & Bell, T. (2008). Microstructure and mechanical properties of SiCN hard films deposited by an arc enhanced magnetic

- sputtering hybrid system. *Surf. Coat. Technol.*, Vol.202, No.22-23, pp.5379–5382, ISSN 0257-8972
- Majoulet, O.; Alauzun, J.G.; Gottardo, L.; Gervais, C.; Schuster, M.E.; Bernard, S.; & Miele, P., (2011). Ordered mesoporous silicoboron carbonitride ceramics from boron-modified polysilazanes: Polymer synthesis, processing and properties. *Microporous and Mesoporous Mater.*, Vol.140, No.1-3, (September 2010), pp.40-50, ISSN: 1387-1811.
- Mannan, Md.A., Nagano, M., Shigezumi, K., Kida, T., Hirao, N., & Baba, Y. (2008). Characterization of Boron Carbonitride (BCN) Thin Films Deposited by Radiofrequency and Microwave Plasma Enhanced Chemical Vapor Deposition. *Amer. J. Appl. Sci.*, Vol. 5, No.6, pp. 736-741, ISSN 1546-9239
- Mannan, Md.A.; Noguchi, H.; Kida, T.; Nagano, M.; Hirao, M.; Baba, Y., (2008). Chemical bonding states and local structures of the oriented hexagonal BCN films synthesized by microwave CVD. *Materials Science in Semiconductor Processing*, Vol.11, No.3, (May 2009), pp.100-105, ISSN: 1369-8001
- Mannan, Md.A.; Nagano, M.; Kida, T.; Hirao, N.; & Baba, Y.; (2009). Characterization of BCN films synthesized by radiofrequency plasma enhanced chemical vapor deposition. *J.Phys.Chem.Solids*, Vol.70, No.1, (August 2008), pp.20-25, ISSN 0022-3697
- Mannan, Md.A., Kida, T., Noguchi, H., Nagano, M, Shimoyama, I., Hirao, N., Baba, Y. (2009). Atomic arrangement, composition and orientation of hexagonal BCN films synthesized by radiofrequency plasma enhanced CVD. *J. Ceram. Soc. Jap.*, Vol.117, No.1364, (January 2009), pp.503-507, ISSN 1882-0743
- Mannan, Md.A., Noguchi, H., Kida T., Nagano, M, Hirao, N., Baba, Y. (2010). Growth and characterization of stoichiometric BCN films on highly oriented pyrolytic graphite by radiofrequency plasma enhanced chemical vapor deposition. *Thin Solid Films*, Vol. 518, No.15, (November 2009), pp. 4163–4169, ISSN 0040-6090
- Mannan, Md.A., Baba, Y., Kida, T., Nagano, M., Shimoyama, I., Hirao, N., & Noguchi, H., (2011). Orientation of B-C-N hybrid films deposited on Ni(111) and polycrystalline Ti substrates explored by X-ray absorption spectroscopy. *Thin Solid Films*, Vol.519, No.6, (September 2010), pp.1780-1786, ISSN: 0040-6090.
- Martínez, E., Lousa, A. & Esteve, J. (2001). Micromechanical and microtribological properties of BCN thin films near the B₄C composition deposited by r.f. magnetron sputtering. *Diamond Relat. Mater*, Vol. 10, No. 9-10, pp. 1892-1896, ISSN: 0925-9635
- Martínez, C., Kyrsta, S., Cremer, R. & Neuschütz, D. (2002). Influence of the composition of BCN films deposited by reactive magnetron sputtering on their properties. *Analytical and Bioanalytical Chemistry*, Vol. 374, No. 4, (July 2002), pp. 709-711, ISSN 1618-2642
- Maya L. (1988). Aminoborane polymers as precursors of C-N-B ceramic materials. *J. Am. Ceram. Soc.*, Vol.71, No. 12, pp.1104-1109
- Maya L. (1988). Semiconducting amorphous film containing carbon, nitrogen and boron. *J. Electrochem. Soc.*, Vol.135, No.5, pp.1278-1281, ISSN: 0013-4651
- Maya, L. & Harris, L.A., (1990). Pyrolytic deposition of carbon films containing nitrogen and/or boron. *J. Am. Ceram. Soc.*, Vol. 73, No.7, (February 1990), pp. 1912-191
- Mazumder, M. K., Aoki, H., Masuzumi, T., Hara, M., Watanabe, D., Kimura, C., Fukagawa, M., Umeda, M., Kusuhashi, M. & Sugino, T. (2009). Properties of boron carbon nitride (BCN) film after plasma ashing *Diamond Relat. Mater*, Vol. 18, No. 2-3, pp. 419-422, ISSN: 0925-9635

- Mishra, S.K., Bhattacharyya, A.S. (2008). Effect of substrate temperature on the adhesion properties of magnetron sputtered nano-composite Si-C-N hard thin films. *Materials Letters*, Vol. 62, No.3, (May 2007), pp.398–402, ISSN: 0167-577X
- Mishra, S. K. (2009). Nano and Nanocomposite Superhard Coatings of Silicon Carbonitride and Titanium Diboride by Magnetron Sputtering. *Int. J. Appl. Ceram. Technol.*, Vol. 6, pp.345–354, ISSN 1546-542X
- Montasser, K., Hattori, S., & Morita, S. (1984). Transparent B-C-N thin films formed by plasma chemical vapour deposition. *Thin Solid Films*, Vol.117, No. 4, pp.311-317, ISSN 0040-6090
- Montasser, K., Hattori, S., & Morita, S. (1985). Characterization of hard transparent B-C-N-H thin films formed by plasma chemical vapor deposition at room temperature. *J. Appl. Phys.*, Vol.58, No.8, pp.3185-3189
- Montasser, R., Morita, S., & Hattori, S. (1991). A promising boron-carbon-nitrogen thin film. *Mat. Sci. Forum...*, Vol.54-55, , pp.295-312, ISSN 0255-5476
- Moore, A. W., Strong, S. L., Doll, G. L., Dresselhaus, M. S, Spain, I. L., Bowers, C. W., Issi, J. P. and Piraux, L. (1989) Properties and characterization of codeposited boron nitride and carbon materials. *J. Appl. Phys.*, Vol.65, IsNo. 12, February 1989, pp.5109-5118
- Morant, C.; Prieto, P.; Bareño, J.; Sanz, J.M.; & Elizalde, E., (2006). Hard BC_xN_y thin films grown by dual ion beam sputtering. *Thin Solid Films*, Vol.515, No1, pp.207-211, ISSN: 0040-6090
- Morjan, I., Conde, O., Oliveira, M., & Vasiliu, F. (1999). Structural characterization of C_xB_yN_z (x=0.1 to x=0.2) layers obtained by laser-driven synthesis. *Thin Solid Films*, Vol. 340, pp. 95-105, ISSN 0040-6090
- Nakao, S., Sonoda, T., Tsugawa, K., Choi, J. & Kato, T. (2009). Effects of nitrogen gas ratio on composition and microstructure of BCN films prepared by RF magnetron sputtering. *Vacuum*, Vol. 84, No. 5, (June 2009), pp. 642-647, ISSN 0042-207X
- Nakayamada, T., Matsuo, K., Hayashi, Y., Izumi, A. & Kadotani, Y. (2008). Evaluation of corrosion resistance of SiCN films deposited by HWCVD using organic liquid materials. *Thin Solid Films*, Vol. 516, No.5, pp.656–658, ISSN 0040-6090
- Nesládek, M., Vaněček, M., Meykens, K., Haenen, K., Manca, J., De Schepper, L., Pace, E., Pini, A., Verona Rinati, G., Kimura, C., Etou, Y., & Sugino, T. (2001). Study of UV and Subgap Photocurrent Response in Diamond and BCN Thin Films for Detector Applications. *Physica status solidi (a)*, Vol. 185, No. 1, pp. 107–113, ISSN: 1862-6300
- O'Keefe, M.A.; Allard, L.F., (2004). Sub-Ångstrom Electron Microscopy for Sub-Ångstrom Nano-Metrology. *National Nanotechnology Initiative Workshop on Instrumentation and Metrology for Nanotechnology, Gaithersburg, MD (2004)*
- Okada, K., Kimura, C., & Sugino, T. (2006). Surface properties of boron carbon nitride films treated with plasma. *Diamond Relat. Mater*, Vol. 15, No. 4-8, pp. 1000-1003, ISSN: 0925-9635
- Oura, K.; Lifshits, V.G.; Saranin, A.A.; Zotov, A.V.; Katayama, M., (2003). *Surface Science: An Introduction*. Springer-Verlag, ISBN 3-540-00545-5
- Pagels, M.; Reinhardt, F.; Pollakowski, B.; Roczen, M.; Becker, C.; Lips, K.; Rech, B.; Kanngießner, B.; Beckhoff, B., (2010). GIXRF-NEXAFS investigations on buried ZnO/Si interfaces: A first insight in changes of chemical states due to annealing of the soecimen. *Nucl.Instr.Meth.B*, Vol.268, No.3-4, pp.370-373, ISSN: 0168-583X.

- Pan, W. J.; Sun, J.; Ling, H.; Xu, N.; Ying Z. F., & Wu, J. D. (2003). Preparation of thin films of carbon-based compounds. *Appl. Surf. Sci. Appl. Surf. Sci.*, Vol. 218, No. 1-4, (April 2003), pp. 298-305. , ISSN 0169-4332
- Peng, X., Song, L., Meng, J., Zhang, Y., & Hu. X., (2001). Preparation of silicon carbide nitride thin films by sputtering of silicon nitride target. *Appl. Surf. Sci.*, Vol.173, pp.313-317, ISSN 0169-4332
- Peng, Y., Zhou, J., Zhang, Z., Zhao, B., & Tan, X. (2010). Influence of radiofrequency power on compositional, structural and optical properties of amorphous silicon carbonitride films. *Appl. Surf. Sci.*, Vol.256, No.7, (September 2009), pp.2189-2192, ISSN 0169-4332
- Perrone, A.; Caricato, A. P.; Luches, A.; Dinescu, M.; Ghica, C.; Sandu, V., and & Andrei, A. (1998). Boron carbonitride films deposited by pulsed laser ablation. *Appl. Surf. Sci. Appl. Surf. Sci.*, Vol. 133, No. 4, (February 1998), pp. 239-242. , ISSN 0169-4332
- Polo, M.C., Martínez, E., Esteve, J. & Andújar, J.L. (1998). Preparation of B-C-N thin films by r.f. plasma assisted CVD. *Diamond and Relat.ed Mater.ials*, Vol. 7, No.2-5, pp. 376-379, ISSN 0925-9635
- Polo, M.C., Martínez, E., Esteve, J., & Andújar, J.L. (1999). Micromechanical properties of BN and B-C-N coatings obtained by r.f. plasma-assisted CVD. *Diamond Relat. Mater. Diamond Relat. Mater.*, Vol. 8, No.2-5, pp. 423-427, ISSN 0925-9635
- Popov, C., Saito, K., Ivanov, B., Koga, Y., Fujiwara, Sh. and Shanov, V. (1998) Chemical vapour deposition of BC₂N films and their laser-induced etching with SF₆. *Thin Solid Films*, Vol. 312, IsNo. 1-2, (August 1997), pp. 99-105, ISSN: 0040-6090
- Popov, C., Saito, K., Yamamoto, K., Ouchi, A., Nakamura, T., Ohana, Yo., & Koga, Yo. (1998) Synthesis of nitrogen-rich B-C-N materials from melamine and boron trichloride. *Journal of Materials Science*, Vol. 33, No. 5, pp.1281-1286, ISSN: 0022-2461
- Probst, D., Hoche, H., Zhou, Y., Hauser, R., Stelzner, T., Scheerer, H., Broszeit, E., Berger, C., Riedel, R., Stafast, H., & Koke, E. (2005). Development of PE-CVD Si/C/N:H films for tribological and corrosive complex-load conditions. *Surf. Coat. Technol.*, Vol. 200, No. 1-4, (1 October 2005), pp. 355- 359, ISSN 0257-8972
- Ray, S.C.; Tsai, H.M.; Chiou, J.W.; Jan, J.C.; Kumar, K.; Pong, W.F.; Chien, F.Z.; Tsai, M.-H.; Chattopadhyay, S.; Chen, L.C.; Chien, S.C.; Lee, M.T.; Lin, S.T.; & Chen, K.H., (2004). X-ray absorption studies of boron-carbon-nitrogen (B_xC_yN_z) ternary alloys. *Diamond Rel. Materials*, Vol.13, No.4-8, pp.1553-1557, ISSN: 0925-9635
- Reigada, D.C. & Freire, F.L. Jr. (2001). Nitrogen incorporation into boron carbide films deposited by dc-magnetron sputtering: film microstructure and tribological properties. *Surface and Coatings Technology*, Vol. 142-144, (July 2001), pp.889-893, ISSN: 0257-8972
- Rose, H.H.; (2008). Optics of high-performance electron microscopes. *Technology of Advanced Materials*, Vol.9, No.1, (March 2008), pp.014107, ISSN: 1468-6996
- Samsonov, G.V., Semenov, Yu.N., & Borodulin, P.Ya. (1962). Refractory materials on the base of boron nitride.
- Saugnas, F., Teyssandier, F., & Marchand, A. (1992). Characterization of C-B-N solid solutions deposited from a gaseous phase between 900° and 1050°C. *J Am. Ceram. Soc.*, Vol.75, No.1, pp.161-169, ISSN 1551-2916
- Schmolla W., Hartnagel H.L. (1983). Amorphous BN films produced in a double-plasma reactor for semiconductor application. *Solid State Electronics*, Vol.26, No.10, pp.931-939, ISSN 0038-1101

- Schonfelder, H., Aldinger, E., Riedel, R. (1993). Silicon carbonitrides - A novel class of materials, *J. de Physique IV*, Vol. 3, No. C7, pp.1293-1298, ISSN 1155-4339
- Shimada, Y., Chikamatsu, K., Kimura, C., Aoki, H., & Sugino, T. (2006). Effect of plasma treatment on interface property of BCN/GaN structure. *Appl. Surf. Sci.*, Vol. 253, No. 3, pp. 1459-1463, ISSN: 0169-4332
- Smirnova T.P., Badalian, A.M., Yakovkina, L.V., Kaichev, V.V., Bukhtiyarov, V.I., Shmakov, A.N., Asanov, I.P., Rachlin, V.I., & Fomina, A.N. (2003). SiCN alloys obtained by remote plasma chemical vapour deposition from novel precursors. *Thin Solid Films.*, Vol. 429, No. 1-2, (April), pp.144-151, ISSN 0040-6090
- Smirnova, T. P., Badalian, A. M., Borisov, V. O., Bakhturova, L. F., Kaichev, V. V., Podgorbunskaya, T. A., & Rakhlin V. I. (2008). Plasma-Chemical Deposition of SiCN Films from Volatile N-Bromhexamethyldisilazane. *Inorganic Materials.*, Vol. 44, No. 12, (November 2007), pp. 1312-1318, ISSN 0020-1685
- Solozhenko, V.L., Andraut, D., Mezouar, M., & Rubie, D.C. (2001). Synthesis of superhard cubic BC₂N. *Appl. Phys. Lett.*, Vol. 78, No. 10, (November 2000), pp. 1385-1387.
- Soto, G., Samano, E. C., Machorro, R., & Cota, L. (1998). Growth of SiC and SiC_xN_y films by pulsed laser ablation of SiC in Ar and N₂ environments. *J. Vac. Sci. Technol. A*, Vol.16, pp.1311-1315, ISSN 0734-2101
- Stanishevsky, A., Li, H., Badzian, A., Badzian, T., Drawl, W., Khriachtchev, L. & McDaniel, E. (2001). B-C-N coatings prepared by microwave chemical vapor deposition. *Thin Solid Films*, Vol. 398-399, pp. 270-274, ISSN 0040-6090
- Stelzner, Th., Arold, T. M., Falk, F., Stafast, H., Probst, D. & Hoche, H. (2005). Single source precursors for plasma-enhanced CVD of SiCN films, investigated by mass spectrometry. *Surf. Coat. Technol.*, Vol. 200, No. 1-4, (October 2005), pp. 372- 376, ISSN 0257-8972
- Stockel, S., Weise, K., Dietrich, D., Thamm, T., Braun, M., Cremer, R., Neuschütz, D., & G. Marx. (2002). Influence of composition and structure on the mechanical properties of BCN coatings deposited by thermal CVD. *Thin Solid Films.* , Vol. 420 -421, pp. 465-471, ISSN 0040-6090
- Stöckel, S., Weise, K., Thamm, T., Körner, K.-U., Dietrich, D., & Marx · G. (2003). Comparative investigations of structure and properties of BCN coatings deposited by thermal and plasma-enhanced CVD. *Anal. Bioanal. Chem.* Vol. 375, (November 2002), pp. 884-890, ISSN 1618-2642
- Stöhr, J., (1992). *NEXAFS Spectroscopy*. Springer, Berlin
- Sugimoto, Y.; ., Pou, P.; ., Abe, M.; ., Jelinek, P.; ., Perez, R.; ., Morita, S.; ., Custance, O.; (2007). Chemical identification of individual surface atoms by atomic force microscopy. *Nature*, Vol.446, No.7131, pp.64-67.
- Sugino, T. & Hieda, H. (2000). Field emission characteristics of boron carbon nitride films synthesized by plasma-assisted chemical vapor deposition. *Diamond Relat. Mater*, Vol. 9, No. 3-6, pp. 1233-1237, ISSN: 0925-9635
- Sugino, T., Tai, T. & Etou, Y. (2001). Synthesis of boron nitride film with low dielectric constant for its application to silicon ultralarge scale integrated semiconductors. *Diamond Relat. Mater*, Vol. 10, No. 3-7, pp. 1375-1379, ISSN: 0925-9635
- Sugino, T., Etou, Y., Tai, T., & Mori, H. (2002). Dielectric constant of boron carbon nitride films synthesized by plasma-assisted chemical-vapor deposition. *Appl. Phys. Lett.*, Vol. 80, No. 4, (November 2001), p. 649-652
- Sugino, T., Kimura, C. & Aoki, H. (2008). Surface properties and field emission of boron nitride. *Diamond Relat. Mater*, Vol. 17, No. 7-10, pp. 1764-1769, ISSN: 0925-9635

- Sugino, T., Kikuchi, J., Kawai, S., Kimura, C., & Aoki, H. (2010). Improved tunneling controlled field emission of Boron carbon nitride nanofilm. *Diamond Relat. Mater.*, Vol. 19, No. 5-6, pp. 545-547, ISSN: 0925-9635
- Sugiyama, T., Tai, T. & Sugino, T. (2002). Effect of annealing on dielectric constant of boron carbon nitride films synthesized by plasma-assisted chemical vapor deposition. *Appl. Phys. Lett.*, Vol.80, No. 22, April 2002, pp.4214-1 - 4214-4
- Sugiyama, T., Tai, T., Okamoto, A., Yoshitake, M., & Sugino, T. (2003). Influence of the annealing process on properties of Cu/BCN/p-Si structure. *Diamond Relat. Mater.*, Vol. 12, No. 3-7, pp. 1113-1116, ISSN: 0925-9635
- Sulyaeva, V.S., Rummyantsev, Yu.M., Kosinova, M.L., Golubenko, A.N., Fainer, N.I., & Kuznetsov, F.A. (2007). Plasma enhanced chemical vapour deposition of BC_xN_y films prepared from N-trimethylborazine: Modelling, synthesis and characterization. *Surf. Coat. Technol.*, Vol.201, No.22-23, April 2007, pp.9009-9014, ISSN 0257-8972
- Sulyaeva, V.S., Kosinova, M.L., Golubenko, A.N., Rummyantsev, Yu.M., Fainer, N.I., & Kuznetsov, F.A. (2009). PECVD BC_xN_y films from mixtures of N-trimethylborazine with hydrogen and ammonia: modelling, synthesis and characterization. *ECS Transaction*, Vol.25, No. 8, part 1. , pp. 343-348, ISSN 1938-5862
- Sulyaeva, V. S., Kosinova, M. L., Rummyantsev, Yu. M., Golubenko, A. N., Fainer, N. I., Alferova, N. I., Ayupov, B. M., Gevko, P. N., Kesler, V. G., Kolesov, B. A., Maksimovskii, E. A., Myakishev, K. G., Yushina, I. V., & Kuznetsov, F. A. (2010). Properties of BC_xN_y Films Grown by Plasma Enhanced Chemical Vapor Deposition from N-Trimethylborazine-Nitrogen Mixtures. *Inorganic Materials*, Vol. 46, No. 5, pp. 487-494, ISSN 0020-1685
- Suvorova, A. A., Nunney, T., & Suvorov, A. V. (2009). Fabrication of Si-C-N compounds in silicon carbide by ion implantation. *Nuclear Instruments and Methods in Physics Research B*, Vol. 267, No. 8-9, pp. 1294-1298, ISSN 0168-583X
- Swain, B. P., Hwang, N. M. (2008). Study of structural and electronic environments of hydrogenated amorphous silicon carbonitride (a-SiCN:H) films deposited by hot wire chemical vapor deposition. *Appl. Surf. Sci.*, Vol. 254, No.17, (February 2008), pp.5319-5322, ISSN 0169-4332
- Tai, T., Sugiyama, T., & Sugino, T. (2003). Growth and characterization of boron carbon nitride films with low dielectric constant. *Diamond Relat. Mater.*, Vol. 12, No. 3-7, pp. 1117-1121, ISSN: 0925-9635
- Taylor, R.; , Hare, J.P.; , Abdul-Sada, A.K.; , & Kroto, H.W., (1990). Isolation, separation and characterization of the fullerenes C60 and C70: the third form of carbon. *Journal of the Chemical Society, Chemical Communications* Vol.20, pp.1423-1425. , ISSN: 0022-4936.
- Teodorescu, V.S.; , Luches, A.; , Dinu, R.; , Zocco, A.; , Ciobanu, M.F.; , Martino, M.; , Sandu, V. and & Dinescu, M. (1999). Influence of the substrate temperature on BCN films deposited by sequential pulsed laser deposition. *App. Phys. A: Mater. Sci. & Proces.*, Vol. 69, No. 7, pp.5667-5670. , ISSN 0947-8396
- Thamm, T., Körner, K.-U., Bohne, W., Strub, E., Röhrich, J., Stöckel, S., & Marx G. (2005). Characterization of PECVD boron carbonitride layers. *Appl. Surf. Sci., Appl. Surf. Sci.*, Vol. 252, No.1, (March 2005), pp. 223-226, ISSN 0169-4332
- Thamm; T., Wett, D., Bohne, W., Strub, E., Röhrich, J., Szargan, R., Marx, G., & Goedel, W.A. (2007). Investigations on PECVD boron carbonitride layers by means of


- ERDA, XPS and nano-indentation measurements. *Microchim. Acta.*, Vol. 156, No.1-2, (April 2006), pp. 53-56, ISSN: 0026-3672
- Thäringen, T., Lippold, G., Riede, V., Lorenz, M., Koivusaari, K. J., Lorenz, D., Mosch, S., Grau, P., Hesse, R., Streubel, P., & Szargan, R. (1999). Hard amorphous CSixNy thin films deposited by RF nitrogen plasma assisted pulsed laser ablation of mixed graphite/Si3N4-targets. *Thin Solid Films*, Vol. 348, pp.103-113, ISSN 0040-6090
- Ting, S.-F., Fang, Y.-K., Hsien, W.-T., Tsair, Y.-S., Chang, C.-N., Lin, C.-S., Hsieh, M.-C., Chiang, H.-C., & Ho, J.-J. , (2002). Heteroepitaxial Silicon-Carbide Nitride Films with Different Carbon Sources on Silicon Substrates Prepared by Rapid-Thermal Chemical-Vapor Deposition. *Journal of Electronic materials*, Vol. 31, No.12, pp.1341-1346, ISSN 0361-5235
- Tomasella, E., Rebib, F., Dubois, M., Cellier, J., & Jacquet, M. (2008). Structural and optical properties studies of sputtered a-SiCN thin films. *Journal of Physics: Conference Series*, Vol.100, (February 2008), pp.082045. ISSN 1742-6596
- Tompkins, H.G., (2006). *A User's Guide to Ellipsometry*. Dover Publications Inc., Mineola, ISBN 0-486-45028-7
- Torres, R.; , Caretti, I.; , Gago, R.; , Martin, Z.; , Jimenéz, I., (2007). Bonding structure of BCN nanopowders prepared by ball milling. *Diamond Rel. Materials*, Vol.16, No.4-7, pp.1450-1454, ISSN: 0925-9635
- Trusso, S., Barreca, F., & Neri, F. (2002). Bonding configurations and optical band gap for nitrogenated amorphous silicon carbide films prepared by pulsed laser ablation. *J. Appl. Phys.*, Vol. 92, No.5, pp.2485-2489, ISSN 0021-8979
- Tsai, P.-C. (2007). The deposition and characterization of BCN films by cathodic arc plasma evaporation. *Surf. Coat. Technol. Surf. Coat. Technol.*, Vol. 201, (August 2007), pp. 5108-5113, ISSN 0257-8972
- Uddin, Md.N., Shimoyama, I., Baba, Y., Sekiguchi, T., Nath, K.G., & Nagano, M. (2005). B-C-N hybrid synthesis by high-temperature ion implantation. *Appl. Surf. Sci., Appl. Surf. Sci.* Vol.241, (October 2004), pp. 246-249, ISSN 0169-4332
- Uddin, Md.N., Shimoyama, I., Baba, Y., Sekiguchi, T., Nath, K.G. & Nagano, M. (2006). Synthesis and characterization of oriented graphitelike B-C-N hybride. *J.Appl. Phys.*, Vol.99, (February 2006), pp. 084902-1 - 084902-5
- Uddin, Md.N., Shimoyama, I., Baba, Y., Sekiguchi, T., & Nagano, M. (2006). X-ray photoelectron spectroscopic observation on B-C-N hybrids synthesized by ion beam deposition of borazine. *J.Vac.Sci.Technol. A*, Vol.23, No.3, (February 2005), pp. 497-502
- Ulrich, S., Ehrhardt, H., Theel, T., Schwan, J., Westermeyr, S., Scheib, M., Becker, P., Oechsner, H., Dollinger, G. & Bergmaier, A. (1998). Phase separation in magnetron sputtered superhard BCN thin films. *Diamond Relat. Mater*, Vol. 7, No. 6, (October 1997), pp. 839-844, ISSN: 0925-9635
- Ulrich, S., Kratzsch, A., Leiste, H., Scheib, M., Schloßmacher, P., Holleck, H., Binder, J., Schild, D., Westermeyr, S., Becker, P., & Oechsner, H. (1999). Variation of carbon concentration, ion energy, and ion current density of magnetron-sputtered boron carbonitride films. *Surface and Coatings Technology*, Vol. 116-119, pp. 742-750. ISSN: 0257-8972
- Umeda, Sh., Yuki, T., Sugiyama, T., & Sugino, T. (2004). Boron carbon nitride film with low dielectric constant as passivation film for high speed electronic devices. *Diamond Relat. Mater*, Vol. 13, No. 4-8, pp. 1135-1138, ISSN: 0925-9635

- Van Grieken, R.; Markowicz, A. (Eds.), (2002). *Handbook of X-ray Spectrometry*. Marcel Dekker, New York
- Vassallo, E., Cremona, A., Ghezzi, F., Dellera, F., Laguardia, L., Ambrosone, G., & Coscia, U. (2006). Structural and optical properties of amorphous hydrogenated silicon carbonitride films produced by PECVD. *Appl. Surf. Sci.*, Vol. 252, No. 22, (8 October 2005), pp. 7993-8000, ISSN 0169-4332
- Vlcek, J., Kormunda, M., Cizek, J., Perina, V., & Zemek, J. (2002). Influence of nitrogen-argon gas mixtures on reactive magnetron sputtering of hard Si-C-N films. *Surface and Coatings Technology*, Vol.160, pp.74-81, ISSN 0257-8972
- Voronkov, M.G., Sulimin, A.D., Yachmenev, V.V., Mirskov, R.G., Kokin, V.N., & Chernova, V.G. (1981). Production of silicon nitride films from hexamethylcyclotrisilazane in high-frequency glow discharge. *Dokl. AN USSR.*, Vol. 259, No.5, pp.1130-1132, ISSN 0002-3264 (in Russian)
- Wada, Y.; Yap, Y. K.; Yoshimura, M.; Mori, Y. & Sasaki, T. (2000). The control of B-N and B-C bonds in BCN films synthesized using pulsed laser deposition. *Diamond and Related Materials*, Vol. 9, No. 3-6, pp. 620-624. , ISSN 0925-9635
- Wang E.G. (1999). A new development in covalently bonded carbon nitride and related materials. *Adv. Mater.*, Vol.11. , No.13, pp.1129-1133, ISSN 1521-4095
- Wang, Z.-C.; Kamphowe, T.W.; Katz, S.; Peng, J.; Seifert, H.J.; Bill, J.; & Aldinger, F., (2000). Effects of polymer thermolysis on composition, structure and high-temperature stability of amorphous silicoboron carbonitride ceramics. *J.Mater.Sc.Letters*, Vol.19, No.19, pp.1701-1704, ISSN: 0261-8028.
- Watanabe, D., Aoki, H., Moriyama, R., Mazumder, M. K., Kimura, C. & Sugino, T. (2008). Characterization of BCN film after wet process for interconnection integration. *Diamond Relat. Mater*, Vol. 17, No. 4-5, pp. 669-672, ISSN: 0925-9635
- Watanabe, M. O., Itoh, S., Mizushima, K., and Sasaki, T. (1995). Electrical properties of BC₂N thin films prepared by chemical vapor deposition. *J. Appl. Phys.*, Vol.78, No. 4, May 1995, pp.2880-2883
- Watanabe, M. O., Itoh, S., Mizushima, K., and Sasaki, T. (1996). Bonding characterization of BC₂N thin films. *Appl. Phys. Lett.*, Vol.68, IsNo. 21, (March 1996), pp.2962-2964 (3 pages)
- Watanabe, M.O., Sasaki, T., Itoh, S. and Mizushima, K. (1996) Structural and electrical characterization of BC₂N thin films. *Thin Solid Films*, Vol. 281-282, pp. 334-336, ISSN: 0040-6090
- Weber, A., Bringmann, U., Klages, C.P., Taube, K., Döllein, G., Meyer, H., & Weidenbach, G. (1992). Plasma deposition of BN, BCN:H and Me-BCN:H films using N-trimethylborazine (Me = Ti, Nb). *J. de Phys. III*, Vol. 2, No.8, (April 1992), pp. 1391-1398
- Weber, A., Bringmann, U., Nikulski, R., & Klages, C.-P. (1993). Growth of cubic boron nitride and boron-carbon-nitrogen coatings using N-trimethylborazine in an electron cyclotron resonance plasma process. *Diamond and Related. Materials*, Vol. 2, No. 2-4, (March 1993), pp. 201-206, ISSN 0925-9635
- Weissenbacher, R., Haubner, R., Aigner, K., & Lux B. (2002). Interactions of Ta-filaments during hot-filament CVD of BCN-layers. *Diamond and Related Materials*, Vol. 11, No.2, (October 2001), pp. 191-197, ISSN 0925-9635
- Weissenbacher, R., Haubner, R. (2003). HF-CVD of B, C, N containing layers on various substrates by the decomposition of Triethylborazine. *Diamond and Related. Materials*, Vol. 12, No.3-7, pp. 884-890, ISSN 0925-9635

- Weissenbacher, R., Haubner, R. (2006). Deposition of B, C, N coatings on WC-Co substrate – Analytical problems indicating c-BN formation. *Int. J. Ref. Met. Hard Mater.*, Vol. 24, No.5, (November 2005), pp.374-379, ISSN 0263-4368
- White, R., (1990). *Chromatography/Fourier transform infrared spectroscopy and its applications*. Marcel Dekker, New York.
<http://books.google.com/books?id=t2VSNnFoO3wC&pg=PA7>
- Wöhle, J., Ahn, H., & Rie, K.-T., (1999). BCN coatings on polymer substrates by plasma CVD at low temperature. *Surf. Coat. Technol.Surf. Coat. Technol.*, Vol. 116-119, pp. 1166-1171, ISSN 0257-8972
- Wrobel, A.M., Blaszczyk-Lezak, I., & Walkiewicz-Pietrzykowska, A. (2007). Silicon Carbonitride Thin-Film Coatings Fabricated by Remote Hydrogen–Nitrogen Microwave Plasma Chemical Vapor Deposition from a Single-Source Precursor: Growth Process, Structure, and Properties of the Coatings. *Journal of Applied Polymer Science.*, Vol. 105, No. 1, (July 2007), pp.122-129, ISSN 0021-8995
- Wrobel, A. M., Blaszczyk-Lezak, I., Uznanski, P., & Glebocki, B. (2010). Silicon Carbonitride (SiCN) Films by Remote Hydrogen Microwave Plasma CVD from Tris(dimethylamino)silane as Novel Single-Source Precursor. *Chem. Vap. Deposition.*, Vol.16, No.7-9 (September 2010), pp. 211-215, ISSN 0948-1907
- Wu, F.; Valle, N.; Fitzpatrick, R.; Ekerdt, J.G.; Houssiau, L.; Migeon, H.-N., (2011). Elaboration and quantitative investigation of BCN-type films by dynamic SIMS using the MCs_x+mode. *Surf.Interface Anal.*, Vol. 43, No. 1-2, pp. 669-672
- Wu, J.-J., Wu, C.-T., Liao, Y. -C., Lu, T.-R., Chen, L.C., Chen, K.H., Hwa, L.-G., Kuo, C.-T., & Ling, K.-J. (1999). Deposition of silicon carbon nitride films by ion beam sputtering. *Thin Solid Films*, Vol. 355-356, pp. 417-422, ISSN 0040-6090
- Xiao, X.-Ch., Li,Ya-W., Song, Li-X., Peng, X.-F., & Hu, X.-F. (2000). Structural analysis and microstructural observation of SiC_xN_y films be reactive sputtering of SiC in N₂ and Ar. *Appl. Surf. Sci.*, Vol. 156, No. 1-4, (February 2000), pp.155-160, ISSN 0169-4332
- Xie, Z.Y., Edgar, J.H., McCormick, T.L, & Sidorov, M.V. (1998). The effects of the simultaneous addition of diborane and ammonia on the hot-filament-assisted chemical vapor deposition of diamond II. Characterization of diamond and BCN film. *Diamond and Relat.ed Mater.ials*, Vol.7, No.9, pp.1357-1363, ISSN 0925-9635
- Xu, S.; Ma, X.; Tang, G., (2006). A Study of Nano-Mechanical Properties and Nano-Scratch Behaviour of Boron Carbonitride Films. *J.Nanoscience and Nanotechnology*, Vol.6, No.5, pp. 1441-1446, ISSN:1533-4880
- Xu, Sh., Ma, X., & Su, M. (2006). Investigation of BCN Films Deposited at Various N₂/Ar Flow Ratios by DC Reactive Magnetron Sputtering Plasma Science, *IEEE Transactions on Issue Date*, Vol. 34, No.4, pp. 1199 - 1203, ISSN 0093-3813.
- Yang, Q.; Wang, C.B.; Zhang, S.; Zhang, D.M.; Shen, Q., & Zhang, L.M. (2010). Effect of nitrogen pressure on structure and optical properties of pulsed laser deposited BCN thin films. *Surf. Coat. Technol.Surf. Coat. Technol.*, Vol. 204, No. 11, (November 2009), pp. 1863-1867, ISSN 0257-8972
- Yang, T.-S., Tsai, T.-H., Lee, Ch.-H., Cheng, Ch.-L. , & Wong, M.-Sh. (2001). Deposition of carbon-containing cubic boron nitride films by pulsed-DC magnetron sputtering *Thin Solid Films*, Vol. 398-399, pp. 285-290, ISSN 0040-6090
- Yang, Z.-H.; Jia D.-C.; Duan, X.-M.; Zhou, Y., (2010). Microstructure and thermal stabilities in various atmospheres of SiB_{0.5}C_{1.5}N_{0.5} nano-sized powders fabricated by mechanical alloying technique. *J.Non-Crystalline Solids*, Vol.356, No.6-8, pp.326-333, ISSN: 0022-3093

- Yap, Y. K.; Wada, Y.; Yamaoka, M.; Yoshimura, M.; Mori, Y., & Sasaki, T. (2001). Bond modification of BCN films on Ni substrate. *Diamond and Related Materials*, Vol. 10, No. 3-7, (December 2001), pp. 1137-1141. , ISSN 0925-9635
- Yap, Y.K. (Ed.). (2009). *B-C-N Nanotubes and Related Nanostructures*, Springer, ISBN 978-1-4419-0085-2, London, New York.
- Yap, Y.K., Wada, Y., Yamaoka, M., Yoshimura, M., Mori, Y., & Sasaki, T., (2001). Bond modification of BCN films on Ni substrate. *Diamond Related Mater.*, Vol.10, No.3-7, pp.1137-1141, ISSN: 0925-9635
- Yasui, K., Fukuda, K., Katoh, H., & Kaneda, Sh. (1989). The influence of carbon addition on the internal stress and chemical inertness of amorphous silicon-nitride films. *Journal of Non-Crystalline Solids*, Vol. 111, No.1-3, pp.173-177, ISSN 0022-3093
- Yasui, H., Hirose, Y., Awazu, K., & Iwaki, M. (2000). The properties of BCN films formed by ion beam assisted deposition. *Colloids and Surfaces B: Biointerfaces*, Vol. 19, pp. 291-295, ISSN
- Ying, Z.F.; Yu, D.; Ling, H.; Xu, N.; Lu, Y.F.; Sun J., & Wu, J.D. (2007). Synthesis of BCN thin films by nitrogen ion beam assisted pulsed laser deposition from a B₄C target. *Diamond Relat. Mater.*, Vol. 16, No. 8 (January 2007), pp. 1579-1585, ISSN: 0925-9635
- Yokomichi, H., Funakawa, T., & Masuda, A. (2002). Preparation of boron-carbon-nitrogen thin films by magnetron sputtering. *Vacuum*, Vol. 66, No. 3-4, pp. 245-249, ISSN 0042-207X
- Yokomichi, H., Futakuchi, T., Yasuoka, M., & Kishimoto, N. (2004). Fabrication of amorphous boron-carbon-nitrogen films by hot-wire CVD. *Journal of Non-Crystalline Solids*, Vol. 338-340, June 2004, pp. 509-512, ISSN 0022-3093
- Yokoshima, S., Goto, T., & Hirai, T. (1990). Dielectric properties of BN-C thick films prepared by chemical vapor deposition. *Proceed. 28th Symposium on the Basic Science of Ceramics*, pp.116-119, Fukuoka, Japan, 1990
- Yu J., & Wang E.G (1999). Turbostratic boron carbonitride film and its field-emitting behavior. *Appl. Phys. Lett.*, Vol.74, No.20, pp.2948-2950, ISSN 0003-6951
- Yu J., Wang E.G., & Xu G. (1999). Synthesis and characterization of B-C-N on molybdenum. *J. Mater. Res.* Vol.14, No.3, Ppp.1137-1141, ISSN 0884-2914
- Yue, J., Cheng, W., Zhang, X., He, D., & Chen, G. (2000). Ternary BCN thin films deposited by reactive sputtering. *Thin Solid Films*, Vol. 375, (November 1999), pp. 247-250, ISSN 0040-6090
- Yuki, T., Umeda, Sh., & Sugino, T. (2004). Electrical and optical characteristics of boron carbon nitride films synthesized by plasma-assisted chemical vapor deposition. *Diamond Relat. Mater.*, Vol. 13, Issues No.4-8, pp. 1130-1134, ISSN 0925-9635
- Zhang, Y., Sun, H., & Chen, C.F. (2004). Superhard Cubic BC₂N Compared to Diamond. *Phys. Rev. Lett.*, Vol. 93, No. 19, pp.195504-1 - 195504-4, ISSN 0031-9007
- Zhang, Zh., Kimura, C., & Sugino, T. (2005). Wavelength-dependent effect of ultraviolet irradiation on dielectric constant of boron carbon nitride films *J. Appl. Phys.*, Vol. 98, No. 3, June 2005, pp. 036105-1 - 036105-4
- Zhou, F., Adachi, K., & Kato, K., (2006). Influence of deposition parameters on surface roughness and mechanical properties of boron carbon nitride coatings synthesized by ion beam assisted deposition. *Thin Solid Films*, Vol.497, No. 1-2, (October 2005), pp.210-217, ISSN: 0040-6090.

- Zhou, F., Adachi, K., & Kato, K. (2006). Comparoson of tribological property of a-C, a-CN_x and BCN coatings sliding against SiC balls in water. *Surf. Coat. Technol.Surf. Coat. Technol*, Vol. 200, (March 2005), pp. 4471-4478, ISSN 0257-8972
- Zhou, F., Adachi, K., & Kato, K. (2006). Friction and wear behavior of BCN coatings sliding against ceramic and steel balls in various environments. *Wear*, Vol. 261, (October 2005), pp. 301-310, ISSN 0043-1648
- Zhou, F., Yue, B., Wang, X., Wu, X. & Zhuge L. (2010). Surface roughness, mechanical properties and bonding structure of silicon carbon nitride films grown by dual ion beam sputtering. *J. Alloys Compounds*, Vol.492, No. 1-2, (March 2010), pp.269-276, ISSN 0925-8388
- Zhou, Y., Probst, D., Thissen, A., Kroke, E., Riedel, R., Hauser, R., Hoche, H., Broszeit, E., Kroll, P. & Stafast H. (2006). Hard silicon carbonitride films obtained by RF-plasma-enhanced chemical vapour deposition using the single-source precursor bis(trimethylsilyl)carbodiimide. *J.Europ. Ceram. Soc.*, Vol. 26, No. 8, (4 February 2005), pp.1325-1335, ISSN 0955-2219
- Zhou, Z. F., Bello, I., Lei, M. K., Li, K. Y., Lee, C. S., & Lee, S. T. (2000). Synthesis and characterization of boron carbon nitride films by radio frequency magnetron sputtering. *Surf. Coat. Technol.Surf. Coat. Technol*, Vol. 128-129, pp. 334-340, ISSN 0257-8972
- Zhuang, Ch., Zhao, J., Jia, F., Guan, Ch., Wu, Zh., Bai, Y. & Jiang, X. (2009). Tuning bond contents in B-C-N films via temperature and bias voltage within RF magnetron sputtering. *Surf. Coat. Technol.Surf. Coat. Technol*, Vol. 204, No 5, (September 2009), pp. 713-717, ISSN 0257-8972



Silicon Carbide - Materials, Processing and Applications in Electronic Devices

Edited by Dr. Moumita Mukherjee

ISBN 978-953-307-968-4

Hard cover, 546 pages

Publisher InTech

Published online 10, October, 2011

Published in print edition October, 2011

Silicon Carbide (SiC) and its polytypes, used primarily for grinding and high temperature ceramics, have been a part of human civilization for a long time. The inherent ability of SiC devices to operate with higher efficiency and lower environmental footprint than silicon-based devices at high temperatures and under high voltages pushes SiC on the verge of becoming the material of choice for high power electronics and optoelectronics. What is more important, SiC is emerging to become a template for graphene fabrication, and a material for the next generation of sub-32nm semiconductor devices. It is thus increasingly clear that SiC electronic systems will dominate the new energy and transport technologies of the 21st century. In 21 chapters of the book, special emphasis has been placed on the "materials" aspects and developments thereof. To that end, about 70% of the book addresses the theory, crystal growth, defects, surface and interface properties, characterization, and processing issues pertaining to SiC. The remaining 30% of the book covers the electronic device aspects of this material. Overall, this book will be valuable as a reference for SiC researchers for a few years to come. This book prestigiously covers our current understanding of SiC as a semiconductor material in electronics. The primary target for the book includes students, researchers, material and chemical engineers, semiconductor manufacturers and professionals who are interested in silicon carbide and its continuing progression.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

P. Hoffmann, N. Fainer, M. Kosinova, O. Baake and W. Ensinger (2011). Compilation on Synthesis, Characterization and Properties of Silicon and Boron Carbonitride Films, Silicon Carbide - Materials, Processing and Applications in Electronic Devices, Dr. Moumita Mukherjee (Ed.), ISBN: 978-953-307-968-4, InTech, Available from: <http://www.intechopen.com/books/silicon-carbide-materials-processing-and-applications-in-electronic-devices/compilation-on-synthesis-characterization-and-properties-of-silicon-and-boron-carbonitride-films>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元

Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

Phone: +86-21-62489820
Fax: +86-21-62489821

© 2011 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.